

 EKİN ENDÜSTRİYEL



**Fluid Chart**

[www.ekinendustriyel.com](http://www.ekinendustriyel.com)



### ► Heat Transfer Products

- Plate Heat Exchangers
- Spare Parts For Plate Heat Exchangers
- Brazed Heat Exchangers
- Tube Heat Exchangers

### ► Pressure Vessels

- Accumulation Tanks
- Water Heater Tanks
- Stainless Steel Tanks
- Separators

### ► Package Systems

- Heat Substations
- Pasteurizers
- Flat Access Substations

### ► Fluid Transfer Products

- Rotary Lobe Parts
- Hygienic Centrifuge Pumps
- Centrifugal Pumps With Magnetic Coupling
- Solenoid Dosing Pumps
- Air Diaphragm Pumps
- Diffusers
- Blowers



ISO  
9001:2015

JAS-ANZ

CE

PG  
GOST CERTIFICATE  
799 33 13

TSE-HYB

TURQUM®  
TURKISH QUALITY OF MANAGEMENT

## Sustainable Innovation, Quality Standardization and Dynamism

Ekin Industrial has entered Turkey's sector of imported plate heat exchanger, with their customer focused vision and dynamic. Ekin has expanded into new and upcoming investments.

One of the main steps was gaining the identity of being a producer. Ekin Industrial has started the production of plate heat exchangers with the brand of 'MIT'.

We grew in the philosophy of quality, through initially adapting to ISO Quality Management System procedures, and completed the CE security and quality certification period, and has matched foreign standards like GOST.

MIT plate heat exchangers have now become a solution to engineering problems in the world market and has grown through an expansion of franchises.

### Engineering Approachments, Integrated Solutions


Ekin Industrial, with investment in MIT plate heat exchangers, their identity of producer and engineer vision is aiming to solve problems in the sector. To meet these views, Ekin Industrial has expanded into the production of components, sales and after sales service by employing expert engineers.

The factors that guided Ekin Industrial to success are their exceptional customer service to the needs and wants of consumers, modern facilities, and becoming partners to projects that involve high-end technology.

Ekin Industrial is an expert company which has wide product range which includes plate heat exchangers, accumulation tanks, water heater tanks, installation materials and its service group and submit competitive advantages to mechanical installation sector in Turkey and all around the World.

4

Follow Us on Social Media



EKİN ENDÜSTRİYEL



[www.facebook.com / ekinendustriyeltr](http://www.facebook.com/ekinendustriyeltr)



[www.linkedin.com/company / ekinendustriyel](http://www.linkedin.com/company/ekinendustriyel)



[www.youtube.com / Ekin Endüstriyel](http://www.youtube.com/EkinEndustriyel)



[www.instagram.com / ekinendustriyel](http://www.instagram.com/ekinendustriyel)



[www.twitter.com / ekinendustriyel](http://www.twitter.com/ekinendustriyel)

You can take assistance about problems you have from MIT Plate Heat Exchanger Solution Center. Our solution center having qualified mechanical engineers will be happy to help you. These are some of the subjects that we can happily help you:

- Utility hot water installations
- Central and local heating systems
- Milk, yogurt, airan heating, cooling and pasteurization
- Industrial heating and cooling systems
- Oil cooling installations
- Energy recycle systems
- Pool heating systems




+90 (216) **660 13 05**

In Plate Heat Exchanger systems, it is vital to setup the system correctly to get the desired capacity. That is why, when you setup your system you can take needed assistance from rst hand just using a phone (+90 216 660 13 05) for 7 days and 24 hours.


To make your system and heat exchangers work correct and full performance, we want to share the information we've had through the long years. It really is a big happiness for us.

We want to emphasize that again and again. Ekin Endüstriyel will continue being the best solution partner in every place where heat exchanger is used.







Liquid	Chemical Formula	Concentration %	Temp. degree C	Specific gravity kg/dm3	Viscosity cSt	Vapour pressure kPa	Bronze	Aluminium	Cast iron	Ductile iron	Hastelloy B	Hastelloy C	Stainless Steel SIS 2333	Stainless Steel SIS 2343	EP - Epoxy	CPVC	PP	PVDF	PTFE	FPM - Viton	EPDM - EPT	NBR - Nitrile	CR - Neoprene	Kaizez	Hytrek	Carbon	Silicon	Ceramic	
Abietic acid	C <sub>20</sub> H <sub>30</sub> O <sub>2</sub>	100	20	0.974				A				A		A				A	A										
Accumuiator acid (Battery acid)	H <sub>2</sub> SO <sub>4</sub>	40	20														A	A	A	A	A	c	C	A					
Acetaidehyde (Ethanal)	CH <sub>3</sub> CHO, C <sub>2</sub> H <sub>4</sub> o	100	20	0.783	0.4	101	A	A	C	C		A	A	A	A	D	A	D	A	c	A	D	D	C	C				
Acetaidehyde (Ethanal)	CH <sub>3</sub> CHO, C <sub>2</sub> H <sub>4</sub> o	100	60				A	A	C	C		A	A	A	A	D	B	D	A	D	B	D	D	C	C				
Acetaidehyde, aqueous	CH <sub>3</sub> CHO+H <sub>2</sub> O	40	20				A	A	C			A		A	A	D	A	D	A	B	A	D	D	A					
Acetaidehyde, aqueous	CH <sub>3</sub> CHO+H <sub>2</sub> O	40	60				A	A	C			A		A	A	D	A	D	A	C	A	D	D	D					
Acetaidehyde, aqueous	CH <sub>3</sub> CHO+H <sub>2</sub> O	40	80				A	A	C			A		A	A	D	B	D	A	D	B	D	D	D					
Acetamide	ch3coNH2	100	20	0.980			D	A	D					A	A	C	A	A	A	A	A	A	B	A					
Acetate solvent, crude		100	20				D		D					A	A		D			D		D	D						
Acetate solvent, pure		100	20				A		A					A	A		D			D		D	C						
Acetic acid	CH3COOH, CH3C02H	10	20				C	A	D	D	A	A		A	A	A	A	A	A	C	B	D	D	A	A				
Acetic acid	CH <sub>3</sub> COOH, CH <sub>3</sub> C0 <sub>2</sub> H	10	40				C	A	D	D	A	A		A	A	A	A	A	A	C	D	D	D	A	A				
Acetic acid	CH <sub>3</sub> COOH, CH <sub>3</sub> C0 <sub>2</sub> H	10	80				C	A	D	D	A	A		A	A	A	B	B	A	D	D	D	D	A	A				
Acetic acid	CH <sub>3</sub> COOH, CH <sub>3</sub> C0 <sub>2</sub> H	20	20				C	A	D	D	A	A		A	A	A	A	A	A	C	C	D	D	A	A				
Acetic acid	CH <sub>3</sub> COOH, CH <sub>3</sub> C0 <sub>2</sub> H	20	40		2		C	A	D	D	A	A		A	A	A	A	A	A	C	D	D	D	A	A				
Acetic acid	CH <sub>3</sub> COOH, CH <sub>3</sub> C0 <sub>2</sub> H	20	60				C	A	D	D	A	A		A	A	A	B	A	A	C	D	D	D	A	A				
Acetic acid	CH <sub>3</sub> COOH, CH <sub>3</sub> C0 <sub>2</sub> H	20	80				C	A	D	D	A	A		A	A	B	C	B	A	C	D	D	D	A	A				
Acetic acid	CH <sub>3</sub> COOH, CH <sub>3</sub> C0 <sub>2</sub> H	30	20				C	A	D	D	A	A		A	A	A	A	A	A	C		D	D	A	A				
Acetic acid	CH <sub>3</sub> COOH, CH <sub>3</sub> C0 <sub>2</sub> H	50	20	1.060			C	A	D	D	A	A		A	A	A	A	A	A	C	D	D	D	D	A				
Acetic acid	CH <sub>3</sub> COOH, CH <sub>3</sub> C0 <sub>2</sub> H	50	40				C	A	D	D	A	A		A	A	B	B	A	A	C	D	D	D	D	A				
Acetic acid	CH <sub>3</sub> COOH, CH <sub>3</sub> C0 <sub>2</sub> H	50	60				C	A	D	D	A	A		A	A	C	C	A	A	C	D	D	D	D	A				
Acetic acid	CH <sub>3</sub> COOH, CH <sub>3</sub> C0 <sub>2</sub> H	50	80				C	A	D	D	A	A		A	A	D		B	A	C	D	D	D	D	A				
Acetic acid	CH <sub>3</sub> COOH, CH <sub>3</sub> C0 <sub>2</sub> H	80	20				C	A	D	D	A	A		A	A	B	B	A	A	C	D	D	D	D	A				
Acetic acid	CH <sub>3</sub> COOH, CH <sub>3</sub> C0 <sub>2</sub> H	80	40				C	A	D	D	A	A		A	A	C	C	B	A		D	D	D	D	A				
Acetic acid	CH <sub>3</sub> COOH, CH <sub>3</sub> C0 <sub>2</sub> H	80	60				C	A	D	D	A	A		A	A	D	D	C	A		D	D	D	D	A				
Acetic acid	CH <sub>3</sub> COOH, CH <sub>3</sub> C0 <sub>2</sub> H	80	80				C	A	D	D	A	A		A	A	D	D	D	A		D	D	D	D	A				
Acetic acid methyl ester (Metyl acetate)	CH <sub>3</sub> C0 <sub>2</sub> CH <sub>3</sub>	100	20	0.930													A										A		
Acetic acid, glacial	CH <sub>3</sub> COOH, CH <sub>3</sub> C0 <sub>2</sub> H	100	20	1.050	1.2	1.5	C	B	D	D	A	A		A	B	D	A	A	A	B	D	D	D	D					
Acetic acid, glacial	CH <sub>3</sub> COOH, CH <sub>3</sub> C0 <sub>2</sub> H	100	40				C	B	D	D	A	A		A	B	D	B	B	A		D	D	D	D					
Acetic acid, glacial	CH <sub>3</sub> COOH, CH <sub>3</sub> C0 <sub>2</sub> H	100	60				C	B	D	D	A	A		A	B	D	C	B	A		D	D	D	D					
Acetic acid, glacial	CH <sub>3</sub> COOH, CH <sub>3</sub> C0 <sub>2</sub> H	100	80				C	B	D	D	A	A		A	B	D	D	B	A		D	D	D	D					
Acetic anhydride, pure	(CH <sub>3</sub> C0) <sub>2</sub> O	100	20	1.080		0.5	C	B	C		B	A		A	A	D	B	B	A	D	C	D	D	A					
Acetic anhydride, pure	(CH <sub>3</sub> C0) <sub>2</sub> O	100	40				C	B	C		B	A		A	A	D	C	C	A	D	D	D	D	A					
Acetic anhydride, pure	(CH <sub>3</sub> C0) <sub>2</sub> O	100	60				C	B	C		B	A		A	A	D	D	D	A	D	D	D	D						
Acetic ether (Ethyl acetate)	CH3cooc2H5, CH3cooCH2CH3	100	20	0.902	0.5	9.7	A	A	A	C		B		A	A	D	B	A	A	D	B	D	D	A	B	A		A	
Acetoacetic ester (Ethyl acetoacetate)	CH3cocH2cooc2H5	100	20	1.030								A		A			D									A		A	
Acetone (Dimethyl ketone)	CH3cocH3, C <sub>3</sub> H <sub>6</sub> o	100	20	0.790	1.3	25	A	B	A	A	A	A		A	B	D	A	D	A	D	B	D	D	A	B	A		A	
Acetone (Dimethyl ketone)	CH <sub>3</sub> COCH <sub>3</sub> , C <sub>6</sub> H <sub>6</sub> o	100	60				A	B	A	A	A	A		A	B	D	C	D	A	D		D	D	A					



Liquid	Chemical Formula	Concentration %	Temp, degree C	Specific gravity kg/dm3	Viscosity cSt	Vapour pressure kPa	Bronze	Aluminium	Cast iron	Ductile iron	Hastelloy B	Hastelloy C	Stainless Steel SIS 2333	Stainless Steel SIS 2343	EP - Epoxy	CPVC	PP	PVDF	PTFE	FPM - Viton	EPDM - EPT	NBR - Nitrile	CR - Neoprene	Kairez	Hytel	Carbon	Silicon	Ceramic	
Acetone cyanhydrine	(CH <sub>3</sub> ) <sub>2</sub> C(OH)CN	100	20	0.930																									
Acetone, aqueous	CH <sub>3</sub> COCH <sub>3</sub> +H <sub>2</sub> O	10	20							A														A					
Acetone, aqueous	CH <sub>3</sub> COCH <sub>3</sub> +H <sub>2</sub> O	100	20				A	B	A	A		A		A	B	A	A	D	A	A	A	B	D	A					
Acetone, aqueous	CH <sub>3</sub> COCH <sub>3</sub> +H <sub>2</sub> O	100	40				A	B	A	A		A		A	B	A	A	D	A	A	A	C	D	A					
Acetone, aqueous	CH <sub>3</sub> COCH <sub>3</sub> +H <sub>2</sub> O	100	60				A	B	A			A		A	B	B	A	D	A	A	A		D	A					
Acetone, aqueous	CH <sub>3</sub> COCH <sub>3</sub> +H <sub>2</sub> O	100	80				A	B	A	A		A		A	B		A	D	A	A	B		D	A					
Acetonitrile (Methyl cyanide)	CH <sub>3</sub> CN	100	20	0.787		9.7		A						A			B	A	A	C	A	C	C	A		A			
Acetonitrile (Methyl cyanide)	CH <sub>3</sub> CN	100	60					A						A				C	A										
Acetonitrile (Methyl cyanide)	CH <sub>3</sub> CN	100	80					A						A				D											
Acetophenone	C <sub>6</sub> H <sub>5</sub> COCH <sub>3</sub> , C <sub>8</sub> H <sub>8</sub> O	100	20	1.030				A				A		A			A	A	A	C	A	D	D			A		A	
Acetophenone	C <sub>6</sub> H <sub>5</sub> COCH <sub>3</sub> , C <sub>8</sub> H <sub>8</sub> O	100	40														B	C	A	D	A	D	D						
Acetophenone	C <sub>6</sub> H <sub>5</sub> COCH <sub>3</sub> , C <sub>8</sub> H <sub>8</sub> O	100	60														C	D	A	D	A	D	D						
Acetophenone	C <sub>6</sub> H <sub>5</sub> COCH <sub>3</sub> , C <sub>8</sub> H <sub>8</sub> O	100	80														D	D	A	D	B	D	D						
Acetyl acetone	C <sub>5</sub> H <sub>8</sub> O <sub>2</sub>	100	20												D		D	D											
Acetyl bromide	CH <sub>3</sub> COBr, C <sub>2</sub> H <sub>3</sub> OBr	100	20	1.520		13.3												A	A										
Acetyl bromide	CH <sub>3</sub> COBr, C <sub>2</sub> H <sub>3</sub> OBr	100	80															B	A										
Acetyl chloride (Acetic chloride)	CH <sub>3</sub> COCl	100	20	1.105		27.9		D		D		A		B			A	A	A	D	D	D	D		D	A		A	
Acetyl chloride (Acetic chloride)	CH <sub>3</sub> COCl	100	40					D		D		A		B			A	B	A	D	D	D	D		D				
Acetyl chloride (Acetic chloride)	CH <sub>3</sub> COCl	100	60					D		D		A		B			B	C	A	D	D	D	D		D				
Acetyl chloride (Acetic chloride)	CH <sub>3</sub> COCl	100	80					D		D		A		B			C	D	A	D	D	D	D		D				
Acetyl hydroperoxide	CH <sub>3</sub> COOOH, C <sub>2</sub> H <sub>3</sub> O <sub>2</sub> H	100	20	1.150																									
Acetyl ketene	CH <sub>2</sub> =CCH <sub>2</sub> C(O)O	100	20	1.080																									
Acetyl peroxide	(CH <sub>3</sub> CO) <sub>2</sub> O <sub>2</sub>	100	20	1.180																									
Acetylene (Ethyne)	C <sub>2</sub> H <sub>2</sub>	100	20			4200	D	A	A	A				A	A	D	A	A	A	A	C	A	D	A	A				
Acetylene (Ethyne)	C <sub>2</sub> H <sub>2</sub>	100	60				D	A	A	A				A	A	D		A	A	A	D	B	D	A	A				
Acetylene dichloride	CHCl=CHCl	100	20	1.270		22																							
Acetylene tetrabromide	CHBr <sub>2</sub> CHBr <sub>2</sub> , (CHBr <sub>2</sub> ) <sub>2</sub>	100	20	2.970		0	D		D					A	D					A									
Acetylsalicylic acid	CH <sub>3</sub> CO <sub>2</sub> C <sub>6</sub> H <sub>4</sub> CO <sub>2</sub> H	100	20	1.200			D	A	D			A		A	A		A	A	A	D		D	D			A		A	
Acrylic acid (Propene acid)	CH <sub>2</sub> =CHCOOH CH <sub>2</sub> =CHCOOH	100	20	1.050		0.37																							
Acrylic acid ethyl ester	CH <sub>2</sub> =CHCOOC <sub>2</sub> H <sub>5</sub>	100	20	0.920		3.9													A	A									
Acrylic acid ethyl ester	CH <sub>2</sub> =CHCOOC <sub>2</sub> H <sub>5</sub>	100	40																B	A									
Acrylic acid ethyl ester	CH <sub>2</sub> =CHCOOC <sub>2</sub> H <sub>5</sub>	100	60																C	A									
Acrylic acid ethyl ester	CH <sub>2</sub> =CHCOOC <sub>2</sub> H <sub>5</sub>	100	80																D	B									
Acrylic aldehyde	CH <sub>2</sub> =CHCHO	100	20	0.840		29																							
Acrylic amide	CH <sub>2</sub> =CHCONH <sub>2</sub>	100	20	1.120																									
Acrylonitrile	CH <sub>2</sub> CHCN, CH <sub>2</sub> =CHCN	100	20	0.806		11	C	A	C			B		A	A		B	A	A	D	A	D	D	A		A		A	
Acrylonitrile	CH <sub>2</sub> CHCN, CH <sub>2</sub> =CHCN	100	40				C	A	C			B		A	A		C	B	A	D	A	D	D	A					
Acrylonitrile	CH <sub>2</sub> CHCN, CH <sub>2</sub> =CHCN	100	60				C	A	C			B		A	A		C	A	D	B	D	D							




Liquid	Chemical Formula	Concentration %	Temp, degree C	Specific gravity kg/dm3	Viscosity cSt	Vapour pressure kPa	Bronze	Aluminium	Cast iron	Ductile iron	Hastelloy B	Hastelloy C	Stainless Steel SIS 2333	Stainless Steel SIS 2343	EP - Epoxy	CPVC	PP	PVDF	PTFE	FPM - Viton	EPDM - EPT	NBR - Nitrile	CR - Neoprene	Kairez	Hytrek	Carbon	Silicon	Ceramic
Adipic acid	(CH <sub>2</sub> ) <sub>4</sub> (COOH) <sub>2</sub> , (C <sub>2</sub> H <sub>4</sub> COOH) <sub>2</sub>	100	20	1.360				B				A	B		A	A	A	A	A	A	A	A				A		
Adipic acid, aqueous, saturated	(CH <sub>2</sub> ) <sub>4</sub> (COOH) <sub>2</sub> , (C <sub>2</sub> H <sub>4</sub> COOH) <sub>2</sub>	100	20	1.360				B				A	B		A	A	A	A	A	A	A	A				A		
Adipic acid, aqueous, saturated	(CH <sub>2</sub> ) <sub>4</sub> (COOH) <sub>2</sub> , (C <sub>2</sub> H <sub>4</sub> COOH) <sub>2</sub>	100	80					B				A	B		B	B	A	A	A	B								
Adiponitrile	CN(CH <sub>2</sub> ) <sub>4</sub> CN	100	20	0.960																								
Adrament solution		100	20													A												
Alkane	C <sub>12</sub> H <sub>25</sub> -CbH <sub>5</sub>	100	20	0.870																								
Alkane sulfonic acid	C <sub>n</sub> H <sub>2n</sub> S <sub>03</sub> H	100	20					D				A	A			A		A							A			
Alkazene		100	20																	B			D					
Alkyl aryl sulphonate	C <sub>n</sub> H <sub>2n+1</sub> , C <sub>6</sub> H <sub>4</sub> S <sub>03</sub> Na	100	20					A				A	A													A	A	
Aliyi alcohol (Propenyl alcohol)	cH <sub>2</sub> cHcH <sub>2</sub> oH, H <sub>2</sub> c=cHcH <sub>2</sub> oH	96	20									A	A			A	A	A	C	C	A	C	A					
Aliyi alcohol (Propenyl alcohol)	cH <sub>2</sub> cHcH <sub>2</sub> oH, H <sub>2</sub> c=cHcH <sub>2</sub> oH	100	20	0.852	1.6	2.4						A	A		D	A	A	A	A		A				A	A		
Aliyi alcohol (Propenyl alcohol)	cH <sub>2</sub> cHcH <sub>2</sub> oH, H <sub>2</sub> c=cHcH <sub>2</sub> oH	100	60									A	A		D	A	A	A	A		B							
Aliyi alcohol (Propenyl alcohol)	cH <sub>2</sub> cHcH <sub>2</sub> oH, H <sub>2</sub> c=cHcH <sub>2</sub> oH	100	80									A	A		D		A	A	B									
Aliyi amine	cH <sub>2</sub> =cHcH <sub>2</sub> cl	100	20	0.760																								
Aliyi chloride	cH <sub>2</sub> =cHcH <sub>2</sub> cl	100	20	0.940	1	40		A				A				D	A	A	B	D	B				A	A		
Aliyi chloride	cH <sub>2</sub> =cHcH <sub>2</sub> cl	100	40					A				A				D	C	A	B	D	C							
Aliyi chloride	cH <sub>2</sub> =cHcH <sub>2</sub> cl	100	60					A				A				D	D	A	C	D	D							
Aliyi chloroformate	CH <sub>2</sub> :CHCH <sub>2</sub> OCCl	100	20	1.140																								
Alum (Potassium aluminium sulphate)	KAl(SO <sub>4</sub> ) <sub>2</sub>	100	20							D						A	A	A	A	A	A	A						
Alum (Potassium aluminium sulphate)	KAl(SO <sub>4</sub> ) <sub>2</sub>	100	80							D						A	A	A	A	A	B	B						
Aluminium acetate, saturated	Al(CH <sub>3</sub> COO) <sub>3</sub>	100	20					A		D				B		A	A	A	A	A	A	A			A	A		
Aluminium acetate, saturated	Al(CH <sub>3</sub> COO) <sub>3</sub>	100	40					A		D				B		B	A	A	A	A	A	A	B					
Aluminium bromide, saturated	(AlBr <sub>3</sub> ), AlBr <sub>3</sub>	100	20	3.210		0.1												A	A	A	A							
Aluminium chlorate	Al(ClO <sub>3</sub> ) <sub>3</sub> +6H <sub>2</sub> O	100	20									A	A			A	A	A							A	A		
Aluminium chloride, powder	AlCl <sub>3</sub>	100	20				D	D	D	D		A	D	A	A	A	A	A	A	A	A	A		C				
Aluminium chloride, saturated	AlCl <sub>3</sub>	5	20	1.030		2.2	D	D	D	D		A	D	A	A	A	A	A	A	A	A	A		C				
Aluminium chloride, saturated	AlCl <sub>3</sub>	10	20	1.090		2.2	D	D	D	D		A	D	A	A	A	A	A	A	A	A	A		C	A	A		
Aluminium chloride, saturated	AlCl <sub>3</sub>	20	20				D	D	D	D	A	A	C	A	A	A	A	A	A	A	A	A		C				
Aluminium chloride, saturated	AlCl <sub>3</sub>	100	20	2.440			D	D	D	D		A	D	A	A	A	A	A	A	A	A	A		C	A	A		
Aluminium chloride, saturated	AlCl <sub>3</sub>	100	60				D	D	D	D		A	D	A	B	A	B	A	A	A		A		C				
Aluminium chloride, saturated	AlCl <sub>3</sub>	100	80				D	D	D	D		A	D	A	B	A	C	A	A	A		A		C				
Aluminium etch		100	20				D		D				D	D						A		A						
Aluminium ethylate	Al(C <sub>2</sub> H <sub>5</sub> ) <sub>3</sub>	100	20																									
Aluminium fluoride, saturated	AlF <sub>3</sub> , Al <sub>2</sub> F <sub>3</sub>	100	20					A		D		B	C	A	A	A	A	A	A	A	A	A			A			
Aluminium hydroxide, saturated	Al(OH) <sub>3</sub>	100	20				A	B	A	D		A	A	A	A	A	A	A	A	A	A	A			A	A		
Aluminium hydroxide, saturated	Al(OH) <sub>3</sub>	100	80				A	B	A	D		A	A	A	A	A	A	A	A	B	B	A						
Aluminium nitrate, saturated	Al(NO <sub>3</sub> ) <sub>3</sub> +9H <sub>2</sub> O	10	20	1.050		2.2		D		D		A	A		A	A	A	A	A	A	A	A		C				
Aluminium nitrate, saturated	Al(NO <sub>3</sub> ) <sub>3</sub> +9H <sub>2</sub> O	100	20					D		D		A	A		A	A	A	A	A	A	A	A		C	A	A		




Liquid	Chemical Formula	Concentration %	Temp, degree C	Specific gravity kg/dm3	Viscosity cSt	Vapour pressure kPa	Bronze	Aluminium	Cast iron	Ductile iron	Hastelloy B	Hastelloy C	Stainless Steel SIS 2333	Stainless Steel SIS 2343	EP - Epoxy	CPVC	PP	PVDF	PTFE	FPM - Viton	EPDM - EPT	NBR - Nitrile	CR - Neoprene	Kairez	Hytrek	Carbon	Silicon	Ceramic	
Aluminium nitrate, saturated	Al(NO3)3+9H2O	100	80					D		D		A		A		A	A	A	A	A	A	B	A		C				
Aluminium oxide	AlO3	100	20				D		D					A	A					A		A	A						
Aluminium phosphate	AlPO4	100	20											A				A		A	A	A							
Aluminium pulverized	Al	100	20	2.710		0																							
Aluminium silicofluoride	Al2(SiF6)3	100	20									A		A			A	A											A
Aluminium sulphate, saturated	Al2(SO4)3	10	20	1.110		2.2	C	B	D	D	B	A		A	A	A	A	A	A	A	A	A	A		C	A		A	
Aluminium sulphate, saturated	Al2(SO4)3	100	20	1.610			C	B	D	D	B	A		A	A	A	A	A	A	A	A	A	A		C	A		A	
Amber acid (Succinic acid), saturated	C4H6O4, C2H4(COOH)2	100	20														A	A			A	A	A						
Amines	r-NH2	100	20				D		D					A	A						D	B	D	D		A			
Aminopyridine	c5H4n-NH2	100	20					A				A		A															A
Aminosalicylic acid	H2NC6H3(OH)CO2H	100	20					A				A		A			A		A							A			A
Ammonia alum	(NH4)Al(SO4)2+12H2O	10	25	1.050													A	A	A	A	A	A							
Ammonia alum	(NH4)Al(SO4)2+12H2O	100	20														A	A	A	A	A	A							
Ammonia alum	(NH4)Al(SO4)2+12H2O	100	80														A	A	A	A	A	B							
Ammonia gas	Nh3	100	20	0.770	0.3	883					B					A	A	A	A	D	A	A	B	A	D				
Ammonia gas	Nh3	100	60								B					B	B	A	A	D	A	B	B		D				
Ammonia gas	Nh3	100	80								B						B	A	A	D	B		B		D				
Ammonia liquor	NH3+H2o, Nh4oH	100	20	0.800		15.3											A	A	A	C	A	A							
Ammonia liquor	NH3+H2o, Nh4oH	100	40														B	A	A		B	B							
Ammonia nitrate	NH4No3	100	20	1.720			D		A					A	A							A	C						
Ammonia water	NH3+H2o, Nh4oH	10	20	0.900	1	48	D	A	A					A	A	A	A	A	A	B	A	A	A	A		A			
Ammonia vvater	NH3+H2o, Nh4oH	10	25	0.960		9.3	D	A	A					A	A	A	A	A	A	B	A	A	A	A		A			
Ammonia vvater	NH3+H2o, Nh4oH	10	40				D	A	A					A	A	A	A	A	A	C	A	B	A	A				A	
Ammonia vvater	NH3+H2o, Nh4oH	10	60				D	A	A					A	A	B	B	A	A	D	A	B	A				A		
Ammonia vvater	NH3+H2o, Nh4oH	10	80				D	A	A					A	A	B	B	A	A	D	A		A				A		
Ammonia water	NH3+H2o, Nh4oH	25	20	0.910		34.5	D	A	A					A	A	A	A	A	A	D		A	A	A		A			
Ammonia vvater	NH3+H2o, Nh4oH	28	20				D	A	A					A	A	A	A	A	A	D		A	A		A		A		
Ammonia vvater	NH3+H2o, Nh4oH	35	20	0.900	1	48	D	A	A					A	A	A	A	A	A	D		A	A		A		A		
Ammonia, anhydrous	NH3	100	20				D	A	A	B	B	A		A	A		A	A	C	A	A	A							
Ammonia, anhydrous	NH3	100	40				D	A	A	B	B	A		A	A		B	A	A		B	B	A						
Ammonium acetate, saturated	NH4oocC3, H3ccoNH4	100	20					A				A		A		A	A	A	A	A	A	A				A			A
Ammonium acetate, saturated	NH4oocC3, H3ccoNH4	100	80					A				A		A		B	B	A	A	B	B	B							
Ammonium bicarbonate	NH4Hco3	100	20				D	A	C	B				A	A		A	A	A		A					A			A
Ammonium bifluoride, saturated	NH4HF2, (NH4)FHF	20	20				D		D			A		A	A	A	A	A	A	A	A	A				A			
Ammonium bifluoride, saturated	NH4HF2, (NH4)FHF	100	20	1.500			D		D			B		A	A	A	A	A	A	A	A	A							
Ammonium bifluoride, saturated	NH4HF21 (NH4)FHF	100	80				D		D			B		A	A	A	A	A	A	B	B	B	A						
Ammonium bisulfite	Nh4Hso3	100	20									A		A			A		A							A			A

Liquid	Chemical Formula	Concentration %	Temp, degree C	Specific gravity kg/dm3	Viscosity cSt	Vapour pressure kPa	Bronze	Aluminium	Cast iron	Ductile iron	Hastelloy B	Hastelloy C	Stainless Steel SIS 2333	Stainless Steel SIS 2343	EP - Epoxy	CPVC	PP	PVDF	PTFE	FPM - Viton	EPDM - EPT	NBR - Nitrile	CR - Neoprene	Kairez	Hytel	Carbon	Silicon	Ceramic		
Ammonium bromide	NH4Br	5	25	1.030				D		D		A		C			A	A										A		
Ammonium bromide	NH4Br	40	20	1.270				D				A					A	A										A		
Ammonium carbonate, saturated	(NH4)2CO3+H2O	10	20	1.030		2.2	D	A	A	V		A		A	A	A	A	A	A	A	A	A	A							
Ammonium carbonate, saturated	(NH4)2CO3+H2O	25	20	1.100			D	A	A	B		A		A	A	A	A	A	A	A	A	A	A				A		A	
Ammonium carbonate, saturated	(NH4)2CO3+H2O	50	20				D	B	A	B				A																
Ammonium carbonate, saturated	(NH4)2CO3+H2O	100	20				D	B	A	B	B	B		B	A	A	A	A	A	A	A	A	A							
Ammonium caseinite		100	20											A	A								A							
Ammonium chloride, saturated	Nh4cl	10	20																											
Ammonium chloride, saturated	Nh4cl	25	20	1.070		1.8					B	A		B	A	A	A	A	A	A	A	A	A							
Ammonium chloride, saturated	Nh4cl	100	20	1.070			D	D	D	D	B	A		B	A	A	A	A	A	A	A	A	A				A			
Ammonium chloride, saturated	Nh4cl	100	80				D	D	D	D	B	A		B	A	B	B	A	A	A	A	A	B	A						
Ammonium fluoride (Fluorammon)	Nh4cl	6	20	1.030		2.3																								
Ammonium fluoride (Fluorammon)	Nh4cl	14	20	1.060				A				A		D			A	A	A	A								A		
Ammonium fluoride (Fluorammon)	Nh4cl	20	20	1.060										A			A	A	A	A	A	A						A		
Ammonium fluoride (Fluorammon)	Nh4cl	20	80											A			B	A	A											
Ammonium fluoride, povvder	Nh4cl	100	20	1.315																										
Ammonium fluoride, solution	Nh4cl	100	20	1.015																										
Ammonium fluorsilicate	(NH4)2SiF6	100	20					A				A		A			A	A											A	
Ammonium formate	Hco2Nh4	100	20					A				A		A			A	A	A								A		A	
Ammonium hydrogen fluoride	NH4HF2, (NH4)FHF	50	20														A	A									A		A	
Ammonium hydrogen phosphat	(Nh4)2HPO4	100	20															A	A								A			
Ammonium hydrogen sulphide	(NH4)HS	100	20														A	A												
Ammonium hydroxide	NH3+H2o, Nh4Oh	100	20	0.800		15.3	A	B	A		A	A		A	A	A	A	A	A	B	A	B	A	A	C					
Ammonium hydroxide	NH3+H2o, Nh4Oh	100	40				A	B	A		A	A		A	A	A	A	A	A	B	A	D	A	A						
Ammonium hydroxide	NH3+H2o, Nh4Oh	100	60	1	1		A	B	A		A	A		A	A	A	A	A	A	C	A	D	A	A						
Ammonium iodide	NH4I	45	20	1.380													A	A									A			
Ammonium metaphosphate		100	20														A	A	A	A	A	A	A							
Ammonium metaphosphate		100	40														A	A	A	A	A	A	B							
Ammonium nitrate	Nh4No3	10	20	1.040		2.2	D	A	A			A		A	A	A	A	A	A	A	A	A	A							
Ammonium nitrate	Nh4No3	50	20	1.230			D	A	A			A		A	A	A	A	A	A	A	A	A	A				A		A	
Ammonium nitrate	Nh4No3	60	20	1.230		0.5	D	A	A			A		A	A	A	A	A	A	A	A	A	A							
Ammonium nitrate	Nh4No3	100	20	1.720			D	B	A		D	A		A	A	B	A	A	A	A	A	A	A							
Ammonium nitrite, saturated	Nh4No3	100	20														A	A					A	A						
Ammonium oxalate	(NH4)2C2O4, (COONH4)2+H2O	30	25	1.040			D	A	D			A		A	A		A						A	A						
Ammonium oxalate	(NH4)2C2O4, (COONH4)2+H2O	100	20				D	A	D			A		A	A		A						A	A			A			
Ammonium perchlorate	Nh4clo4	10	25	1.040																										
Ammonium perchlorate	Nh4clo4	14	20	1.070				A				A																A		




Liquid	Chemical Formula	Concentration %	Temp, degree C	Specific gravity kg/dm3	Viscosity cSt	Vapour pressure kPa	Bronze	Aluminium	Cast iron	Ductile iron	Hastelloy B	Hastelloy C	Stainless Steel SIS 2333	Stainless Steel SIS 2343	EP - Epoxy	CPVC	PP	PVDF	PTFE	FPM - Viton	EPDM - EPT	NBR - Nitrile	CR - Neoprene	Kairez	Hytel	Carbon	Silicon	Ceramic		
Ammonium perchlorate	Nh4clo4	100	20	1.950																										
Ammonium persulphate	(Nh4)2S2O8	10	25	1.060			D	D	D						A	A	A	A	A	A	A	A								
Ammonium persulphate	(Nh4)2S2O8	40	20				D	D	D			A			A	A	A	A	A	A	A	A	A				A			
Ammonium persulphate	(Nh4)2S2O8	50	20				D	D	D			A			A	A	A	A	A	A	A	A	A				A			
Ammonium persulphate	(Nh4)2S2O8	100	20				D	D	D		D	A			A	A	A	A	A	A	A	A	D	D						
Ammonium phosphate, dibasic	(NH4)2HP04	50	20				C	D	C			A			C	A	A	A	A	A	A	A	A		c	A				
Ammonium phosphate, dibasic	(NH4)2HP04	100	20				C	D	C			A			C	A	A	A	A	A	A	A	A		c					
Ammonium phosphate, mono	NH4H2P04, (NH4)H2P04	100	20				D	D	D	D		A			C	A	A	A	A	A	A	A	A		c					
Ammonium phosphate, mono	NH4H2P04, (NH4)H2P04	100	60				D	D	D	D		A			C	A	A	A	A	A	A	A	B	A		c				
Ammonium phosphate, tribasic	(NH4)3H2P04	100	20				C		A			A			A	A	A	A		A	A	A	C		c					
Ammonium stannic chloride	(NH4)2SnCl6	100	20												A			A	A											
Ammonium sulphate, saturated	(NH4)2S04	10	20	1.060			A	A	C	D		A			A	A	A	A	A	A	A	A	A							
Ammonium sulphate, saturated	(NH4)2S04	50	20	1.280		0.7	A	A	C	D		A			A	A	A	A	A	A	A	A	A			A		A		
Ammonium sulphate, saturated	(NH4)2S04	100	20	1.300			A	D	C	D		B			B	A	A	A	A	A	A	A	A							
Ammonium sulphide, saturated	(NH4)2S04	100	20					A		D		A			A	A	A	A	A			A				A		A		
Ammonium sulphite, diluted	(NH4)2 SO3	100	20					A		C		A			A			A	A			A			c	A		A		
Ammonium thiosulphate	(NH4)2S2O3	100	20				D		D						A	A						A	A							
Amyl acetate, pure	CHaCOOC5HN, C7H14O2	100	20	0.880	2.3	0.7	A	B	C	C		B			A	A	D	D	A	A	D	B	D	D	A		A		A	
Amyl acetate, pure	CHgCOOC5HN, C7H14O2	100	40				A	B	C	C		B			A	A	D	D	B	A	D	C	D	D						
Amyl acetate, pure	CHaCOOC5HN, C7H14O2	100	60				A	B	C	C		B			A	A	D	D	C	B	D		D	D						
Amyl alcohol (Amyl hydrate), pure	C5H11OH	100	20	0.820	1.2		A	A	A	C	A	A			A	A	A	A	A	A	A	B	Â	A	C	A		A		
Amyl alcohol (Amyl hydrate), pure	C5H11OH	100	60				A	A	A	C	A	A			A	A	A	A	A	A	B	A	B	A	A	c				
Amyl alcohol (Amyl hydrate), pure	C5H11OH	100	80				A	A	A	C	A	A			A	A	B	B	A	A	B	A	A	A	C					
Amyl borate, pure		100	20																A	A	A	B	A	A						
Amyl chloride, pure	C5H11Cl, CH3(CH2)3CH2Cl	100	20	0.870			A	D		B		A			D	A	D	D	A	A	B	D	B	D			A		A	
Amyl chloride, pure	C5H11Cl, CH3(CH2)3CH2Cl	100	80				A	D		B		A			D	A	D	D	B	A		D	D							
Amyl chloronaphtalene		100	20																A	A			D							
Amyl mercaptan	CH3(CH2)4SH, C5H11SH	100	20	0.850		1.9																								
Amyl naphthalene		100	20																		A		D	D						
Aniline dyes	r-C6H4Nh2	100	20				C	B	C		A				A	A		A	A	A	B	C	C	C						
Aniline hydrochloride, pure	c6H5NH2Hcl	20	20	1.090								A			D			A	A	A	A		B	D						
Aniline hydrochloride, pure	c6H5NH2Hcl	100	20	1.080								A			D			A	A	A	A		B	D			A		A	
Aniline hydrochloride, pure	c6H5NH2Hcl	100	60									A			D			A	B	A	A		B	D						
Aniline hydrochloride, pure	c6H5NH2Hcl	100	80									A			D			D	A			B	D							
Aniline oil	C6H7N, c6H5NH2	100	20	1.020		0.3	A		A			B			A	A				A	B	D	D							
Aniline sulphate	(C6H5NH2)2.H2SO4	100	20									A					A	A	A								A			
Aniline, pure	C6H5NH2, C6H7N	100	20	1.020		0.3	C	B	A	C		B			A	A	C	B	A	A	B	B	D	D	A	D	A		A	






Liquid	Chemical Formula	Concentration %	Temp, degree C	Specific gravity kg/dm3	Viscosity cSt	Vapour pressure kPa	Bronze	Aluminium	Cast iron	Ductile iron	Hastelloy B	Hastelloy C	Stainless Steel SIS 2333	Stainless Steel SIS 2343	EP - Epoxy	CPVC	PP	PVDF	PTFE	FPM - Viton	EPDM - EPT	NBR - Nitrile	CR - Neoprene	Kairez	Hytrek	Carbon	Silicon	Ceramic	
Ascorbic acid	C <sub>6</sub> H <sub>8</sub> O <sub>6</sub>	100	20					A									A	A									A		
Askarel		100	20																		A	D	B	D					
Asphalt		100	20	1.100	500-2500		A	C	A	B				A	A	D	A	A	A	A	A	D	B	C		C			
Aviation petrol (Aviation spirit)		100	20	0.720		25																							
Barbeque sauce		100	20		2000		D		D					A	A								A	A					
Barium carbonate, saturated	BaCO <sub>3</sub>	100	20					A		B		A		A	A	A	A	A	A	A	A	A	A						
Barium carbonate, saturated	BaCO <sub>3</sub>	100	80					A		B		A		A	A	A	A	A	A	A	A	A	B						
Barium chlorate	Ba(ClO <sub>3</sub> ) <sub>2</sub> +H <sub>2</sub> O	20	20	1.180				A				A		A			A	A									A		A
Barium chlorate	Ba(ClO <sub>3</sub> ) <sub>2</sub>	100	20	3.180																									
Barium chloride	BaCl <sub>2</sub>	10	20	1.090		2.2	C	A	C	C	A	A			A	A	A	A	A	A	A	A	A						
Barium chloride	BaCl <sub>2</sub>	25	20	1.270		1.8	C	A	C	C	A	A		D	A	A	A	A	A	A	A	A	A			A		A	
Barium chloride, saturated	BaCl <sub>2</sub> +2H <sub>2</sub> O	100	20	3.860			C	A	C	C	A	A		B	A	A	A	A	A	A	A	A	A						
Barium chloride, saturated	BaCl <sub>2</sub> +2H <sub>2</sub> O	100	80				C	A	C	C	A	A		B	A	A	A	A	A	A	A	A	B	A					
Barium cyanide	Ba(CN) <sub>2</sub>	100	20				C			C				A	A						A	A	C	A					
Barium dioxide	BaO <sub>2</sub>	100	20	4.960																									
Barium hydrate	BaOH	100	20				A		A					A	A								A	A					
Barium hydroxide, saturated	Ba(OH) <sub>2</sub>	4	20	1.040			A	A	A	B	B	B		A	A	A	A	A	A	A	A	A	A		C	A		A	
Barium hydroxide, saturated	Ba(OH) <sub>2</sub>	100	20				A	D	A	B	B	B		A	A	A	A	A	A	A	A	A	A		C				
Barium hydroxide, saturated	Ba(OH) <sub>2</sub>	100	80				A	D	A	B	B	B		A	A	A	A	A	A	A	A	B	A		C				
Barium nitrate	Ba(NO <sub>3</sub> ) <sub>2</sub>	8	20	1.070			D	A	A			A		A	A	A	A	A	A	A	A	A	A			A			
Barium nitrate, saturated	Ba(NO <sub>3</sub> ) <sub>2</sub>	100	20	3.240			D		A					A	B	A	A	A	A	A	A	A	A						
Barium nitrate, saturated	Ba(NO <sub>3</sub> ) <sub>2</sub>	100	80				D		A					A	B	A	A	A	A	A	A	A	B	A					
Barium salts		100	20														A	A					A						
Barium sulphate, saturated	BaSO <sub>4</sub>	100	20					B		C				A	B	A	A	A	A	A	A	A	A		D				
Barium sulphate, saturated	BaSO <sub>4</sub>	100	80					B		C				A	B	A	A	A	A	A	A	A	B	A		D			
Barium sulphide, saturated	BaS	100	20				A	D		D				A	A	A	A	A	A	A	A	A	B	A					
Barium sulphite	BaS <sub>3</sub>	100	20				A								A	A					A		A						
Beef extract		100	20				D		D					A	A						A		A						
Beer		100	20	1.010	2		A	A	D			A		A	A	A	A	A	A	A	A	A	B	A		C	A		
Beet sugar liquor		100	20				C	A	A			A		A	A	A	A	A	A	A	A	A	A						
Benzaldehyde	C <sub>6</sub> H <sub>5</sub> CHO	0,1	20	1.050			A	A	A	C		A		A	A	D	A	A	A	C	C	D	D			A			
Benzaldehyde	C <sub>6</sub> H <sub>5</sub> CHO	10	20				A	A	A	C		A		A	A	D	A	A	A	C	C	D	D						
Benzaldehyde	C <sub>6</sub> H <sub>5</sub> CHO	10	60				A	A	A	C		A		A	A	D	B	B	A			D	D						
Benzaldehyde, above 10%	C <sub>6</sub> H <sub>5</sub> CHO	10	20				A	A	A	C		A		A	A	D	A	A	A	C	C	D	D						
Benzaldehyde, above 10%	C <sub>6</sub> H <sub>5</sub> CHO	10	40				A	A	A	C		A		A	A	D	B	B	A			D	D						
Benzaldehyde, saturated	C <sub>6</sub> H <sub>5</sub> CHO	100	20	1.050										A			A	A	A	A	A	C	D	A					
Benzene (Benzol), pure	C <sub>6</sub> H <sub>6</sub>	100	20	0.880	1	10.1	A	B	A	B	B	B		B	A	C	B	A	A	B	D	D	D	A	C	A		A	
Benzene (Benzol), pure	C <sub>6</sub> H <sub>6</sub>	100	40				A	B	A	B	B	B		B	A	D	C	B	A	B	D	D	D	A	C	A		A	






Liquid	Chemical Formula	Concentration %	Temp, degree C	Specific gravity kg/dm3	Viscosity cSt	Vapour pressure kPa	Bronze	Aluminium	Cast iron	Ductile iron	Hastelloy B	Hastelloy C	Stainless Steel SIS 2333	Stainless Steel SIS 2343	EP - Epoxy	CPVC	PP	PVDF	PTFE	FPM - Viton	EPDM - EPT	NBR - Nitrile	CR - Neoprene	Kairez	Hytrek	Carbon	Silicon	Ceramic	
Biphenyl	c6h5c6h5	100	25	1.990																									
Birch oil		100	20											A	A					A			A	D					
Biscuit dough		100	20				A							A						A			A	A					
Bisque mass		100	20				C							A	A	A	A			A			A	A					
Black liquor, saturated		100	20					C		C				B		A	A	A	A	A	A	A	A	B					
Black liquor, saturated		100	80					C		C				B		B	B	A	A	A	A	A	B	B					
Blast furnace gas		100	20																A	A			D	D					
Bleach liquor (Bleaching agent)	CaOCl2	5	20											A	A	A	A	A	A	A	A	A	C	C					
Bleach liquor (Bleaching agent)	CaOCl2	12	20											A	A	A	A	A	A	A	A	B	C	C					
Bleaching agent	CaOCl2	5	20											A	A	A	A	A	A	A	A	A	C	C					
Bleaching agent	CaOCl2	12	20											A	A	A	A	A	A	A	A	B	C	C					
Blood		100	20	1	5			B		D				A	A								A	A					
Bone oil		100	20	0.92	50		A		A					A	A					A			A	D					
Bone oil (Dippel's oil)		100	20				A		A					A	A								A	A					
Borax (Sodium tetraborate)	Na2B4O7+10H2O	3,5	20	1.030		2.2	A	C	A	C	A	A		A	A	A	A	A	A	A	A	A	A	C		A			
Borax (Sodium tetraborate)	Na2B4O7+10H2O	100	20	2.370			A	C	A	C	A	A		A	A	A	A	A	A	A	A	A	A	C		A			
Borax (Sodium tetraborate)	Na2B4O7+10H2O	100	40				A	C	A	C	A	A		A	A	A	A	A	A	A	A	A	B	C		A			
Borax (Sodium tetraborate)	Na2B4O7+10H2O	100	60				A	C	A	C	A	A		A	A	A	A	A	A	A	A	A	C	C		A			
Borax (Sodium tetraborate)	Na2B4O7+10H2O	100	80				A	C	A	C	A	A		A	A	A	A	A	A	A	A		D	C		A			
Bordeaux mixture		100	20					D						A					A	A	A		A						
Boric acid, saturated	H3B03, B(OH)3	10	20	1.010							A	A			A	A	A	A	A	A	A	A	A	A	A				
Boric acid, saturated	H3B03, B(OH)3	50	20								A	A			A	A	A	A	A	A	A	A	A	A	A				
Boric acid, saturated	H3B03, B(OH)3	100	20	1.435			B	B	D	D	A	A		B	A	A	A	A	A	A	A	A	A	A	A	A	A		A
Boric acid, saturated	H3B03, B(OH)3	100	80				B	B	D	D	A	A		B	A	B	A	A	A	A	B	B	A	A	A				
Borofluoric acid	HF4	100	20	1.220				D				B		C	A	A	A	A	A	A	A	A	A			A			
Borofluoric acid	HF4	100	80					D				B		C	A	A	B	A	A	A	B	A	A						
Boron trichloride	BCl3	100	20	1.430				D				A					A	A	A					A		A		A	
Boron triethyl hydrate	(C2H5)3B	100	20									A			A					A									
Boron trifluoride	(C2H5)3B	100	20															A	A					A					
Brake fluid		100	20				A		A					A	A								D	A					
Brandy		100	20															A	A										
Brass, plating solution		100	20								A	A		A	A	A	A	A	A	A	A	A	A						
Brass, plating solution		100	80								A	A		A	A	B	A	A	A				A	A					
Brawn		100	20											A										A					
Brewery dregs (Brevvery slop)		100	20				A		A					A	A					A			A	A					
Brine		100	20				A		D					A	A	A	A	A	A	A	A	A	A						
Brine		100	60				A		D					A	A	A	A	A	A	A	A	A	B	A					
Brine		100	80				A		D					A	A	A	A	A	A	A	A	B	A						


Liquid	Chemical Formula	Concentration %	Temp, degree C	Specific gravity kg/dm3	Viscosity cSt	Vapour pressure kPa	Bronze	Aluminium	Cast iron	Ductile iron	Hastelloy B	Hastelloy C	Stainless Steel SIS 2333	Stainless Steel SIS 2343	EP - Epoxy	CPVC	PP	PVDF	PTFE	FPM - Viton	EPDM - EPT	NBR - Nitrile	CR - Neoprene	Kairez	Hytrel	Carbon	Silicon	Ceramic
Bromic acid, pure	HBr	100	20				D	D	D			A		D	A	A	D	A	A	A	A	D	C					
Bromine trifluoride	BrF3	100	20					D						B						D	D	D	D					
Bromine water, saturated		100	20					D						B		C	C	A	A	A	D	D	B					
Bromine water, saturated		100	40					D						B			D	A	A	A	D	D	B					
Bromine water, saturated		100	80					D						B			D	B			D	D	B					
Bromine, anhydrous	Br2	100	20	3.102	0.32	23.3	D	D		D	A	A		D	C	D	A	A	A	A	D	D	D					
Bromine, aqueous	Br2	100	20				D	D	D		A	D		D			A	A	A	A	D	D	D				A	
Bromine, fluid	Br2	100	20	3.190				A		D	A	A		D			A	A	A	A	D	D	D		D	D		
Bromine, vapor	Br2	25	20														D	A	A	A	D	D	D					
Bromine, vapor	Br2	25	80														D	B			D	D	D					
Bromine, vapor	Br2	100	20																									
Bromobenzene	C6H5Br	100	20	1.500				A				A		A			A	A		A	D	D	D			A		
Bronze, plating solution		100	20											A	A	A	A			A		A	A					
Bunker oil		100	20					A						A				A		A	D	A						
Butadiene-1,3, gas	CH2=CHCH=CH2, (CH2)2(CH)2	100	20	0.620	0.3	150		A						A	A	A	A	A	A	A	D	B	B					
Butadiene-1,3, gas	CH2=CHCH=CH2, (CH2)2(CH)2	100	40					A						A	A	A	A	A	A	A	D	C	B					
Butanal (i)	(CH3)2CHCHO	100	20	0.790		15.3																						
Butane (n), gas	C4H10, CH3CH2CH2CH3	100	20	0.580	0.1	800	A	A	A	B	B			A	A	A	A	A	A	A	D	C	A	A	A			
Butane diol	HOCH2CH2CH2CH2OH	10	20					A				A		A			A		A	D		A						
Butter		100	20		100000		D		D					A	A			A	A	A	A	A	C		C			
Butter milk		100	20				D		D					A	A			A	A	A	A	A						
Butyl acetate (i), pure	CH3COOCH2CH(CH3)2	100	20	0.870		1.2	A	A	A	B	A	A		A	A	C	C	A	A	D	B	D	D		C	A		A
Butyl acetate (n), pure	CH3COOC4H9, C4H9CO2CH3	100	20	0.883		1.2	A	A	A	B	A	A		A	A	C	C	A	A	D	B	D	D	A	C	A		A
Butyl acetate (n), pure	CH3COOC4H9, C4H9CO2CH3	100	40				A	B	A	B	A	B		C	A		D	B	A	D	C	D	D	A	C			
Butyl acetate (n), pure	CH3COOC4H9, C4H9CO2CH3	100	60				A	B	A	B	A	B		C	A		D	D	A	D	D	D	D	A	C			
Butyl acetate (n), pure	CH3COOC4H9, C4H9CO2CH3	100	80				A	B	A	B	A	B		C	A		D	D	B	D	D	D	D		C			
Butyl acetate (Sec), pure	CH3COOCH(CH3)C2H5	100	20	0.870		2.5	A	A	A	B	A	A		A	A	C	C	A	A	D	B	D	D		C	A		A
Butyl acetvl ricinoleate		100	20																A	A	C		B					
Butyl acrylate, pure	CH2=CHCOOC4H9	100	20	0.900		0.48										D	D	A	A	D	A	D						
Butyl acrylate, pure	CH2=CHCOOC4H9	100	40													D	D	B	A	D	A	D						
Butyl acrylate, pure	CH2=CHCOOC4H9	100	60													D	D	C	A	D		D						
Butyl acrylate, pure	CH2=CHCOOC4H9	100	80													D	D	D		D		D						
Butyl acrylate, saturated	CH2=CHCOOC4H9	100	20																	D	A	D						
Butyl alcohol (Butanol), pure	C4H9OH	100	20	0.810	1.2	0.9	A	B	D	C	A	A		A	A	A	A	A	A	B	A	B	A		C	A		
Butyl alcohol (Butanol), pure	C4H9OH	100	60				A	B	D	C	A	A		A	A	A	A	A	A	C	A	B	A		C			
Butyl alcohol (Butanol), pure	C4H9NH	100	80				A	B	D	C	A	A		A	A	B	A	A	A		A	A			c			
Butyl amine, saturated	C4H9NH	100	20	0.750		9.3		A						A		D	D	B	A	A	D	A	D					
Butyl amine, saturated	C4H9NH	100	40					A						A		D	D	D	A		D	D						




Liquid	Chemical Formula	Concentration %	Temp, degree C	Specific gravity kg/dm3	Viscosity cSt	Vapour pressure kPa	Bronze	Aluminium	Cast iron	Ductile iron	Hastelloy B	Hastelloy C	Stainless Steel SIS 2333	Stainless Steel SIS 2343	EP - Epoxy	CPVC	PP	PVDF	PTFE	FPM - Viton	EPDM - EPT	NBR - Nitrile	CR - Neoprene	Kairez	Hytel	Carbon	Silicon	Ceramic		
Butyl benzoate		100	20					B						B					A	A	B		D							
Butyl bromid, pure	C6H9-Br	100	20															A	A											
Butyl carbitol	C4H9OCH2CH2OCH2CH2OH	100	20	0.960		0.6													A	A	A	A	B							
Butyl cellosolve, pure	C4H9OCH2CH2OH	100	20	0.900														A	A	D		D	B							
Butyl cellosolve, pure	C4H9OCH2CH2OH	100	60															B	A	D		D	B							
Butyl cellosolve, pure	C4H9OCH2CH2OH	100	80															C	A	D		D	B							
Butyl chloride	C4H10-nCln	100	20	0.890				A				A		D			A	A	A								A			
Butyl diol		100	20															A	A	A	A	A								
Butyl ether	CH3COOC4H9	100	20	0.880		1.2										D	D	A	A	D	D	B	D	A						
Butyl ether	ch3cooC4H9	100	60													D	D	C	A	D	D									
Butyl ether	ch3cooC4H9	100	80													D	D	D		D	D									
Butyl glycol	C4H9OCH2CH2OH, C6H14O2	100	20	0.900				A				A		A			A	A									A			
Butyl glycolate	ch2oHcooc4H9	100	20	1.010		0.13																								
Butyl hydroperoxide	(CH3)3COOH	100	20	0.860																										
Butyl lithium	C4H9Li	100	20																											
Butyl mercaptan, pure		100	20																A	A	A		D	D						
Butyl oleate		100	20																		A	C		D						
Butyl peracetate	CH3CO(02)C(CH3)3	100	20	0.920																										
Butyl perbenzoate	C6H6COOOC(CH3)3	100	20	1.030																										
Butyl phenol	HOC6H4C(CH3)3	100	20					A					A			A	A	A	A	D		D					A			
Butyl phthalate		100	20					A				A		A				A	A	A	B	B	D				A			
Butyl phthalate		100	40					A				A		A				A	B	A	B	D	D							
Butyl phthalate		100	60					A				A		A				A	C		D	D								
Butyl phthalate		100	80					A				A		A				D		D	D	D								
Butyl stearate, pure		100	20					B						B				A	A	A	C	B								
Butyl stearate, pure_		100	60					B						B				A	A	A		C								
Butylene	C4H8	100	20	0.620			D	A					A	A	A	D	A	A	A	A	D	A	C				A			
Butylene	C4H8	100	80				D	A					A	A	A	D	A	A	B	D	A	C								
Butylene glycol	HO-CH2-CH=CH-CH2-OH	100	20	1.010																										
Butyraldehyde (n)	C3H7CHO, CH3(CH2)2CHO	100	20	0.800		12	D		A				D	A						C	C	C	D							
Butyric acid, pure	C3H7COOH, C4H8O2	20	20	0.880			A	A			B	A	B	A	D	A	A	A	A	A	A	D	A	A	C	A				
Butyric acid, pure	C3H7COOH, C4H8O2	100	20	0.960			A	A	D	D	B	A	B	A	D	A	A	A	B	B	D	D			C	A		A		
Butyric acid, pure	C3H7COOH, C4H8O2	100	40				A		D	D	B	A	B	A	D	A	A	A	C		D	D			C					
Butyric acid, pure	C3H7COOH, C4H8O2	100	60				A		D	D	B	A	B	A	D	A	A	A	D		D	D			C					
Cadmium chloride	CdCl2	50	20	1.680				D				A		A				A	A	A							A			
Cadmium nitrate	Cd(NO3)2	50	20	1.640															A	A										
Cadmium sulphate	CdSO4	40	20	1.550				A				A		A				A	A	A							A		A	



Liquid	Chemical Formula	Concentration %	Temp, degree C	Specific gravity kg/dm3	Viscosity cSt	Vapour pressure kPa	Bronze	Aluminium	Cast iron	Ductile iron	Hastelloy B	Hastelloy C	Stainless Steel SIS 2333	Stainless Steel SIS 2343	EP - Epoxy	CPVC	PP	PVDF	PTFE	FPM - Viton	EPDM - EPT	NBR - Nitrile	CR - Neoprene	Kairez	Hytrek	Carbon	Silicon	Ceramic
Cadmium, plating solution		100	20								A				A	A	D	A	A	A	A	A						
Cadmium, plating solution		100	80								A				A	B	D	A	A			A	A					
Caffeine citrate		100	20															A	A									
Calcium	Ca	100	20																									
Calcium acetate, saturated	Ca(C <sub>2</sub> H <sub>3</sub> O <sub>2</sub> ) <sub>2</sub> +2H <sub>2</sub> O	100	20					C						B		A	A	A	A	A	A	A	B					
Calcium acetate, saturated	Ca(C <sub>2</sub> H <sub>3</sub> O <sub>2</sub> ) <sub>2</sub> +2H <sub>2</sub> O	100	80					C						B		B	B	A	A	A	A		B					
Calcium bisulphate	Ca(HSO <sub>4</sub> ) <sub>2</sub>	100	20				C		D					A	A								A					
Calcium bisulphide, saturated		100	20				C							B	A	A	A	A	A	A	D	A	A					
Calcium bisulphide, saturated		100	40				C							B	A	A	A	A	A	A	D	B	A					
Calcium bisulphide, saturated		100	80				C							B	A		A	A	A	B	D		A					
Calcium bisulphite, saturated	Ca(HSO <sub>3</sub> ) <sub>2</sub>	25	25	1.040				A		D		A		B		A	A	A	A	A	A	A	A					
Calcium bisulphite, saturated	Ca(HSO <sub>3</sub> ) <sub>2</sub>	100	20	1.400				A		D		A		B		A	A	A	A	A	B	A	A			A		A
Calcium bromide	CaBr <sub>2</sub>	50	20	1.640													A	A								A		
Calcium carbide	CaC <sub>2</sub>	100	20	2.220																								
Calcium carbonate, saturated	CaCO <sub>3</sub>	100	20								A	A		A	A	A	A	A	A	A	A	A	A					
Calcium carbonate, saturated	CaCO <sub>3</sub>	100	60								A	A		A	A	A	A	A	A	A	A	B	A					
Calcium chlorate, saturated	Ca(ClO <sub>3</sub> ) <sub>2</sub>	100	20											A		A	A	A	A	A	A	C				A		A
Calcium chloride	CaCl <sub>2</sub> +6H <sub>2</sub> O, CaCl <sub>2</sub>	40	20	1.400			A	D	C	C	B	A		B	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Calcium chloride, saturated	CaCl <sub>2</sub> +6H <sub>2</sub> O, CaCl <sub>2</sub>	100	20				A	D	C	C	B	A		B	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Calcium chloride, saturated	CaCl <sub>2</sub> +6H <sub>2</sub> O CaCl <sub>2</sub>	100	60				A	D	C	C	B	A		B	A	A	A	A	A	A	A	B	A	A	A	A	A	A
Calcium cyanide	Ca(CN) <sub>2</sub>	100	20																									
Calcium hydroxide	Ca(OH) <sub>2</sub>	0,15	20	1.000			D	D	A	C	A	A		A	A	A	A	A	A	A	A	A	A			A		A
Calcium hydroxide	Ca(OH) <sub>2</sub>	5	25	1.060			D	D	A	C	A	A		A	A	A	A	A	A	A	A	A	A					
Calcium hydroxide, saturated	Ca(OH) <sub>2</sub>	100	20				D	D	A	C	A	A		A	A	A	A	A	A	A	A	A	A					
Calcium hydroxide, saturated	Ca(OH) <sub>2</sub>	100	80				D	D	A	C	A	A		A	A	B	A	A	A	A	A	C	A					
Calcium hypochlorite, saturated	Ca(ClO) <sub>2</sub>	100	20	2.100			D	D	D			A		D	A	A	A	A	A	A	B	c	D		C	A		A
Calcium hypochlorite, saturated	Ca(ClO) <sub>2</sub>	100	60				D	D	D			A		D	A	B	B	A	A	A			D		C			
Calcium hypochlorite, saturated	Ca(ClO) <sub>2</sub>	100	80				D	D	D			A		D	A		C	A	A				D		C			
Calcium nitrate	Ca(NO <sub>3</sub> ) <sub>2</sub>	50	20	1.480				A				A		A	A	A	A	A	A	A	A	A	A			A		A
Calcium nitrate, saturated	Ca(NO <sub>3</sub> ) <sub>2</sub>	100	20					B						B		A	A	A	A	A	A	A	A					
Calcium oxide (Burnt lime)	CaO	100	20	3.370			A		A					A	A	A				A	A	A	A		C			
Calcium permanganate	Ca(MnO <sub>4</sub> ) <sub>2</sub>	100	20					A									A	A	A									
Calcium sulphate	CaSO <sub>4</sub>	50	20	1.490			A	A	A	C	B	B		A	A	A	A	A	A	A	A	A	D			A		A
Calcium sulphate, saturated	CaSO <sub>4</sub>	100	20				A		A	C	B	B		B	A	A	A	A	A	A	A	A	D					
Calcium sulphate, saturated	CaSO <sub>4</sub>	100	80				A		A	C	B	B		B	A	A	A	A	A	A	A	B	D					
Calcium sulphide, saturated	CaS	100	20	2.800				A						A			A	A	A	A	A	A	A			A		
Calcium sulphide, saturated	CaS	100	80					A						A			A	A	A	A	A	B	A					




Liquid	Chemical Formula	Concentration %	Temp, degree C	Specific gravity kg/dm3	Viscosity cSt	Vapour pressure kPa	Bronze	Aluminium	Cast iron	Ductile iron	Hastelloy B	Hastelloy C	Stainless Steel SIS 2333	Stainless Steel SIS 2343	EP - Epoxy	CPVC	PP	PVDF	PTFE	FPM - Viton	EPDM - EPT	NBR - Nitrile	CR - Neoprene	Kairez	Hytrek	Carbon	Silicon	Ceramic
Calcium sulphite	CaSO3	100	20					A						A			A	A	A								A	A
Calgon (Sodium hexametaphosphate)	(NaPO3)6	100	20				C		D					A	A					A		A	A					
Campher	C10H16O	100	20	0.990			A				A			A			A		A	D		A				A		
Cane sugar liquor	C12H22O11	100	20				A	A	A			B		A	A	A	A	A	A	A	A	A	A		C			
Cane sugar liquor	C12H22O11	100	80				A	A	A			B		A	A		A	A	A	A	A	B	A		C			
Capric acid-n	CH3(CH2)8CO2H	100	20					A				A		A			A	A	A							A		
Capronic acid	CH3(CH2)4CO2H	100	20	0.930			A					A		A			D	A	A							A		A
Capronic nitrile-n	CH3(CH2)4CN	100	20												A								D					
Capryl alcohol	CH3CHOH(CH2)5CH3	100	20	0.820		0.03		A				A		A					A							A		
Caprylic acid, pure	CH3(CH2)6CO2H	100	20	0.920				A				A					D	A	A							A		
Carbamate (Carbamido)		100	20																	A	C	C	B					
Carbamide (Urea)	(H2N)CO(NH2)	50	20	1.115																								
Carbamide (Urea)	(H2N)CO(NH2)	100	20	1.320			C	A	A			A		A	A	A	A	A	A	A	A	A	D			A		
Carbaryl	C10H7OCONHCH3	100	20																									
Carbide slurry		100	20														A	A										
Carbitol	C2H5OCH2CH2OCH2CH2OH	100	20	0.990										B					A	A	A	A	B					
Carbitol	C2H5OCH2CH2OCH2CH2OH	100	40											B					A	B		C	B					
Carbitol	C2H5OCH2CH2OCH2CH2OH	100	60											B					A	C			B					
Carbon dioxide, dry	co2	100	20				A	A	D		A			A	A	A	A	A	A	A	A	A	A					
Carbon dioxide, dry	co2	100	80				A	A	D		A			A	A	A	A	A	A	A	A	B	A					
Carbon dioxide, wet	co2	100	20				A	A	D		A			A	A	A	A	A	A	A	A	A	A					
Carbon dioxide, wet	co2	100	80				A	A	D		A			A	A	A	A	A	A	A	B	A	A					
Carbon disulphide, pure	cs2	100	20	1.260		39.9	D	A	A	B		A		A	A	C	D	A	A	A	D	C	D	A	C			
Carbon disulphide, pure	cs2	100	40				D	A	A	B		A		A	A	C	D		A	B	D	C	D	A	C			
Carbon disulphide, pure	cs2	100	60				D	A	A	B		A		A	A	D	D		A	C	D	D	D		C			
Carbon disulphide, pure	cs2	100	80				D	A	A	B		A		A	A	D	D		A	D	D	D	D		C			
Carbon monoxide, gas	co	100	20				C	A	D		A			A	A	A	A	A	A	A	A	A	A		A			
Carbon monoxide, gas	co	100	80				C	A	D		A			A	A	A	A	A	A	A	A	B	A		A			
Carbon tetrachloride, pure	cc14	100	20	1.590	0.6	12	B	B	C	D	B	A		A	A	C	D	A	A	B	D	D	D	C	D	A		
Carbon tetrachloride, pure	cc14	100	40				B	B	C	D	B	A		A	A	D	D	A	A		D	D	D	C	D			
Carbonated water		100	20				C							A	A	A	A			A		A	A					
Carbonic acid, saturated	H2CO3	100	20				A	D	D		A	A		A	A	A	A	A	A	A	A	A	A		C	A		A
Carbonic acid, saturated	H2CO3	100	80				A	D	D		A	A		A	A	B	B	A	A	A	B	A			C			
Carnallite lye	MgCl2+KCl	100	20					D				A		A			A		A							A		A
Casein		100	20																A	A	A	A						
Castor oil, pure		100	20	0.960	600		A	A	A					A	A	A	A	A	A	A	A	A	A			A		
Caustic potash (Potassium hydroxide)	KOH	20	20	1.190			D	D	C			B		B	A	A	A	A	A	D	A	B	D			A		A




Liquid	Chemical Formula	Concentration %	Temp, degree C	Specific gravity kg/dm3	Viscosity cSt	Vapour pressure kPa	Bronze	Aluminium	Cast iron	Ductile iron	Hastelloy B	Hastelloy C	Stainless Steel SIS 2333	Stainless Steel SIS 2343	EP - Epoxy	CPVC	PP	PVDF	PTFE	FPM - Viton	EPDM - EPT	NBR - Nitrile	CR - Neoprene	Kairez	Hytrel	Carbon	Silicon	Ceramic
Caustic potash (Potassium hydroxide)	KOH	25	20				D	D	C			B		B	A	A	A	A	A	D	A	B	D			A		A
Caustic potash (Potassium hydroxide)	KOH	25	60				D	D	C			B		B	A	A	A	B	A	D	A	C	D			A		A
Caustic potash (Potassium hydroxide)	KOH	25	80				D	D	C			B		B	A	B	A	C	A	D	A	D	D			A		A
Caustic potash (Potassium hydroxide)	KOH	30	20	1.290		2.2	D	D	C			B		B	A	A	A	A	A	D	A	B	D			A		A
Caustic potash (Potassium hydroxide)	KOH	45	20	1.470			D	D	C			B		B	A	A	A	A	A	D	A	D	D			A		A
Caustic potash (Potassium hydroxide)	KOH	50	25	1.510		2.2	D	D	C			B		B	A	A	A	A	A	D	A	D	D			A		A
Caustic potash (Potassium hydroxide)	KOH	60	20	1.630			D	D	C			B		B	A	A	A	A	A	D	A	D	D			A		A
Caustic potash (Potassium hydroxide)	KOH	100	20	2.040																								
Cellosolve (Ethyl glycol)	C <sub>2</sub> H <sub>5</sub> OCH <sub>2</sub> CH <sub>2</sub> OH, C <sub>4</sub> H <sub>10</sub> O <sub>2</sub>	100	20	0.930		0.67		B						B			A	A	A	C	B	C			D	A		
Cellosolve (Ethyl glycol)	C <sub>2</sub> H <sub>5</sub> OCH <sub>2</sub> CH <sub>2</sub> OH, C <sub>4</sub> H <sub>10</sub> O <sub>2</sub>	100	40					B						B			A	A	A	D		D			D			
Cellosolve (Ethyl glycol)	C <sub>2</sub> H <sub>5</sub> OCH <sub>2</sub> CH <sub>2</sub> OH, C <sub>4</sub> H <sub>10</sub> O <sub>2</sub>	100	60					B						B				B	A	D		D			D			
Cellosolve (Ethyl glycol)	C <sub>2</sub> H <sub>5</sub> OCH <sub>2</sub> CH <sub>2</sub> OH, C <sub>4</sub> H <sub>10</sub> O <sub>2</sub>	100	80					B						B				C	A	D		D			D			
Cellosolve acetate (Ethyl glycol acetate)	CH <sub>3</sub> COOC <sub>2</sub> H <sub>4</sub> OC <sub>2</sub> H <sub>5</sub>	100	20	0.970		0.3												A		D		D						
Cellulose acetate		100	20					B		B				A				A										
Cellulose ether		100	20									A		A			A	A	A									
Cellulose glue		100	20				C							A	A		A			A		A	A					
Cellulose nitrate	C <sub>6</sub> H <sub>7</sub> O <sub>2</sub> (OH) <sub>2</sub> (ONO <sub>2</sub> )	100	20	1.660																								
Cetyl alcohol (Hexadecanol)	CH <sub>3</sub> (CH <sub>2</sub> ) <sub>15</sub> OH	100	20	0.800				A				A		A				A								A		
Chlor trisodium phosphate		100	20											A	A					A		A	A					
Chloral	cc13cHo	100	20	1.520		4.3																						
Chloral hydrate	CCL3-CH(OH)2	100	20					D				A					D	D	A	D		D				A		
Chlorepoxypropane	ocH2cHcH2cl	100	20												A						D	D	D					
Chlorethanoic sulfonic acid-B	clcH2cH2sO3H	100	20															A										
Chlorethanol (Ethylene chlorohydrin)	clcH2cH2sO3H	100	20																									
Chloric acid	HClO3	10	20					D				A		D			A	A	A	A		D				D		A
Chloric acid	HClO3	20	20					D				A		D			A	A	A	A		D						
Chloride of lime	Ca(ClO)2+4H2O	100	20	2.350			D	D	D					A	A		A	A	A	A		D	C			A		
Chloride of lime	CaOCl2	100	20				D	D	D					A	A		A	A	A	A		D	C			A		
Chlorinated glue		100	20				A		D						A	A				A	B	C	D					
Chlorinated hydrocarbons		100	20				A								A					D		A	D					
Chlorinated solvents		100	20																A	B	D	D						
Chlorine dioxide, pure	clO2	5	20					D				D		D				A	A							A		
Chlorine dioxide, pure	clO2	100	20	3.090				D						D		A	C	A	A	D	C	D	D					
Chlorine dioxide, pure	clO2	100	40					D						D		B	D	A	A	D	C	D	D					
Chlorine lye		100	20				A							A	A		D			A		C	A					
Chlorine trifluoride		100	20					A						A						D	D	D	D					
Chlorine water	Cl <sub>2</sub> +H <sub>2</sub> O	100	20					D				A		D		A	C	A	A	C	B	D				A		A






Liquid	Chemical Formula	Concentration %	Temp, degree C	Specific gravity kg/dm3	Viscosity cSt	Vapour pressure kPa	Bronze	Aluminium	Cast iron	Ductile iron	Hastelloy B	Hastelloy C	Stainless Steel SIS 2333	Stainless Steel SIS 2343	EP - Epoxy	CPVC	PP	PVDF	PTFE	FPM - Viton	EPDM - EPT	NBR - Nitrile	CR - Neoprene	Kairez	Hytrel	Carbon	Silicon	Ceramic	
Chloronitrobenzene	C <sub>6</sub> H <sub>4</sub> NO <sub>2</sub> Cl	100	20	1.370		0.7																							
Chloropicrin	CCl <sub>3</sub> NO <sub>2</sub>	100	20	1.660		2.7	D		A					A	A					D		D	D						
Chlorosulphonic acid, pure	HOCISO <sub>2</sub> , HCISO <sub>3</sub>	100	20	1.766	4	0	D	D	D	B		B		D	C	D	D	C	A	D	D	D	D	A	D	D		A	
Chlorosulphonic acid, pure'	HOCISO <sub>2</sub> , HCISO <sub>3</sub>	100	25	1.280			D	D	D	B		B		D	C	D	D	C	A	D	D	D	D	A	D	D		A	
Chlorosulphonic acid, pure	HOCSO <sub>2</sub> , HCISO <sub>3</sub>	100	40				D	D	D	B		B		D	C	D	D	D	A	D	D	D	D	A	D				
Chlorotoluene	cl-C <sub>6</sub> H <sub>4</sub> -CH <sub>3</sub>	100	20	1.080				A				A		A			D	A	A	A		D	D			A			
Chlorox (Bleach)		100	20				A		D			A		A	A	A	D			A	B	B	A						
Chocolate, chocolate svrup		100	20				D		D					A	A					A		A	A						
Chrome alum	KCr(SO <sub>4</sub> ) <sub>2</sub>	50	20	1.620				D				A		A		A	A	A	A	A	A	A	A						
Chrome alum, saturated	KCr(SO <sub>4</sub> ) <sub>2</sub>	100	20					D				A		A		A	A	A	A	A	A	A	A						
Chrome alum, saturated	KCr(SO <sub>4</sub> ) <sub>2</sub>	100	80					D				A		A				A	A	A	B	B							
Chrome, plating solution		100	20									A		B	C	A	D	A	A	A	C	A	A						
Chrome, plating solution		100	80									A		B	C	B	D	A	A	A	C	A	A						
Chromic acid	CrO <sub>3</sub>	5	20				D	A	D	C	A	A			B	A	A	A	A	A	A	D	D	A	D				
Chromic acid	CrO <sub>3</sub>	10	20	2.700			D	A	D	C		A			C	A	D	A	A	A	B	D	D	D	A	D	A		A
Chromic acid	CrO <sub>3</sub>	10	40				D	A	D	C		A			C	A	D	A	A	B	C	D	D	A	D				
Chromic acid	CrO <sub>3</sub>	10	60				D	A	D	C		A			C	A	D	A	A	B	D	D	D	A	D				
Chromic acid	CrO <sub>3</sub>	20	20				D	A	D	C		A			C	A	D	A	A	B	B	D	D	A	D				
Chromic acid	CrO <sub>3</sub>	20	40				D	A	D	C		A			C	A	D	A	A	B	D	D	D	A	D				
Chromic acid	CrO <sub>3</sub>	20	80				D	A	D	C		A			C	B	D	A	A	C	D	D	D	A	D				
Chromic acid	CrO <sub>3</sub>	25	20				D	A	D	C		A			C	A	D	A	A	B	B	D	D	A	D	A		A	
Chromic acid	CrO <sub>3</sub>	40	20				D	B	D	C		A			C	B	D	A	A	D	D	D	D	A	D				
Chromic acid	CrO <sub>3</sub>	40	40				D	B	D	C		A			C	C	D	A	A	D	D	D	D	A	D				
Chromic acid	CrO <sub>3</sub>	40	60				D	B	D	C		A			C	D	D	A	A	D	D	D	D	A	D				
Chromic acid	CrO <sub>3</sub>	50	20				D	B	D	C	D	A			C	C	D	A	A	D	D	D	D	A	D				
Chromic acid	CrO <sub>3</sub>	50	40				D	B	D	C	D	A			C	D	D	A	A	D	D	D	D	A	D				
Chromic acid	CrO <sub>3</sub>	50	60				D	B	D	C	D	A			C	D	D	B	A	D	D	D	D	A	D				
Chromic acid	CrO <sub>3</sub>	50	80				D	B	D	C	D	A			C	D	D	C	A	D	D	D	D	A	D				
Cutting oil		100	20						A					A	A					A		A	D						
Cutting oil containing sulfur		100	20						A					A	A					A		A	C						
Cutting oil water soluble		100	20				A		A					A	A					A			D						
Cyanbromide	BrCN	100	20	2.020		12.2																							
Cyanic acid	CNOH	100	20				D		D					A	A							C	D						
Cyanoacetic acid	(CH <sub>2</sub> CNCO <sub>2</sub> H, CNCH <sub>2</sub> COOH	100	20											A			A	A	A								A		
Cyanogen	(CN) <sub>2</sub>	100	20																										
Cyclohexane, pure	C <sub>6</sub> H <sub>12</sub> , (CH <sub>2</sub> ) <sub>6</sub>	100	20	0.779	1.3	10.4	A	A	A			A		A	A	D	C	A	A	A	D	B	D	A	A	A			
Cyclohexane, pure	C <sub>6</sub> H <sub>12</sub> , (CH <sub>2</sub> ) <sub>6</sub>	100	40				A	A	A			A		A	A	D	D	A	A	A	D		D	A					
Cyclohexanol, pure	C <sub>6</sub> H <sub>11</sub> OH, C <sub>6</sub> H <sub>12</sub> O	100	20	0.960	70	0.1		C				A		A	A	D	A	A	A	A	B	C	A			A			




Liquid	Chemical Formula	Concentration %	Temp, degree C	Specific gravity kg/dm3	Viscosity cSt	Vapour pressure kPa	Bronze	Aluminium	Cast iron	Ductile iron	Hastelloy B	Hastelloy C	Stainless Steel SIS 2333	Stainless Steel SIS 2343	EP - Epoxy	CPVC	PP	PVDF	PTFE	FPM - Viton	EPDM - EPT	NBR - Nitrile	CR - Neoprene	Kairez	Hytrek	Carbon	Silicon	Ceramic
Cyclohexanol, pure	C <sub>6</sub> H <sub>11</sub> OH, C <sub>6</sub> H <sub>12</sub> O	100	40					C				A	A	A	D	B	A	A	A				A					
Cyclohexanol, pure	C <sub>6</sub> H <sub>11</sub> OH, C <sub>6</sub> H <sub>12</sub> O	100	60					C				A	A	A	D	C	A	A					A					
Cyclohexanol, pure	C <sub>6</sub> H <sub>11</sub> OH, C <sub>6</sub> H <sub>12</sub> O	100	80					C				A	A	A	D	D	A	A					A					
Cyclohexanone (Anon), pure	C <sub>6</sub> H <sub>10</sub> O, (CH <sub>2</sub> ) <sub>5</sub> CO	100	20	0.950	5	0.5		A				A	A	B	D	B	B	A	D	C	D	D	A			A		
Cyclohexanone (Anon), pure	C <sub>6</sub> H <sub>10</sub> O, (CH <sub>2</sub> ) <sub>5</sub> CO	100	40					A				A	A	B	D	C	C	A	D		D	D	A					
Cyclohexanone (Anon), pure	C <sub>6</sub> H <sub>10</sub> O, (CH <sub>2</sub> ) <sub>5</sub> CO	100	60					A				A	A	B	D	D	C	A	D		D	D	A					
Cyclohexanone (Anon), pure	C <sub>6</sub> H <sub>10</sub> O, (CH <sub>2</sub> ) <sub>5</sub> CO	100	80					A				A	A	B	D	D	D	A	D		D	D	A					
Cyclohexene	C <sub>6</sub> H <sub>10</sub>	100	20	0.810																					C			
Cyclohexylamine	C <sub>6</sub> H <sub>11</sub> NH <sub>2</sub>	100	20	0.860		1.4																						
Cyclopentane	C <sub>5</sub> H <sub>10</sub>	100	20	0.745	0.6	34.7																						
Cyclopropane	C <sub>3</sub> H <sub>6</sub>	100	20																									
Decaborane	B <sub>10</sub> H <sub>14</sub>	100	20	0.940																								
Decalin (Decahydronaphthalene), pure	C <sub>10</sub> H <sub>18</sub>	100	20	0.880				A								C	A	A	A	D	D	D				A		
Decane (Capric acid), pure	CH <sub>3</sub> (CH <sub>2</sub> ) <sub>8</sub> CO <sub>2</sub> H	100	20					A					A				A	A	A	D	D	D						
Denatured alcohol		100	20					A									A	A	A	A	A	A						
Densodrin W		100	20															A				A						
Detergent solutions		100	20										A			A	A	A	A	A	A	A	A					
Detergents, svnthetic		100	20					A		B			A			A	A	A	A	A	A	A	A					
Dextrin, saturated	(C <sub>6</sub> H <sub>10</sub> O <sub>5</sub> )-n	100	20					A				A	A		A	A	A	A	A	A	A	A				A		
Dextrin, saturated	(C <sub>6</sub> H <sub>10</sub> O <sub>5</sub> )-n	100	80					A				A	A		A	A	A	A	A	A	A	B						
Dextrose	C <sub>6</sub> H <sub>12</sub> O <sub>6</sub>	100	20					A		B			A		A	A	A	A	A	A	A	A				C		
Dextrose	C <sub>6</sub> H <sub>12</sub> O <sub>6</sub>	100	80					A		B			A		A	A	A	A	A	A	B					C		
Diacetone alcohol, pure	(CH <sub>3</sub> ) <sub>2</sub> COHCH <sub>2</sub> COCH <sub>3</sub>	100	20	0.940		0.1	A	A	A		A	A	A	A		A	A	A	D	A	D	A			C			
Diacetone alcohol, pure	(CH <sub>3</sub> ) <sub>2</sub> COHCH <sub>2</sub> COCH <sub>3</sub>	100	40				A	A	A		A	A	A	A		A	B	A	D		D	A			C			
Diacetone alcohol, pure	(CH <sub>3</sub> ) <sub>2</sub> COHCH <sub>2</sub> COCH <sub>3</sub>	100	60				A	A	A		A	A	A	A			C	A	D		D	A			C			
Diacetone alcohol, pure	(CH <sub>3</sub> ) <sub>2</sub> COHCH <sub>2</sub> COCH <sub>3</sub>	100	80				A	A	A		A	A	A	A			D	A	D		D	A			C			
Diacetone, pure	(CH <sub>3</sub> ) <sub>2</sub> C(OH)CH <sub>2</sub> COCH <sub>3</sub>	100	20	0.930		0.1		A					A				D	A	D	B	A							
Diamylamine	(C <sub>5</sub> H <sub>11</sub> ) <sub>2</sub> NH	100	20	0.780																								
Diazo salt solution		100	20					D					A			A		A								A		
Dibenzyl ether, pure	(C <sub>6</sub> H <sub>5</sub> CH <sub>2</sub> ) <sub>2</sub> O	100	20				D	B	D				A	A			A	A		C	D	D						
Dibenzyl ether, pure	(C <sub>6</sub> H <sub>5</sub> CH <sub>2</sub> ) <sub>2</sub> O	100	40				D	B	D				A	A			B	A			D	D						
Dibenzyl ether, pure	(C <sub>6</sub> H <sub>5</sub> CH <sub>2</sub> ) <sub>2</sub> O	100	60				D	B	D				A	A			C	A			D	D						
Dibenzyl ether, pure	(C <sub>6</sub> H <sub>5</sub> CH <sub>2</sub> ) <sub>2</sub> O	100	80				D	B	D	1			A	A			D	A			D	D						
Dibenzyl sebecate		100	20																	B	C		D		A			
Diborane	B <sub>2</sub> H <sub>6</sub>	100	20	0.460																								
Dibutyl amine, pure		100	20															A	A	D	D	D	D					
Dibutyl amine, pure		100	40															C	A	D	D	D	D					
Dibutyl amine, pure		100	60															D	A	D	D	D	D					



Liquid	Chemical Formula	Concentration %	Temp, degree C	Specific gravity kg/dm3	Viscosity cSt	Vapour pressure kPa	Bronze	Aluminium	Cast iron	Ductile iron	Hastelloy B	Hastelloy C	Stainless Steel SIS 2333	Stainless Steel SIS 2343	EP - Epoxy	CPVC	PP	PVDF	PTFE	FPM - Viton	EPDM - EPT	NBR - Nitrile	CR - Neoprene	Kairez	Hytrel	Carbon	Silicon	Ceramic		
Dibutyl aniline	C <sub>6</sub> H <sub>5</sub> N(C <sub>4</sub> H <sub>9</sub> ) <sub>2</sub>	100	20	0.940																										
Dibutyl ether, pure	C <sub>8</sub> H <sub>18</sub> O, CH <sub>3</sub> (CH <sub>2</sub> ) <sub>3</sub> O(CH <sub>2</sub> ) <sub>3</sub> CH <sub>3</sub>	100	20	0.770			D	B	D					A	A		D	A	A	D	D	B	D							
Dibutyl ether, pure	C <sub>8</sub> H <sub>18</sub> O, CH <sub>3</sub> (CH <sub>2</sub> ) <sub>3</sub> O(CH <sub>2</sub> ) <sub>3</sub> CH <sub>3</sub>	100	40				D	B	D					A	A		D	B	A	D	D		D							
Dibutyl ether, pure	C <sub>8</sub> H <sub>18</sub> O, CH <sub>3</sub> (CH <sub>2</sub> ) <sub>3</sub> O(CH <sub>2</sub> ) <sub>3</sub> CH <sub>3</sub>	100	60				D	B	D					A	A		D	C	A	D	D		D							
Dibutyl ether, pure	C <sub>8</sub> H <sub>18</sub> O, CH <sub>3</sub> (CH <sub>2</sub> ) <sub>3</sub> O(CH <sub>2</sub> ) <sub>3</sub> CH <sub>3</sub>	100	80				D	B	D					A	A		D	D	A	D	D		D							
Dibutyl peroxide	(CH <sub>3</sub> ) <sub>3</sub> COOC(CH <sub>3</sub> ) <sub>3</sub>	100	20	0.790		2.6																								
Dibutyl phthalate, pure	C <sub>6</sub> H <sub>4</sub> (C <sub>0</sub> 2C <sub>4</sub> H <sub>9</sub> ) <sub>2</sub>	100	20	1.050								A		A			A	A	A	B	A	D	D		A	A				
Dibutyl phthalate, pure	C <sub>6</sub> H <sub>4</sub> (C <sub>0</sub> 2C <sub>4</sub> H <sub>9</sub> ) <sub>2</sub>	100	40									A		A			A	B	A		A	D	D		A					
Dibutyl phthalate, pure	C <sub>6</sub> H <sub>4</sub> (C <sub>0</sub> 2C <sub>4</sub> H <sub>9</sub> ) <sub>2</sub>	100	60									A		A			A	C	A			D	D		A					
Dibutyl phthalate, pure	C <sub>6</sub> H <sub>4</sub> (C <sub>0</sub> 2C <sub>4</sub> H <sub>9</sub> ) <sub>2</sub>	100	80									A		A			A	D	A			D	D		A					
Dibutyl sebacate	C <sub>8</sub> H <sub>16</sub> (COOC <sub>4</sub> H <sub>9</sub> ) <sub>2</sub>	100	20											A			A	A	A	C	B	D	D		A					
Dibutyl sebacate	C <sub>8</sub> H <sub>16</sub> (COOC <sub>4</sub> H <sub>9</sub> ) <sub>2</sub>	100	40											A			A	B	A			D	D							
Dibutyl sebacate	C <sub>8</sub> H <sub>16</sub> (COOC <sub>4</sub> H <sub>9</sub> ) <sub>2</sub>	100	60											A			A	C	A			D	D							
Dibutyl sebacate	C <sub>8</sub> H <sub>16</sub> (COOC <sub>4</sub> H <sub>9</sub> ) <sub>2</sub>	100	80											A			A	D	A			D	D							
Dichlorodifluormethane (Freon 12)	cc12F2	100	20	1.320																										
Dichlorethane (Ethylene chloride)	cH2Cl-cH2cl	100	20	1.180		31.2																								
Dichloroacetic acid	CHCl2C02H, CHCl2-COOH	50	20															A	A	A	D		D							
Dichloroacetic acid	CHCl2C02H, CHCl2-COOH	100	20	1.560														A	A	A	D		D							
Dichloroacetic acid methyl ester	Cl2CHOOCH3	100	20															A	A	A	D		D							
Dichloroaniline	NH <sub>2</sub> C <sub>6</sub> H <sub>3</sub> Cl <sub>2</sub>	100	20																											
Dichlorobenzene, pure	C <sub>6</sub> H <sub>4</sub> Cl <sub>2</sub>	100	20	1.320										B	A		D	A	A	B	D	D	D	A	D	A				
Dichlorobenzene, pure	C <sub>6</sub> H <sub>4</sub> Cl <sub>2</sub>	100	80											B	A		D	B	A		D	D	D	A	D					
Dichlorobenzene-O, -P	C <sub>6</sub> H <sub>4</sub> Cl <sub>2</sub>	100	20	1.310										B	A		D	A	A	B	D	D	D	A	D	A				
Dichlorobenzene-O, -P	C <sub>6</sub> H <sub>4</sub> Cl <sub>2</sub>	100	80											B	A		D	B	A		D	D	D	A	D					
Dichloroethylene	CH <sub>2</sub> cc12, C <sub>2</sub> H <sub>2</sub> Cl <sub>2</sub>	100	20	1.220		32	B			B		A					A	A	A	A	D	D	D			A				
Dichlorohydrine	(CH <sub>2</sub> Cl) <sub>2</sub> 2CHOH	100	25	1.360																										
Diisopropyl ketone, pure	(CH <sub>3</sub> ) <sub>2</sub> CHCOCH(CH <sub>3</sub> ) <sub>2</sub>	100	40											A	A				D		D	D	D							
Diisopropyl peroxydicarbonate	(CH <sub>3</sub> ) <sub>2</sub> CHOCOOCH(CH <sub>3</sub> ) <sub>2</sub>	100	20	1.080																										
Dimethyl amine, aqueous	(CH <sub>3</sub> ) <sub>2</sub> NH+H <sub>2</sub> O	40	25	0.890		28.6																								
Dimethyl amine, pure	(CH <sub>3</sub> ) <sub>2</sub> NH	100	20	0.650		171											D	A	B	A	D	A	D							
Dimethyl amine, pure	(CH <sub>3</sub> ) <sub>2</sub> NH	100	40														D	B	C	A	D		D							
Dimethyl amine, pure	(CH <sub>3</sub> ) <sub>2</sub> NH	100	60														D		D	A	D		D							
Dimethyl aniline, pure	C <sub>8</sub> H <sub>11</sub> N	100	20	0.957															B		D	D	D	D						
Dimethyl aniline, pure	C <sub>8</sub> H <sub>11</sub> N	100	40																C		D	D	D	D						
Dimethyl aniline, pure	C <sub>8</sub> H <sub>11</sub> N	100	60																D		D	D	D	D						
Dimethyl ethanolamine	(CH <sub>3</sub> ) <sub>2</sub> NC <sub>2</sub> H <sub>4</sub> OH	100	20	0.890		0.6																								
Dimethyl ether	CH <sub>3</sub> OCH <sub>3</sub>	100	20	0.670		510		A				A		A			D		A	A		D				A		A		
Dimethyl formamide, pure'	HCON(CH <sub>3</sub> ) <sub>2</sub> , (CH <sub>3</sub> ) <sub>2</sub> NCHO	100	20	0.950	10	0.35		A					A		D	A	D	A	D	A	D	B	D	C	A	A	A		A	









Liquid	Chemical Formula	Concentration %	Temp, degree C	Specific gravity kg/dm3	Viscosity cSt	Vapour pressure kPa	Bronze	Aluminium	Cast iron	Ductile iron	Hastelloy B	Hastelloy C	Stainless Steel SIS 2333	Stainless Steel SIS 2343	EP - Epoxy	CPVC	PP	PVDF	PTFE	FPM - Viton	EPDM - EPT	NBR - Nitrile	CR - Neoprene	Kairez	Hytrek	Carbon	Silicon	Ceramic		
Ethyl formate, pure	Hco <sub>2</sub> C <sub>2</sub> H <sub>5</sub>	100	20	0.920		25.6		C						B					A	A	C	D	B							
Ethyl hexaldehyde	C <sub>4</sub> H <sub>9</sub> CH(C <sub>2</sub> H <sub>5</sub> )CHO	100	20	0.900		0.1																								
Ethyl hexanol	C <sub>4</sub> H <sub>9</sub> CH(C <sub>2</sub> H <sub>5</sub> )CH <sub>2</sub> OH, C <sub>8</sub> H <sub>18</sub> O	100	20	0.830														A	A			D								
Ethyl hexylamine	C <sub>4</sub> H <sub>9</sub> CH(C <sub>2</sub> H <sub>5</sub> )CH <sub>2</sub> NH <sub>2</sub>	100	20	0.790																										
Ethyl mercaptan, pure	C <sub>2</sub> H <sub>5</sub> Sh	100	20	0.840				B						B				A	A	A	A	D								
Ethyl mercaptan, pure	C <sub>2</sub> H <sub>5</sub> sH	100	50			177		B						B					A	A		D								
Ethyl methyl ether	CH <sub>3</sub> OC <sub>2</sub> H <sub>5</sub>	100	20																A				A							
Ethyl nitrite	C <sub>2</sub> H <sub>5</sub> ONO	100	20																					A						
Ethyl oxalate		100	20					A											A	D	A	D	C							
Ethyl pentachlorobenzene		100	20																A	A		C	D							
Ethyl silicate	(OC <sub>2</sub> H <sub>5</sub> ) <sub>4</sub> Si	100	20	0.935		0.27		B						A					A	A	A	A	A							
Ethyl sulphate	(C <sub>2</sub> H <sub>5</sub> ) <sub>2</sub> SO <sub>4</sub>	100	20	1.180										D	A					A		A								
Ethyl sulphuric acid	C <sub>2</sub> H <sub>5</sub> OSO <sub>3</sub> H	100	20	1.320				D				A						A								A		A		
Ethyl trichlorosilane	C <sub>2</sub> H <sub>5</sub> SiCl <sub>3</sub>	100	15	1.240		2.7																								
Ethylene (Ethene)	c <sub>2</sub> h <sub>4</sub> , ch <sub>2</sub> =ch <sub>2</sub>	100	20	0.410				A						A					A	A	A	C	A							
Ethylene bromide, pure	C <sub>2</sub> H <sub>4</sub> Br <sub>2</sub> , CH <sub>2</sub> BrCH <sub>2</sub> Br	100	20	2.180		1.2		A		B		A		A			D	A	A	C	B	D	D	A		A		A		
Ethylene chloride (Dichlorethane)	CH <sub>2</sub> ClCH <sub>2</sub> Cl	100	20	1.260			A	C			B	B		A	A		B	A	A	A	D	D	D			A		A		
Ethylene chloride (Dichlorethane)	CH <sub>2</sub> ClCH <sub>2</sub> Cl	100	30			8.7	A	C			B	B		A	A		D	A	A		D	D	D			A		A		
Ethylene chloride (Dichlorethane)	CH <sub>2</sub> ClCH <sub>2</sub> Cl	100	40				A	C			B	B		A	A		D	A	A		D	D	D			A		A		
Ethylene chlorohydrin, pure	CH <sub>2</sub> ClCH <sub>2</sub> Cl	100	20	1.210		0.65		A				A		A			A	A	A	D	A	D	B	C		A		A		
Ethylene chlorohydrin, pure	CH <sub>2</sub> ClCH <sub>2</sub> Cl	100	40					A				A		A				B	A	D		D	B	C						
Ethylene chlorohydrin, pure	CH <sub>2</sub> ClCH <sub>2</sub> Cl	100	60					A				A		A				C	A	D		D	B							
Ethylene chlorohydrin, pure	CH <sub>2</sub> ClCH <sub>2</sub> Cl	100	80					A				A		A				D	A	D		D	B							
Ethylene cyanohydrin	CH <sub>2</sub> (OH)CH <sub>2</sub> CN	100	20	1.060																										
Ethylene diamine, pure	NH <sub>2</sub> CH <sub>2</sub> CH <sub>2</sub> NH <sub>2</sub>	100	20	0.900	1.5	1.4		D				A		A			A	B	A	D	A	A	A	A		A		A		
Ethylene diamine, pure	NH <sub>2</sub> CH <sub>2</sub> CH <sub>2</sub> NH <sub>2</sub>	100	40					D				A		A			A	D	A	D			A	A						
Ethylene dichloride (Dichloroethane)	C <sub>2</sub> H <sub>4</sub> Cl	100	20	1.250	8		C	C	A		A	B		A	A	D	B	A	A	A	D	D	D		D					
Ethylene fluoride	CH <sub>3</sub> CHF <sub>2</sub>	100	20	0.910																										
Ethylene glycol (Cellosolves), pure	C <sub>2</sub> H <sub>4</sub> (OH) <sub>2</sub> , HOCH <sub>2</sub> CH <sub>2</sub> OH	100	20	1.110	18-90		A	A	A			A		A	A	A	A	A	A	A	A	A	A	A	A	A	A	A		
Ethylene glycol (Cellosolves), pure	C <sub>2</sub> H <sub>4</sub> (OH) <sub>2</sub> , HOCH <sub>2</sub> CH <sub>2</sub> OH	100	80				A	A	A			A		A	A	B	B	B	A	A	A	A	A	A	A	A	A			
Ethylene oxide	(CH <sub>2</sub> ) <sub>2</sub> O, CH <sub>2</sub> OCH <sub>2</sub>	100	20	0.870	1.1	145	A	A	D					B	A	D	D	A	A	D	D	D	D	A	A	A				
Ethylene oxide	(CH <sub>2</sub> ) <sub>2</sub> O, CH <sub>2</sub> OCH <sub>2</sub>	100	40				A	A	D					B	A	D	D	B	A	D	D	D	D	A	A					
Ethylene oxide	(CH <sub>2</sub> ) <sub>2</sub> O, CH <sub>2</sub> OCH <sub>2</sub>	100	60				A	A	D					B	A	D	D	C	A	D	D	D	D	A	A					
Ethylene oxide	(CH <sub>2</sub> ) <sub>2</sub> O, ch <sub>2</sub> och <sub>2</sub>	100	80				A	A	D					B	A	D	D	D		D	D	D	D	A	A					
Ethylene trichloride	ClCH=Cl <sub>2</sub>	100	20	1.460		7.7		C						A						A	D	D	D							
Ethylenimine	NHCH <sub>2</sub> CH <sub>2</sub>	100	20	0.830		22																								
Fat		100	20				A							A	A					A			D							
Fatty acid (Sebacic acid)	C <sub>17</sub> H <sub>33</sub> CO <sub>2</sub> H	100	20	0.900			C	A	C	C	A	A		A	A	B	A	A	A	A	D	A	D		C				A	






Liquid	Chemical Formula	Concentration %	Temp, degree C	Specific gravity kg/dm3	Viscosity cSt	Vapour pressure kPa	Bronze	Aluminium	Cast iron	Ductile iron	Hastelloy B	Hastelloy C	Stainless Steel SIS 2333	Stainless Steel SIS 2343	EP - Epoxy	CPVC	PP	PVDF	PTFE	FPM - Viton	EPDM - EPT	NBR - Nitrile	CR - Neoprene	Kairez	Hytrek	Carbon	Silicon	Ceramic		
Fluorine monoxide	OF <sub>2</sub>	100	20	1.900																										
Fluorobenzene		100	20																	A	D	D	D							
Fluosilicic acid (Fluoric siicate)	H <sub>2</sub> SiF <sub>6</sub>	25	20	1.240			D	D	D	D		A		B	A	A		A		A		A	A							
Fluosilicic acid (Fluoric siicate)	H <sub>2</sub> SiF <sub>6</sub>	32	20																											
Fluosilicic acid (Fluoric siicate)	H <sub>2</sub> SiF <sub>6</sub>	50	20				D	D	D	D		A		B	A	A	A	A	A	A	A	A	A							
Fluosilicic acid (Fluoric siicate)	H <sub>2</sub> SiF <sub>6</sub>	50	40				D	D	D	D		A		B	A	A	A	A	A	A	A	A	B	A						
Fluosilicic acid (Fluoric siicate)	H <sub>2</sub> SiF <sub>6</sub>	50	80				D	D	D	D		A		B	A	B	B	A	A	A	A	B	B	A						
Fluosilicic acid (Fluoric siicate)	H <sub>2</sub> SiF <sub>6</sub>	100	20				D	D	D	D		A		B	A	A		A		C	B	A	A							
Formaldehyde	HCHO, CH <sub>2</sub> O	35	20				C	A	C	D	B	B		A	A	A	A	A	A	A	A	A	B	D	A	C				
Formaldehyde	HCHO, CH <sub>2</sub> O	35	60				C	A	C	D	B	B		A	A	A	A	B	A	A	A	A	B	D		C				
Formaldehyde	HCHO, CH <sub>2</sub> O	35	80				C	A	C	D	B	B		A	A	A	A	D	A	A	A	A	B	D		C				
Formaldehyde	HCHO, CH <sub>2</sub> O	37	20	1.1	0.9		C	A	C	D	B	B		A	A	A	A	A	A	A	A	A	B	D		C				
Formaldehyde	HCHO, CH <sub>2</sub> O	37	60				C	A	C	D	B	B		A	A	A	A	B	A	A	A	A	B	D		C				
Formaldehyde	HCHO, CH <sub>2</sub> O	37	80				C	A	C	D	B	B		A	A	A	A	D	A	A	A	A	B	D		C				
Formaldehyde	HCHO, CH <sub>2</sub> O	40	20				C	A	C	D	B	B		A	A	A	A	A	A	A	A	A	A	D	A	A	A		A	
Formaldehyde	HCHO, CH <sub>2</sub> O	50	20				C	A	C	D	B	B		A	A	A	A	A	A	B	A		D	D						
Formaldehyde	HCHO, CH <sub>2</sub> O	50	60				C	A	c	D	B	B		A	A	A	A	B	A				D	D						
Formaldehyde	HCHO, CH <sub>2</sub> O	50	80				C	A	c	D	B	B		A	A	A	A	D	A				D	D						
Formaldehyde	HCHO, CH <sub>2</sub> O	100	25	0.820			C	A	c	D	B	B		A	A	A	A	A	A	A	B	C	D							
Formalin	HCHO	100	20	1.100			C	A	c		B	B		A	A	A	A	A	A	A	A	B	C	D						
Formamide	HCONH <sub>2</sub>	100	20	1.130	3			A				A		A					A	D		A				A	A			
Formamide	HCONH <sub>2</sub>	100	70			0.13		A						A						D										
Formic acid (Methanoic acid)	HCOOH, HC02H	50	20									A		A				A	A	A	A	A	D	A	D					
Formic acid (Methanoic acid)	HCOOH, HC02H	90	20				C	B	D	D	B	A		B	A	A	A	A	A	D	A	D	D	D						
Formic acid (Methanoic acid)	HCOOH, HC02H	90	40				C	B	D	D	B	A		B	A	B	B	A	A	D	A	D	D	D						
Formic acid (Methanoic acid)	HCOOH, HC02H	90	60				C	B	D	D	B	A		B	A	D	D	A	A	D	A	D	D	D						
Formic acid (Methanoic acid)	HCOOH, HC02H	100	20	1.220	1.5	4.4	C	A	D	D	B	A		B	A	A	A	A	A	D	A	D	D	D		A		A		
Freon 11	CCl <sub>3</sub> F, CFCI <sub>3</sub>	100	20	1.494		89	A	B	C					C	A	A	D	A	A	B	C	D	D	D	A					
Freon 113	CF <sub>2</sub> =CFCl	100	20	1.000		576																								
Freon 112		100	20																	A		B	B							
Freon 113	CCl <sub>2</sub> FccI <sub>2</sub>	100	20	1.563		36	A							A	A			A	A	B	D	D	D	D	A					
Freon 114	CF <sub>2</sub> cIcF <sub>2</sub> cI	100	20	1.000		122												A	A	A	C	B	A		A					
Freon 114 B2		100	20																		B	D	B	A						
Freon 115		100	20																	B	A	A	A							
Freon 12	cCl <sub>2</sub> F <sub>2</sub>	100	20	1.000		587	A		A	B				D	A	A	A	A	A	B	B	C	D	A	A	A				
Freon 12 B1	CClF <sub>2</sub> Br	100	20	1.000		253																								
Freon 13	CCIF <sub>3</sub>	100	20	1.000		324														A	A	A	A							
Freon 13 B1		100	20																	A	A	A	A		C					




Liquid	Chemical Formula	Concentration %	Temp, degree C	Specific gravity kg/dm3	Viscosity cSt	Vapour pressure kPa	Bronze	Aluminium	Cast iron	Ductile iron	Hastelloy B	Hastelloy C	Stainless Steel SIS 2333	Stainless Steel SIS 2343	EP - Epoxy	CPVC	PP	PVDF	PTFE	FPM - Viton	EPDM - EPT	NBR - Nitrile	CR - Neoprene	Kairez	Hytrel	Carbon	Silicon	Ceramic
Freon 133 a	CH <sub>2</sub> Cl-CF <sub>3</sub>	100	20	1.000		182																						
Freon 142 b	C <sub>2</sub> H <sub>3</sub> ClF <sub>2</sub>	100	20	1.118		303														D		A	A					
Freon 152 a		100	20																	D		A	A					
Freon 21	CHCl <sub>2</sub> F	100	20	1.380		162											D	A	A	C	C	D	B	D				
Freon 21	CHCl <sub>2</sub> F	100	40														D	A	A	D		D	B	D				
Freon 218		100	20																	A		A	A					
Freon 22	CHClF <sub>2</sub>	100	20	1.213		950	A		C				C	A	D	C	A	A	A	D	B	D	D	D	D			
Freon 23	CHF <sub>3</sub>	100	20	1.000		4295																						
Freon 31		100	20																		D		D	A				
Freon 32		100	20																		C		A	A				
Freon 502		100	20	1.4	0.24																B		B	A				
Freon BF		100	20																				B	B				
Freon C316		100	20																				A	A				
Freon C318		100	20																		A		A	A				
Freon MF		100	20																				A	C				
Freon T-P35		100	20																	A	A		A	A				
Freon T-WD602		100	20																	A	A		B	B				
Freon TA		100	20																		C		A	A				
Freon TC		100	20																	A	A		A	A				
Freon TF		100	20				A						A	A	B					B	D	C	D					
Glycerphosphoric acid	C <sub>3</sub> H <sub>7</sub> O <sub>3</sub> P(OH) <sub>2</sub>	100	20																A									
Glycocoil (Glycine, Aminoacetic acid)	NH <sub>2</sub> CH <sub>2</sub> COOH	10	20																									
Glycocoll (Glycine, Aminoacetic acid)	NH <sub>2</sub> CH <sub>2</sub> COOH	100	20														A	A	A	A		A					A	
Glycol (Ethylene glycol), pure	C <sub>2</sub> H <sub>4</sub> (OH) <sub>2</sub> , HOCH <sub>2</sub> CH <sub>2</sub> OH	100	20	1.110			A	A	A	B		A	A	A	A	A	A	A	A	A	A	A	A		A	A		
Glycol (Ethylene glycol), pure	C <sub>2</sub> H <sub>4</sub> (OH) <sub>2</sub> , HOCH <sub>2</sub> CH <sub>2</sub> OH	100	80				A	A	A	B		A	A	A	B	B	B	B	A	A	A	A	A					
Glycol acetate	CH <sub>2</sub> OH-CH <sub>2</sub> O	100	20	1.110																							A	
Glycolic acid, saturated	HOCH <sub>2</sub> COOH, CH <sub>2</sub> OHC <sub>2</sub> H	37	20					A				A	A	A	A	A	A	A	A	A	A	A	A	A	A		A	
Glycolic acid, saturated	HOCH <sub>2</sub> COOH, CH <sub>2</sub> OHC <sub>2</sub> H	70	20												A	A	A	A	A	A	A	A	A	A				
Glycolic acid, saturated	HOCH <sub>2</sub> COOH, CH <sub>2</sub> OHC <sub>2</sub> H	100	20												A	A	A	A	A	A	A	A	A	A				
Glycolic acid, saturated	HOCH <sub>2</sub> COOH, CH <sub>2</sub> OHC <sub>2</sub> H	100	40												A	A	A	B	A				A					
Glycolic acid, saturated	HOCH <sub>2</sub> COOH, CH <sub>2</sub> OHC <sub>2</sub> H	100	60												A	A	A	C	A				A					
Glycolic acid, saturated	HOCH <sub>2</sub> COOH, CH <sub>2</sub> OHC <sub>2</sub> H	100	80												A	A		D	A				A					
Gold monocyaniide	AuCN	100	20				A		D				A	A						A		A	A					
Gold, plating solution		100	20										A	A	A	D	A	A	A	A	A	A	A					
Grape iuice		100	20				A		D				A	A	A					A		A	A					
Grape sugar		100	20												A	A	A	A	A	A	A	A	A					
Grape suqar		100	80															A	A	A	A	A	B					
Grease		100	20				A		A				A	A						A		D	D		A			





Liquid	Chemical Formula	Concentration %	Temp, degree C	Specific gravity kg/dm <sup>3</sup>	Viscosity cSt	Vapour pressure kPa	Bronze	Aluminium	Cast iron	Ductile iron	Hastelloy B	Hastelloy C	Stainless Steel SIS 2333	Stainless Steel SIS 2343	EP - Epoxy	CPVC	PP	PVDF	PTFE	FPM - Viton	EPDM - EPT	NBR - Nitrile	CR - Neoprene	Kairez	Hytrek	Carbon	Silicon	Ceramic	
Hydrochloric acid, aqueous solution	HCl+H <sub>2</sub> O	5	20					D	D	D			D	D			A	A	A	A	A	C	C	A					
Hydrochloric acid, aqueous solution	HCl+H <sub>2</sub> O	5	40					D	D	D			D	D			A	A	A	A	A	D	D	A					
Hydrochloric acid, aqueous solution	HCl+H <sub>2</sub> O	5	80					D	D	D			D	D			C	A	A	A	A	D	D	A					
Hydrochloric acid, aqueous solution	HCl+H <sub>2</sub> O	10	20					D		D		A		D			A	A	A	A	A	C	C	A		A		A	
Hydrochloric acid, aqueous solution	HCl+H <sub>2</sub> O	10	40					D		D		A		D			A	A	A	A	A	D	P	A		A		A	
Hydrochloric acid, aqueous solution	HCl+H <sub>2</sub> O	10	60					D		D		A		D			C	A	A	A	A	D	D			A		A	
Hydrochloric acid, aqueous solution	HCl+H <sub>2</sub> O	20	20	1.100	1	1.3	D	D	D	D	B	A	D	D	A	A	A	A	A	A	A	A	D	D	A		A		A
Hydrochloric acid, aqueous solution	HCl+H <sub>2</sub> O	20	40				D	D	D	D	B	A	D	D	A	A	C	A	A	A	A			A		A		A	
Hydrochloric acid, aqueous solution	HCl+H <sub>2</sub> O	20	60				D	D	D	D	B	A	D	D	A	A	C	A	A	C	C			A		A		A	
Hydrochloric acid, aqueous solution	HCl+H <sub>2</sub> O	20	80				D	D	D	D	B	A	D	D	A	A	D	A	A					A		A		A	
Hydrochloric acid, aqueous solution	HCl+H <sub>2</sub> O	25	20	1.150				D	D	D		A	D	D			A	A	A	A	A	A	C	D	A		A		A
Hydrochloric acid, aqueous solution	HCl+H <sub>2</sub> O	25	40					D	D	D		A	D	D			A	A	A	A	A	A	D		A		A		A
Hydrochloric acid, aqueous solution	HCl+H <sub>2</sub> O	25	80					D	D	D		A	D	D			A	A	A	A	D	B	D		A		A		A
Hydrochloric acid, aqueous solution	HCl+H <sub>2</sub> O	35	20	1.180		1.3		D	D	D		D	D	D			A	A	A	A	B	B	C	D	A		A		A
Hydrochloric acid, aqueous solution	HCl+H <sub>2</sub> O	35	40					D	D	D		D	D	D			A	A	A	A	B	B	D	D	A		A		A
Hydrochloric acid, aqueous solution	HCl+H <sub>2</sub> O	35	60					D	D	D		D	D	D			A	A	A	A	D	D	D			A		A	
Hydrochloric acid, aqueous solution	HCl+H <sub>2</sub> O	35	80					D	D	D		D	D	D			B	B	A	A	D	D	D			A		A	
Hydrochloric acid, aqueous solution	HCl+H <sub>2</sub> O	37	20				D	D	D	D	A	A		D	A	A	A	A	A	A	A	A	D	D	A		A		A
Hydrochloric acid, aqueous solution	HCl+H <sub>2</sub> O	37	40				D	D	D	D	A	A		D	A	A	C	A	A	A	C	D	D	A		A		A	
Hydrochloric acid, aqueous solution	HCl+H <sub>2</sub> O	37	60				D	D	D	D	A	A		D	A	A	D	A	A	C	D	D	D			A		A	
Hydrochloric acid, aqueous solution	HCl+H <sub>2</sub> O	38	20	1.200				D	D	D		D	D	D			A	A	A	A	B	C	C	D	A		A		A
Hydrochloric acid, aqueous solution	HCl+H <sub>2</sub> O	38	40					D	D	D		D	D	D			A	A	A	A	B	C	D	D	A		A		A
Hydrochloric acid, aqueous solution	HCl+H <sub>2</sub> O	38	60					D	D	D		D	D	D			B	A	A	A	D	D	D			A		A	
Hydrochloric acid, aqueous solution	HCl+H <sub>2</sub> O	38	80					D	D	B		D	D	D			B	B	A	B	D	D	D			A		A	
Hydrocyanic acid (Prussic acid), gas	HCN	100	20	0.690		81	D	A	D	C	A	A		A	A	A	A	A	A	B	B	B	A		c	A		A	
Hydrofluoric acid	HF+H <sub>2</sub> O	10	25	1.030		2.2	D	D	D	D	B	B		D															
Hydrofluoric acid	HF+H <sub>2</sub> O	30	20				D	D	D	D	B	B		D	C	A	A	A	A	A	A	D	C						
Hydrofluoric acid	HF+H <sub>2</sub> O	30	40				D	D	D	D	B	B		D	C	B	B	A	A	A	A	A	D	C					
Hydrofluoric acid	HF+H <sub>2</sub> O	30	60				D	D	D	D	B	B		D	C	C	B	A	A	A	A	D	C						
Hydrofluoric acid	HF+H <sub>2</sub> O	30	80				D	D	D	D	B	B		D	C	D	B	A	A	A	B	D	C						
Hydrofluoric acid	HF+H <sub>2</sub> O	38	20	1.125			D	D	D	D	B	B		D	C	B	A	A	A	A	A	D	C						
Hydrofluoric acid	HF+H <sub>2</sub> O	40	20	1.060		1	D	D	D	D	B	B		D	C	B	A	A	A	A	A	D	C						
Hydrofluoric acid	HF+H <sub>2</sub> O	40	40				D	D	D	D	B	B		D	C	C	B	A	A	A	B	D	C						
Hydrofluoric acid	HF+H <sub>2</sub> O	40	60				D	D	D	D	B	B		D	C	D	B	A	A	A	C	D	C						
Hydrofluoric acid	HF+H <sub>2</sub> O	40	80				D	D	D	D	B	B		D	C	D	B	A	A	A	A	D	C						
Hydrofluoric acid	HF+H <sub>2</sub> O	50	20				D	D	D	D	B	B		D	C	B	A	A	A	A	A	D	C		D				
Hydrofluoric acid	HF+H <sub>2</sub> O	50	40				D	D	D	D	B	B		D	C	D	B	A	A	A	A	D	C						
Hydrofluoric acid	HF+H <sub>2</sub> O	50	60				D	D	D	D	B	B		D	C	D	B	A	A	A	B	D	C						




Liquid	Chemical Formula	Concentration %	Temp, degree C	Specific gravity kg/dm3	Viscosity cSt	Vapour pressure kPa	Bronze	Aluminium	Cast iron	Ductile iron	Hastelloy B	Hastelloy C	Stainless Steel SIS 2333	Stainless Steel SIS 2343	EP - Epoxy	CPVC	PP	PVDF	PTFE	FPM - Viton	EPDM - EPT	NBR - Nitrile	CR - Neoprene	Kairez	Hytrek	Carbon	Silicon	Ceramic	
Hydrofluoric acid	HF+H <sub>2</sub> O	50	80				D	D	D	D	B	B		D	C	D	B	A	A	A	C	D	C						
Hydrofluoric acid	HF+H <sub>2</sub> O	70	20	1.230			D	D	D	D	B	B		D	C	A	A	A	A	A	C	D	D	A					
Hydrofluoric acid	HF+H <sub>2</sub> O	75	20	0.990			D	D	D	D	B	B		D	C	A	A	A	A	A	C	D	D		D				
Hydrofluoric acid	HF+H <sub>2</sub> O	75	25	1.240			D	D	D	D	B	B		D	C	A	A	A	A	A	C	D	D						
Hydrofluoric acid	HF+H <sub>2</sub> O	100	25	0.990			D	D	D	D	B	B		D															
Hydrofluoric acid, dilute	HF	100	20												A	A	A	A	A	A	A	D							
Hydrofluoric acid, dilute	HF	100	40												A	B	B	A	A	A	A	D							
Hydrofluoric acid, dilute	HF	100	80												A	C	B	A	A	A	A	D							
Hydrofluosilicic acid	H <sub>2</sub> SiF <sub>6</sub>	10	20				A	D	D		B	B		D	A	A	A	A	A	A	A	A	C						
Hydrofluosilicic acid	H <sub>2</sub> SiF <sub>6</sub>	20	20				A	D	D		B	B		D	A	A	A	A	A	A	A	A	C						
Hydrofluosilicic acid	H <sub>2</sub> SiF <sub>6</sub>	32	20	1.170			A	D	D		B	B		D	A	A	A	A	A	A		D	C			A		A	
Hydrogen	H <sub>2</sub>	100	20	0.070			A	A		B				A		A	A	A	A	A	A	A	A						
Hydrogen chloride, anhydrous	HCl	100	20	0.910		4400																							
Hydrogen fluoride, anhydrous	HF	100	20	0.970											A			A	A	D	B	D							
Hydrogen peroxide	H <sub>2</sub> O <sub>2</sub>	3	20	1.010			D	A	D			D			A	D	A	A	A	A		D	D			D		A	
Hydrogen peroxide	H <sub>2</sub> O <sub>2</sub>	5	20				D	A	D			D			A	D	A	A	A	A	A	D	D			D		A	
Hydrogen peroxide	H <sub>2</sub> O <sub>2</sub>	5	40				D	A	D			D			A	D	B	A	A	A	c	D	D			D		A	
Hydrogen peroxide	H <sub>2</sub> O <sub>2</sub>	10	20	1.040			D	A	D			D			A		A	A	A	A		D	D			D		A	
Hydrogen peroxide	H <sub>2</sub> O <sub>2</sub>	20	20	1.070			D	A	D			D			A		A	A	A	A		D	D			D		A	
Hydrogen peroxide	H <sub>2</sub> O <sub>2</sub>	30	20	1.100		3.2	D	A	D			D			A		A	A	A	A		D	D			D		A	
Hydrogen peroxide	H <sub>2</sub> O <sub>2</sub>	35	20	1.130																							D		A
Hydrogen peroxide	H <sub>2</sub> O <sub>2</sub>	50	20	1.200		0.1	D	A	D						A	D	C	A	A	A	c	D	D			D		A	
Hydrogen peroxide	H <sub>2</sub> O <sub>2</sub>	50	40				D	A	D						A	D	D	A	A	B		D	D			D		A	
Hydrogen peroxide	H <sub>2</sub> O <sub>2</sub>	90	20	1.400		0.67	D	A	D			D			A	D	D	A	A	A	D	D	D			D		A	
Hydrogen peroxide	H <sub>2</sub> O <sub>2</sub>	100	20	1.442		0.3	D	A	D			D															D		A
Hydrogen sulphide, aqueous	H <sub>2</sub> S	100	20	0.960		1760	D	A	D	C		A		A	A	A	A	A	A	A	A	A	D		A	A		A	
Hydrogen sulphide, aqueous	H <sub>2</sub> S	100	60				D	A	D	C					A	A	A	A	A	B	A	A	D		A	A			
Hydrogen sulphide, aqueous	H <sub>2</sub> S	100	20	0.960		1760	D		D						A	A	A	A	A	A	A	A	D		A				
Hydrogen sulphide, aqueous	H <sub>2</sub> S	100	60				D		D						A	A	A	A	A	B	A	A	D		A				
Hydrogen sulphide, dry	H <sub>2</sub> S	100	20	0.960		1760	D	A	D	c		A		A	A	A	A	A	A	A	A	A	D	A		A		A	
Hydrogen sulphide, dry	H <sub>2</sub> S	100	80				D		D	c					A	A	A	A	A	A	B	B	D	A		A			
Hydrogen sulphide, dry	H <sub>2</sub> S	100	20			1760	D		D						A	A	A	A	A	A	A	A	D	A					
Hydrogen sulphide, dry	H <sub>2</sub> S	100	80				D		D						A	A	A	A	A	A	B	B	D	A					
Hydroquinone, saturated	C <sub>6</sub> H <sub>4</sub> (OH) <sub>2</sub>	100	20				D	A	D						A	A	A	A	A	A	A	A	A						
Hydrosulphite (Sodium dithionite)	Na <sub>2</sub> S <sub>2</sub> O <sub>4</sub>	10	20					D							A			A	A	A	A	D					A		
Hydrosulphite (Sodium dithionite)	Na <sub>2</sub> S <sub>2</sub> O <sub>4</sub>	10	40					D							A			A	A	A		D							











Liquid	Chemical Formula	Concentration %	Temp, degree C	Specific gravity kg/dm3	Viscosity cSt	Vapour pressure kPa	Bronze	Aluminium	Cast iron	Ductile iron	Hastelloy B	Hastelloy C	Stainless Steel SIS 2333	Stainless Steel SIS 2343	EP - Epoxy	CPVC	PP	PVDF	PTFE	FPM - Viton	EPDM - EPT	NBR - Nitrile	CR - Neoprene	Kairez	Hytrel	Carbon	Silicon	Ceramic	
Lithium sulphate	LiSO4	25	20	1.230				A						A			A	A	A									A	
Lithophone	ZnS, BaSO4	100	20					A						A			A	A	A									A	
Liver paste		100	20											A	A								A	A					
Lubricating oil (ASTM 1)		100	20				A	A	A	A				A	A	A	A	A	A	A	D	A	D		A				
Lubricating oil (ASTM 2)		100	20				A	A	A	A				A	A	A	A	A	A	A	D	A	D		A				
Lubricating oil (ASTM 3)		100	20				A	A	A	A				A	A	A	A	A	A	A	D	A	D		A				
Lubricating oil (ASTM 3)		100	40				A	A	A	A				A	A	A		A	A	A	D	B	D		A				
Lubricating oil (ASTM 3)		100	80				A	A	A	A				A	A	A		A	A	B	D	D	D		A				
Machine oil		100	20														A	A	A	A	D	A							
Machine oil		100	60														B	A	A	A	D	B							
Magnesium bisulphite	Mg(HSO3)2	100	20					D									A	A	A								A		A
Magnesium carbonate	MgCO3	100	20	2.960				A			B	B		A	A	A	A	A	A	A	A	A	A		A	A			A
Magnesium carbonate	MgCO3	100	80					A			B	B		A	A	B	A	A	A	A	A	B	A		A				
Magnesium chloride, saturated	MgCl2+6H2O	10	20	1.080		2.2	C	B	D	D	A	A		A	A	A	A	A	A	A	A	A	A		A	A			A
Magnesium chloride, saturated	MgCl2+6H2O	15	20	1.130		2.2	C	B	D	D	A	A		A	A	A	A	A	A	A	A	A	A		A	A			A
Magnesium chloride, saturated	MgCl2+6H2O	25	20	1.150		2.2	C	B	D	D	A	A		A	A	A	A	A	A	A	A	A	A		A	A			A
Magnesium chloride, saturated	MgCl2+6H2O	30	20	1.280		2.2	C	B	D	D	A	A		A	A	A	A	A	A	A	A	A	A		A	A			A
Magnesium chloride, saturated	MgCl2+6H2O	100	20	2.320			C	B	D	D	A	A		A	A	A	A	A	A	A	A	A	A		A	A			A
Magnesium citrate		100	20														A	A	A	A	A	A	A						
Magnesium citrate		100	80														A	A	A	A	A	A	B						
Magnesium fluoride	MgF2	100	20					A						D			A	A	A								A		A
Magnesium hydroxide, saturated	Mg(OH)2	100	20				A	B	A					A	A	A	A	A	A	A	A	A	A		A				
Magnesium hydroxide, saturated	Mg(OH)2	100	80				A	B	A					A	A	A	A	A	A	A	A	B	A		A				
Magnesium nitrate	Mg(NO3)2+6H2O	25	20	1.210			D	A	D			A		A	A	A	A	A	A	A	A	A	A				A		A
Magnesium nitrate	Mg(NO3)2+6H2O	100	20	1.460			D		D					A	A	A	A	A	A	A	A	A	A						
Magnesium nitrate	Mg(NO3)2+6H2O	100	80				D		D					A	A	B	B	A	A	A	A	B	A						
Magnesium oxide	MgO	100	20				A		A					A	A					C		A	A						
Magnesium perchlorate	Mg(ClO4)2+H2O	100	25	2.600																									
Magnesium salt (Epsom salt), saturated	MgSO4+7H2O	100	20	1.280			A				A	B		A	A	A		A	A	A	A	A	A						
Magnesium silicofluoride	MgSiF6+6H2O	100	20	1.780				A						A			A	A	A								A		
Magnesium sulfite	MgSO3	100	20					A						A			A	A	A								A		A
Magnesium sulphate	MgSO4	10	20	1.100		2.2	C	A	A	B	A	B		A	A	A	A	A	A	A	A	A	A		C				
Magnesium sulphate	MgSO4	20	20	1.300		2.2	C	A	A	B	A	B		A	A	A	A	A	A	A	A	A	A		C				
Magnesium sulphate	MgSO4	100	20	1.280			C	A	A	B	A	B		A	A	A	A	A	A	A	A	A	A		C	A			
Maleic acid	CHC02HCHC02H, (HCCOOH)2	100	20					A		C	B	A		A	A	A	A	A	A	A	A	B	D	A					
Maleic acid	CHC02HCHC02H, (HCCOOH)2	100	40					A		C	B	A		A	A	A	A	A	A	A	B	B	D	A					
Maleic acid	CHC02HCHC02H, (HCCOOH)2	100	60					A		C	B	A		A	A	A	A	A	A	B	B	D	A						




Liquid	Chemical Formula	Concentration %	Temp, degree C	Specific gravity kg/dm3	Viscosity cSt	Vapour pressure kPa	Bronze	Aluminium	Cast iron	Ductile iron	Hastelloy B	Hastelloy C	Stainless Steel SIS 2333	Stainless Steel SIS 2343	EP - Epoxy	CPVC	PP	PVDF	PTFE	FPM - Viton	EPDM - EPT	NBR - Nitrile	CR - Neoprene	Kairez	Hytrek	Carbon	Silicon	Ceramic			
Maleic acid, saturated	CHC02HCHC02H, (HCCOOH)2	50	20	1.300				A		C	B	A		A	A	A	A	A	A	A	A	A	D	A							
Maleic acid, saturated	CHC02HCHC02H, (HCCOOH)2	100	20	1.590				A		C	B	A		A	A	A	A	A	A	A	A	A	D	A		A					
Maleic acid, saturated	CHC02HCHC02H, (HCCOOH)2	100	60					A		C	B	A		A	A	A	A	A	A	B	A	A	D	A							
Maleic acid, saturated	CHC02HCHC02H, (HCCOOH)2	100	80					A		C	B	A		A	A	A	A	A	A		A	B	D	A							
Maleic anhydride	(C0CH)20	100	20	0.930				A			A	A		A	A			A	A	A	D	D	D								
Malic acid	CO <sub>2</sub> -CH <sub>2</sub> O-CH <sub>2</sub> -CO <sub>2</sub> H	50	20					A				A		A			A	A	A							A		A			
Malic acid	CO <sub>2</sub> -CH <sub>2</sub> O-CH <sub>2</sub> -CO <sub>2</sub> H	100	20					B						A		A	A	A	A	A	A	A	A								
Malic acid	CO <sub>2</sub> -CH <sub>2</sub> O-CH <sub>2</sub> -CO <sub>2</sub> H	100	60					B						A		B	A	A	A	A	A	A	A								
Manganese (II) chloride	MnCl2	10	20	1.060																											
Manganese (II) chloride	MnCl2	20	20	1.190										D			A	A	A							A		A			
Manganese (II) chloride	MnCl2	100	20	2.980																											
Manganese chloridehydrate	MnCl2+4H2O	100	20	2.010																											
Manganese nitrate	Mn(N03)2+6H2O	100	20												A					C		A	A								
Manganese sulphate	MnS04+4H2O	20	20	1.220				A		D		A		A		A	A	A	A	A	A	A				A		A			
Manganese sulphate	MnS04+4H2O	30	20	1.220				A		D		A		A		A	A	A	A	A	A	A									
Manganese sulphate	MnS04+4H2O	100	20	2.090				A		D		A		A		A	A	A	A	A	A	A									
Manganese sulphate	MnS04+4H2O	100	80					A		D		A		A		B	A	A	A	A	A	B									
Marmelade (Jam)		100	20														A	A													
Mash		100	20				A							A	A								A	A							
Mayonnaise		100	20	1	5000		D	D	D	D				A	A					A		A	A								
Meat extract		100	20	1	22000		D							A	A					A		A	A								
Melamine	C <sub>3</sub> H <sub>6</sub> N <sub>6</sub>	100	20		420-1000		D		D					D	A								C	D							
Menthol	C <sub>10</sub> H <sub>19</sub> OH	100	20	0.800				A		B		A		A			A	A	A				A								
Mercuric chloride	HgCl2	100	20	7.150			D	D	D	D		B		D	A	A	A	A	A	A	A	A	A								
Mercuric cyanide, saturated	Hg(CN)2	100	20				D	D		D				A	A	A	A	A	A	A	A	A									
Mercuric nitrate	Hg(N03)2	100	20					D						A			A	A	A	A	A	A				A					
Mercuric salts		100	20														A	A	A	A	A	D				A					
Mercuric sulphate, saturated	Hg2S04	100	20													A	A	A	A	A	A	A									
Mercury	Hg	100	20	13.60			D	D	A	A	B	A		A	A	A	A	A	A	A	A	A	A		A	A		A			
Mesityl oxide (Isopropylidene acetone)	(CH3)2CCHCOCH3, C6H10O	100	20	0.850		1.1		A						A							D	B	D	D							
Meta cresol	CH3C6H4OH	100	20	1.030																											
Methane	CH4	100	20					A						A				A	A	A	A	A	B		C						
Methane sulphonic acid	CH <sub>3</sub> SO <sub>2</sub> OH	50	20															A	A												
Methanol (Methyl alcohol), pure	CH <sub>3</sub> OH	100	20	0.790	0.8	12.8	A	A	A	B	A	A		A	A	A	A	A	A	B	A	B	A	A	A	A		A		A	
Methanol (Methyl alcohol), pure	CH <sub>3</sub> OH	100	40				A	A	A	B	A	A		A	A	B	A	A	A	B	A	C	A	A	A						
Methanol (Methyl alcohol), pure	CH <sub>3</sub> OH	100	60				A	A	A	B	A	A		A	A	B	A	A	A	C	A	D	A			A					
Methanol (Methyl alcohol), pure	CH <sub>3</sub> OH	100	80				A	A	A	B	A	A		A	A		B	A	A	C	B	D	A		A						
Methyl acetate, pure	CH <sub>3</sub> CO <sub>2</sub> CH <sub>3</sub>	100	20	0.930				B		B	B	A		A		D	B	A	A	D	B	D	D		C	A					



Liquid	Chemical Formula	Concentration %	Temp, degree C	Specific gravity kg/dm3	Viscosity cSt	Vapour pressure kPa	Bronze	Aluminium	Cast iron	Ductile iron	Hastelloy B	Hastelloy C	Stainless Steel SIS 2333	Stainless Steel SIS 2343	EP - Epoxy	CPVC	PP	PVDF	PTFE	FPM - Viton	EPDM - EPT	NBR - Nitrile	CR - Neoprene	Kairez	Hytrel	Carbon	Silicon	Ceramic
Methyl acetate, pure	CH <sub>3</sub> CO <sub>2</sub> CH <sub>3</sub>	100	40					B		B	B	A		A		D		B	A	D	C	D	D		C			
Methyl acetate, pure	CH <sub>3</sub> CO <sub>2</sub> CH <sub>3</sub>	100	60					B		B	B	A		A		D		C	A	D		D	D		C			
Methyl acetate, pure	CH <sub>3</sub> CO <sub>2</sub> CH <sub>3</sub>	100	80					B		B	B	A		A		D		D	A	D		D	D		C			
Methyl acetoacetate	CH <sub>3</sub> COCH <sub>2</sub> COOCH <sub>3</sub>	100	20	1.080																								
Methyl acetone		100	20				B							A	C								D	D				
Methyl acrylate, pure	CHCHOOCH <sub>3</sub> , CH <sub>2</sub> =CHCO <sub>2</sub> CH <sub>3</sub>	100	20	0.950		9.3		B						A	A			A	A	D	B	D	D					
Methyl acrylate, pure	CHCHOOCH <sub>3</sub> , CH <sub>2</sub> =CHCO <sub>2</sub> CH <sub>3</sub>	100	40					B						A	A			B	A	D		D	D					
Methyl acrylate, pure	CHCHOOCH <sub>3</sub> , CH <sub>2</sub> =CHCO <sub>2</sub> CH <sub>3</sub>	100	60					B						A	A			C	A	D		D	D					
Methyl acrylate, pure	CHCHOOCH <sub>3</sub> , CH <sub>2</sub> =CHCO <sub>2</sub> CH <sub>3</sub>	100	80					B						A	A			D	A	D		D	D					
Methyl acrylic acid	CH <sub>2</sub> =C(CH <sub>3</sub> )COOH, C <sub>4</sub> H <sub>6</sub> O <sub>2</sub>	100	20	1.020		0.13														B	C		B					
Methyl amine	CH <sub>3</sub> NH <sub>2</sub> +H <sub>2</sub> O	32	20	0.700				A						A	A		A	D	A			D				A		
Methyl amine	CH <sub>3</sub> NH <sub>2</sub> +H <sub>2</sub> O	40	25	0.890		40																						
Methyl amine	CH <sub>3</sub> NH <sub>2</sub>	100	20	0.660		253	D							A	A	D	D	C	A		A	C						
Methyl amine	CH <sub>3</sub> NH <sub>2</sub>	100	40				D							A	A	D	D	D	A									
Methyl aniline	C <sub>7</sub> H <sub>9</sub> N, C <sub>6</sub> H <sub>4</sub> (CH <sub>3</sub> )NH <sub>2</sub>	100	20	1.000																A	D	D	D				A	
Methyl bromide	CH <sub>3</sub> Br	100	20	1.730		189		D				A		A	B		D	A	A	A	B	D	D	A		A		
Methyl butyl ketone	CH <sub>3</sub> CO(CH <sub>2</sub> ) <sub>3</sub> CH <sub>3</sub>	100	20								B			A	B					D	A	D	D					
Methyl cellosolve	CH <sub>3</sub> OCH <sub>2</sub> CH <sub>2</sub> OH	100	20	0.970		1.07	A	B						B	C			A	A	D	B	D	D					
Methyl cellulose		100	20				A								C					D	B	D	D					
Methyl chloride	CH <sub>3</sub> Cl	100	20	0.921	11	500	B	D	A	B	B			A	A	D	C	A	A	D	B	D	D	A	D			
Methyl chloride	CH <sub>3</sub> Cl	100	25	1.790			B	D	A	B	B			A	A	D	C	A	A	D	B	D	D	A	D			
Methyl chloroform (1,1,1-Trichloroethane)	CH <sub>3</sub> CCl <sub>3</sub>	100	20	1.340		13.3	A		A					A	A			A	A	B	D	D						
Methyl chloroformate	CH <sub>3</sub> OCCl	100	20	1.220		13.7																						
Methyl cyclohexanol	C <sub>7</sub> H <sub>13</sub> OH	100	20	0.920																								
Methyl cyklopentane	C <sub>6</sub> H <sub>12</sub>	100	20											A	A		A	A	A	A	D	D	D	A				
Methyl dichloride		100	20												A					A	D	D	D					
Methyl ether	C <sub>2</sub> H <sub>6</sub> O	100	20	0.670		510														D	D	B	A					
Methyl ethyl carbinol	CH <sub>3</sub> CH <sub>2</sub> CH(OH)CH <sub>3</sub>	100	20	0.810		1.7																						
Methyl ethyl ketone	CH <sub>3</sub> COCH <sub>2</sub> CH <sub>3</sub> , CH <sub>3</sub> COC <sub>2</sub> H <sub>5</sub>	100	20	0.805	0.5	9.4	A	B			B			A	A	D	B	D	A	D	B	D	D	A	C	A		
Methyl ethyl ketone	CH <sub>3</sub> COCH <sub>2</sub> CH <sub>3</sub> , CH <sub>3</sub> COC <sub>2</sub> H <sub>5</sub>	100	40				A	B			B			A	A	D	C	D	A	D	C	D	D	A	C			
Methyl ethyl ketone	CH <sub>3</sub> COCH <sub>2</sub> CH <sub>3</sub> , CH <sub>3</sub> COC <sub>2</sub> H <sub>5</sub>	100	60				A	B			B			A	A	D	D	D	A	D		D	D		C			
Methyl fenylendiisocyanate	CH <sub>3</sub> C <sub>6</sub> H <sub>3</sub> (NCO) <sub>2</sub>	100	20	1.220	5	0																						
Methyl formate	HCO <sub>2</sub> CH <sub>3</sub>	100	20	0.970		63.9		A						B					A	D	A	D	B					
Methyl glycol	C <sub>3</sub> H <sub>8</sub> O <sub>2</sub> , (CH <sub>2</sub> ) <sub>2</sub> OHCH <sub>2</sub> OH	100	20	0.970		1.07											A	A	A	A	A	A	A	A		A		
Methyl isobutyl carbinol	CH <sub>3</sub> CHOHCH <sub>2</sub> CH(CH <sub>3</sub> ) <sub>2</sub>	100	20	0.810		0.7													A	A	A	A	A					
Methyl isobutyl ketone	(CH <sub>3</sub> ) <sub>2</sub> CHCH <sub>2</sub> COCH <sub>3</sub>	100	20	0.800		0.8	A	A						A	A		D	A	A	D	B	D	D		D			
Methyl isobutyl ketone	(CH <sub>3</sub> ) <sub>2</sub> CHCH <sub>2</sub> COCH <sub>3</sub>	100	40					A						A	A		D	B	A	D		D	D		D			
Methyl isobutyl ketone	(CH <sub>3</sub> ) <sub>2</sub> CHCH <sub>2</sub> COCH <sub>3</sub>	100	60					A						A	A		D	C	A	D		D	D		D			

Liquid	Chemical Formula	Concentration %	Temp, degree C	Specific gravity kg/dm3	Viscosity cSt	Vapour pressure kPa	Bronze	Aluminium	Cast iron	Ductile iron	Hastelloy B	Hastelloy C	Stainless Steel SIS 2333	Stainless Steel SIS 2343	EP - Epoxy	CPVC	PP	PVDF	PTFE	FPM - Viton	EPDM - EPT	NBR - Nitrile	CR - Neoprene	Kairez	Hytel	Carbon	Silicon	Ceramic		
Methyl isobutyl ketone	(CH <sub>3</sub> ) <sub>2</sub> CHCH <sub>2</sub> COCH <sub>3</sub>	100	80					A						A	A		D	D	A	D		D	D		D					
Methyl isopropyl ketone	CH <sub>3</sub> CNOHCH(CH <sub>3</sub> ) <sub>2</sub>	100	20											A	A			A	A	D	D	D	D		D					
Methyl isopropyl ketone	CH <sub>3</sub> CNOHCH(CH <sub>3</sub> ) <sub>2</sub>	100	40											A	A			B	A	D	D	D	D		D					
Methyl isopropyl ketone	CH <sub>3</sub> CNOHCH(CH <sub>3</sub> ) <sub>2</sub>	100	60											A	A			C	A	D	D	D	D		D					
Methyl isopropyl ketone	CH <sub>3</sub> CNOHCH(CH <sub>3</sub> ) <sub>2</sub>	100	80											A	A			D	A	D	D	D	D		D					
Methyl mercaptan	CH <sub>3</sub> SH	100	20	0.870		167																								
Methyl methacrylate	CH <sub>2</sub> =C(CH <sub>3</sub> )COOCH <sub>3</sub>	100	20	0.940		3.9		B						B	A		C	A	A	D	D	D	C							
Methyl methacrylate	CH <sub>2</sub> =C(CH <sub>3</sub> )COOCH <sub>3</sub>	100	40					B						B	A		C	B	A	D	D	D	c							
Methyl methacrylate	CH <sub>2</sub> =C(CH <sub>3</sub> )COOCH <sub>3</sub>	100	60					B						B	A		C	C	A	D	D	D	c							
Methyl methacrylate	CH <sub>2</sub> =C(CH <sub>3</sub> )COOCH <sub>3</sub>	100	80					B						B	A		C	D	A	D	D	D	c							
Methyl oleate		100	20																	A	C	D	D							
Methyl parathion	(CH <sub>3</sub> ) <sub>2</sub> P(S)OC <sub>6</sub> H <sub>4</sub> N <sub>2</sub> O <sub>2</sub>	100	20																											
Methyl propane	(CH <sub>3</sub> ) <sub>3</sub> CH	100	20			202																								
Methyl salicylate	C <sub>8</sub> H <sub>8</sub> O <sub>3</sub>	100	20	1.185				A													C		D							
Methyl sulfoxide		100	20															D	A											
Methyl sulphate	(CH <sub>3</sub> ) <sub>2</sub> SO <sub>2</sub>	100	20	1.330																										
Methyl sulphide	(CH <sub>3</sub> ) <sub>2</sub> S	100	20	0.850		53																								
Methylene bromide	CH <sub>2</sub> Br <sub>2</sub>	100	20						A					A	A			A	A	A	D	D	D							
Methylene chloride (Dichloromethane)	CH <sub>2</sub> Cl <sub>2</sub>	100	20	1.330	1	44.7		A	A	B	A	A		A	A	D	D	B	A	C	D	D	D	A	D	A				
Methylene dichloride	CH <sub>2</sub> Cl <sub>2</sub>	100	20	1.330		44.7								A	A				A	B	D	D			D					
Methylene iodine	CH <sub>2</sub> I <sub>2</sub>	100	20															A	A	A										
Milk		100	20	1.040	2		C	A	D	D				A	A	A	A	A	A	A	A	A	A	A	C	A				
Mineral oil		100	20				A	A	A	B				A	A	A	A	A	A	A	D	A	B		A	A				
Mineral oil		100	40				A	A	A	B				A	A	A	B	A	A		D		B		A					
Mineral oil		100	60				A	A	A	B				A	A	A	C	A	A		D		B		A					
Mineral oil, free of aromatic compounds		100	20																											
Mineral water		100	20														A	A	A	A		A								
Molasses		100	20	1.4	2600		D	A	A		A			A	A	A	A	A	A	A		A	A			A				
Molasses wort		100	20														A	A	A			A								
Monoamylamine	CH <sub>3</sub> (CH <sub>2</sub> ) <sub>4</sub> NH <sub>2</sub>	100	20	0.760																										
Monobromobenzene		100	20																											
Monobutylamine	(CH <sub>3</sub> ) <sub>2</sub> CHCH <sub>2</sub> NH <sub>2</sub>	100	20	0.730		13																								
Monobutylamine	CH <sub>3</sub> (CH <sub>2</sub> ) <sub>3</sub> NH <sub>2</sub> , C <sub>4</sub> H <sub>9</sub> NH <sub>2</sub>	100	20	0.730		9																								
Monobutylamine	CH <sub>3</sub> CH(NH <sub>2</sub> )C <sub>2</sub> H <sub>5</sub>	100	20	0.720		13																								
Monobutylamine	C(CH <sub>3</sub> ) <sub>3</sub> NH <sub>2</sub>	100	20	0.700		13																								
Monochloroacetic acid	CH <sub>2</sub> ClCO <sub>2</sub> H	50	20				D	D	D			A		D	C	A	B	A	A	B	C	D	D	A						
Monochloroacetic acid	CH <sub>2</sub> ClCO <sub>2</sub> H	50	40				D	D	D			A		D	C	B	B	A	A	D		D	D	A						
Monochloroacetic acid	CH <sub>2</sub> ClCO <sub>2</sub> H	50	60				D	D	D			A		D	C	B	D	B	A	D		D	D							



Liquid	Chemical Formula	Concentration %	Temp, degree C	Specific gravity kg/dm3	Viscosity cSt	Vapour pressure kPa	Bronze	Aluminium	Cast iron	Ductile iron	Hastelloy B	Hastelloy C	Stainless Steel SIS 2333	Stainless Steel SIS 2343	EP - Epoxy	CPVC	PP	PVDF	PTFE	FPM - Viton	EPDM - EPT	NBR - Nitrile	CR - Neoprene	Kairez	Hytrek	Carbon	Silicon	Ceramic			
Monochloroacetic acid	CH <sub>2</sub> ClCO <sub>2</sub> H	100	20	1.580			D	D	D			A		D	D	A	A	A	A	D	B	D	D								
Monochloroacetic acid ethyl ester	ClCH <sub>2</sub> COOC <sub>2</sub> H <sub>5</sub>	100	20					D									A	A	A	A		D									
Monochloroacetic acid methyl ester	ClCH <sub>2</sub> COOCH <sub>3</sub>	100	20														A	A	A	A		D									
Monochlorobenzene (Chlorobenzene)	C <sub>6</sub> H <sub>5</sub> Cl	100	20	1.110		1.20	A	A	D		B	A		A	A	D	B	A	A	A	D	D	D				A				
Monochlorobenzene (Chlorobenzene)	C <sub>6</sub> H <sub>5</sub> Cl	100	40				A	A	D		B	A		A	A	D	C	A	A		D	D	D								
Monochlorobenzene (Chlorobenzene)	C <sub>6</sub> H <sub>5</sub> Cl	100	60				A	A	D		B	A		A	A	D		B	A		D	D	D								
Monochlorobenzene (Chlorobenzene)	C <sub>6</sub> H <sub>5</sub> Cl	100	80				A	A	D		B	A		A	A	D		C	A		D	D	D								
Monochlorobenzol	C <sub>6</sub> H <sub>5</sub> Cl	100	20	1.110		1.20	A	A	D		B	A		A	A	D	B	A	A	A	D	D	D				A				
Monochlorophenol	C <sub>6</sub> H <sub>4</sub> OHCl	100	20	1.300																											
Monoethanolamine	NH <sub>2</sub> CH <sub>2</sub> CH <sub>2</sub> OH	100	20	1.020				A						A	A	D	A	D	A	D	A	A	B								
Monoisopropanolamine	H <sub>2</sub> NCH <sub>2</sub> CH(CH <sub>3</sub> )OH	100	20	0.960		0.20																									
Monomethyl ether	(CH <sub>3</sub> ) <sub>2</sub> O, C <sub>3</sub> H <sub>8</sub> O	100	20	0.670		510									A						A	A	A	A							
Monomethylamine	CH <sub>3</sub> NH <sub>2</sub>	100	20	0.660		250																									
Monomethylaniline	C <sub>7</sub> H <sub>9</sub> N	100	20																		A	D	D	D							
Monomethylethanolamine	H <sub>3</sub> CNHCH <sub>2</sub> CH <sub>2</sub> OH	100	20	0.940		0.09																									
Morpholine	NH(C <sub>2</sub> H <sub>4</sub> ) <sub>2</sub> O, OCH <sub>2</sub> CH <sub>2</sub> NHCH <sub>2</sub> CH <sub>2</sub>	100	20	1.000	5	1.07		A				A		A			A	A	A	A		D					A				
Motor oil		100	20	0.900			A	A						A	A					A	A	A	D	A	D						
Movvilit D		100	20																												
Mustard		100	20				D	B	D	B				A	A	A	A				B		B	C							
Mustard gas	(CH <sub>2</sub> Cl-CH <sub>2</sub> ) <sub>2</sub> S	100	20																	A			A								
Myrtle oil		100	20											A	A						A										
Naphta	C <sub>n</sub> H <sub>2n+2</sub>	100	20	0.8	1.25		B	A	A		B	B		A	A	A	A	A	A	A	D	C	D		A						
Naphta	C <sub>n</sub> H <sub>2n+2</sub>	100	40				B	A	A		B	B		A	A	A	B	A	A		D		D		A						
Naphta	C <sub>n</sub> H <sub>2n+2</sub>	100	60				B	A	A		B	B		A	A	A	C	A	A		D		D		A						
Naphta	C <sub>n</sub> H <sub>2n+2</sub>	100	80				B	A	A		B	B		A	A	A		B	A		D		D		A						
Naphtalene	C <sub>10</sub> H <sub>8</sub>	100	20	1.140	0.7	0.007	C	A	A	B		A		A	A	D	B	A	A	A	D	D	D		C	A					
Naphtalene	C <sub>10</sub> H <sub>8</sub>	100	20	1.140			C	A	A	B		A		A	A	D	B	A	A	A	D	D	D		C	A					
Naphtalene, pure	C <sub>10</sub> H <sub>8</sub>	100	20	1.150			C	A	A	B		A		A	A	D	B	A	A	A	D	D	D		C	A					
Naphtalenesulphonic acid	C <sub>10</sub> H <sub>7</sub> SO <sub>3</sub> H	10	20	1.030				A						A			A														
Naphtalenesulphonic acid	C <sub>10</sub> H <sub>7</sub> SO <sub>3</sub> H	100	20	1.450				A						A			A										A				
Napthenic acid		100	20					B						A						A	A	D	B								
Natural gas		100	20					A		B				A					A	A	A	D	A	A							
Neatsfoot oil		100	20					A						A							A	C	A								
Neville-vvinther acid		100	20																		A	C	C	C							
Nickel acetate		100	20																	A	C	A	A	B							
Nickel carbonyle	Ni(CO) <sub>4</sub>	100	25	1.318		53.3																									
Nickel chloride	NiCl <sub>2</sub>	20	20	1.220			D	D	D	D	A	A		A	A	A	A	A	A	A	A	A	C		D	A					
Nickel chloride, saturated	NiCl <sub>2</sub>	100	20				D	D	D	D	A	A		C	A	A	A	A	A	A	A	A	C		D						


Liquid	Chemical Formula	Concentration %	Temp, degree C	Specific gravity kg/dm3	Viscosity cSt	Vapour pressure kPa	Bronze	Aluminium	Cast iron	Ductile iron	Hastelloy B	Hastelloy C	Stainless Steel SIS 2333	Stainless Steel SIS 2343	EP - Epoxy	CPVC	PP	PVDF	PTFE	FPM - Viton	EPDM - EPT	NBR - Nitrile	CR - Neoprene	Kairez	Hytrek	Carbon	Silicon	Ceramic	
Nickel nitrate	Ni(NO3)2, Ni(NO3)2+6H2O	10	20	1.050				D		D				A				A	A	A	A	A							
Nickel nitrate	Ni(NO3)2, Ni(NO3)2+6H2O	35	20	1.380				D		D		A		A			A	A	A	A	A	A				A			
Nickel nitrate, saturated	Ni(NO3)2, Ni(NO3)2+6H2O	100	20	2.050				D		D								A	A	A	A	A							
Nickel nitrate, saturated	Ni(NO3)2, Ni(NO3)2+6H2O	100	80					D		D								A	A	A	A	B							
Nickel salts		100	20																										
Nickel sulphate, saturated	NiSO4, NiSO4+7H2O	10	25	1.060			C	D	D			B	B	A	A	A	A	A	A	A	A	A	C						
Nickel sulphate, saturated	NiSO4, NiSO4+7H2O	100	20	1.950			C	D	D			B	B	A	A	A	A	A	A	A	A	A	c			A			
Nickel sulphate, saturated	NiSO4, NiSO4+7H2O	100	80				C	D	D			B	B	A	B	B	A	A	A	A	A	A	c						
Nickel, plating solution		100	20								A	A			A	A	A	A	A	A	A	A							
Nicotine	C10H14N2	100	20															A	A										
Nicotine	C10H14N2	100	40															B	A										
Nicotinic acid	C6H5NO2	100	20					A		C				A				A	A	B	A	D	D						
Nitroaniline	C6H4NO2NH2	100	20	1.140								A							A							A			
Nitric acid	HNO3	5	20	1.030			D	D	D	D	D	A		A	A	A	A	A	A	A	A	D	D		D				
Nitric acid	HNO3	6,3	20																						D				
Nitric acid	HNO3	10	20	1.050	5		D	D	D	D	D	A		A	A	A	A	A	A	A	A	D	D		D	A		A	
Nitric acid	HNO3	10	60				D	D	D	D	D	A		A	A	A	A	A	A	A	B	D	D		D				
Nitric acid	HNO3	10	80				D	D	D	D	D	A		A	A	A	A	A	A	A	D	D	D		D				
Nitric acid	HNO3	20	20	1.120		2	D		D	D	D	A		A	B	A	D	A	A	A	D	D	D		D				
Nitric acid	HNO3	30	20	1.180			D	D	D	D	D	A		A		A	D	A	A	A	B	D	D		D	A		A	
Nitric acid	HNO3	30	60				D	D	D	D	D	A		A		B	B	A	A	B	D	D	D		D				
Nitric acid	HNO3	30	80				D	D	D	D	D	A		A		B	B	A	A	C	D	D	D		D				
Nitric acid	HNO3	40	20	1.250		1.5	D	D	D	D	D	A		A	C	A	D	A	A	A	D	D	D		D				
Nitric acid	HNO3	50	20	1.310			D	D	D	D	D	A		A	C	A	D	A	A	A	D	D	D		D	D		A	
Nitric acid	HNO3	50	40				D	D	D	D	D	A		A	C	B	A	A	A	B	D	D	D		D				
Nitric acid	HNO3	50	60				D	D	D	D	D	A		A	C	C	B	A	A	C	D	D	D		D				
Nitric acid	HNO3	50	80				D	D	D	D	D			A	C	C	D	B	A	D	D	D	D		D				
Nitric acid	HNO3	65	20	1.480	5		D	C	D	D	D	B		A	D	D	D	A	A	A	D	D	D		D				
Nitric acid	HNO3	70	20	1.410			D	D	D	D	D	A		A	D	B	C	A	A	C	D	D	D	A	D			A	
Nitric acid	HNO3	70	40				D	D	D	D	D			A	D	B	D	A	A	D	D	D	D	A	D				
Nitric acid	HNO3	70	60				D	D	D	D	D			A	D	C	D	A	A	D	D	D	D	A	D				
Nitric acid	HNO3	70	80				D	D	D	D	D			A	D	D	D	B	A	D	D	D	D	A	D				
Nitric acid	HNO3	80	20	1.452			D		D	D	D			D	C	C	A	A	C	D	D	D		D					
Nitric acid	HNO3	98	20				D	A	D	D	D			D	D	D	D	A	A	C	D	D	D	A	D				
Nitric acid	HNO3	98	40				D	A	D	D	D			D	D	D	D	B		D	D	D	A	D					
Nitric acid	HNO3	99	20	1.500			D	A	D	D	D			D	D	D	D	A	A		D	D	D		D	D			
Nitric acid	HNO3	100	20							D															D				









Liquid	Chemical Formula	Concentration %	Temp, degree C	Specific gravity kg/dm3	Viscosity cSt	Vapour pressure kPa	Bronze	Aluminium	Cast iron	Ductile iron	Hastelloy B	Hastelloy C	Stainless Steel SIS 2333	Stainless Steel SIS 2343	EP - Epoxy	CPVC	PP	PVDF	PTFE	FPM - Viton	EPDM - EPT	NBR - Nitrile	CR - Neoprene	Kairez	Hytrek	Carbon	Silicon	Ceramic	
Photogene, kerosene, paraffin		100	20	0.780	2.5	0.1	A		A	B				A	A	A	B	A	A	A	D	A	D						
Photographic developer	C <sub>6</sub> H <sub>4</sub> (OH) <sub>2</sub>	100	20				D	A	D		A	A		A	A	A	A	A	A	A	A	A	A				A		
Photographic emulsion		100	20																										
Photographic fixer	Na <sub>2</sub> S <sub>2</sub> O <sub>3</sub>	40	20	1.380										A		A	A					A							
Photographic fixer		100	20																										
Phthalic acid	C <sub>6</sub> H <sub>4</sub> (COOH) <sub>2</sub> +H <sub>2</sub> O	50	20					A								D	A	A	A	A	A	A				A		A	
Phthalic acid	C <sub>6</sub> H <sub>4</sub> (COOH) <sub>2</sub> , C <sub>6</sub> H <sub>4</sub> (CO <sub>2</sub> H) <sub>2</sub>	100	20	1.600				A								D	D	A	A	A	A	A					A		A
Phthalic anhydride	C <sub>6</sub> H <sub>4</sub> (CO <sub>2</sub> ) <sub>2</sub> O <sub>2</sub>	100	20	1.527							A							A	A							A		A	
Phthalic anhydride, powder	C <sub>6</sub> H <sub>4</sub> (CO <sub>2</sub> ) <sub>2</sub> O <sub>2</sub>	100	20	1.527							A							A	A							A		A	
Pickling solution (steel)		100	20					C						C		A	A	A	A	B	D								
Pickling solution (steel)		100	80					C						C		B	A	A	A	B	D								
Picric acid	C <sub>6</sub> H <sub>2</sub> (NO <sub>2</sub> ) <sub>3</sub> OH, HO <sub>2</sub> C <sub>6</sub> H <sub>2</sub> (NO <sub>2</sub> ) <sub>3</sub>	1	20				D	A	A	D				A	A		A	A	A	A		D				A			
Picric acid	C <sub>6</sub> H <sub>2</sub> (NO <sub>2</sub> ) <sub>3</sub> OH, HO <sub>2</sub> C <sub>6</sub> H <sub>2</sub> (NO <sub>2</sub> ) <sub>3</sub>	10	20				D		A	D				A	A	A	A	A	A	A	A	B	D						
Picric acid	C <sub>6</sub> H <sub>2</sub> (NO <sub>2</sub> ) <sub>3</sub> OH, HO <sub>2</sub> C <sub>6</sub> H <sub>2</sub> (NO <sub>2</sub> ) <sub>3</sub>	10	60				D		A	D				A	A	A	A	A	A	A	A	C	D						
Picric acid	C <sub>6</sub> H <sub>2</sub> (NO <sub>2</sub> ) <sub>3</sub> OH, HO <sub>2</sub> C <sub>6</sub> H <sub>2</sub> (NO <sub>2</sub> ) <sub>3</sub>	10	80				D		A	D				A	A	B	A		A	B	B	D	D						
Picric acid	C <sub>6</sub> H <sub>2</sub> (NO <sub>2</sub> ) <sub>3</sub> OH, HO <sub>2</sub> C <sub>6</sub> H <sub>2</sub> (NO <sub>2</sub> ) <sub>3</sub>	50	20				D	A	A	D				A	A			A		A		D				A			
Picric acid	C <sub>6</sub> H <sub>2</sub> (NO <sub>2</sub> ) <sub>3</sub> OH, HO <sub>2</sub> C <sub>6</sub> H <sub>2</sub> (NO <sub>2</sub> ) <sub>3</sub>	100	20	1.767			D	C	A	D				A	A							D							
P inene		100	20																	A	D	B	B						
Polyethylene glycol		100	20													A	A	A	A	A	A								
Polyethylene glycol		100	80													B	B	A	A	A	A								
Polyvinyl acetate	(CH <sub>2</sub> CHCOOCH <sub>3</sub> ) <sub>n</sub>	100	20				A										A	A	A	A	A	A	B						
Polyvinyl alcohol		100	20	1.2												A	A	A	A	A	A	A							
Potash	KCO <sub>3</sub>	100	20				D		C					A	A	A	A	A	A	A	A	A	D						
Potash (Potassium carbonate)	K <sub>2</sub> CO <sub>3</sub>	100	20																										
Potash alum	KAl(SO <sub>4</sub> ) <sub>2</sub>	100	20					A								A	A	A	A	A	A	A							
Potash alum	KAl(SO <sub>4</sub> ) <sub>2</sub>	100	80					A								A	A	A	A	A	A	B							
Potassium	K	100	20	0.860		0																							
Potassium acetate, saturated	CH <sub>3</sub> CO <sub>2</sub> K	100	20					D				A		A		A	A	A	A	A	A	A	B			A		A	
Potassium aluminium sulphate (Alum)	KAl(SO <sub>4</sub> ) <sub>2</sub>	50	20	1.740				A							A	A	A	A	A	A	A	A				A			
Potassium aluminium sulphate (Alum)	KAl(SO <sub>4</sub> ) <sub>2</sub>	100	20									B		A	A	A	A	A	A	A	A	A							
Potassium bicarbonate, saturated	KHCO <sub>3</sub>	100	25	2.170			D	D	A		B			B	A	A	A	A	A	A	A	A				A			
Potassium bichromate	K <sub>2</sub> Cr <sub>2</sub> O <sub>7</sub>	25	25	1.050			A	A	A		B			A	C	A	A	A	A	A	A	A							
Potassium bichromate	K <sub>2</sub> Cr <sub>2</sub> O <sub>7</sub>	40	20				A	A	A		B			A	C	A	A	A	A	A	A	A							
Potassium bichromate, saturated	K <sub>2</sub> Cr <sub>2</sub> O <sub>7</sub>	100	25	2.680			A	A	A		B			A	C	A	A	A	A	A	A	A							
Potassium bichromate, saturated	K <sub>2</sub> Cr <sub>2</sub> O <sub>7</sub>	100	80				A	A	A		B			A	C	B	B	A	A	A	A	B	A						
Potassium bifluoride	KHF <sub>2</sub> , KF+ <sub>2</sub> H <sub>2</sub> O	100	25	2.450										A			A	A											
Potassium bisulphate	KHSO <sub>4</sub>	5	25	1.035										D		A	A	A	A	A	A	A							
Potassium bisulphate	KHSO <sub>4</sub>	12	20	1.090				A						D		A	A	A	A	A	A	A							




Liquid	Chemical Formula	Concentration %	Temp, degree C	Specific gravity kg/dm3	Viscosity cSt	Vapour pressure kPa	Bronze	Aluminium	Cast iron	Ductile iron	Hastelloy B	Hastelloy C	Stainless Steel SIS 2333	Stainless Steel SIS 2343	EP - Epoxy	CPVC	PP	PVDF	PTFE	FPM - Viton	EPDM - EPT	NBR - Nitrile	CR - Neoprene	Kairez	Hytrel	Carbon	Silicon	Ceramic
Potassium bisulphate	KHSO <sub>4</sub>	100	20	2.320										D	A	A	A	A	A	A	A	A						
Potassium bisulphate	KHSO <sub>4</sub>	100	80											D	B	A	A	A	A	A	A	B						
Potassium bisulphite	KHSO <sub>3</sub>	100	20					D		D				A			A	A	A							A		
Potassium bitartrate (Tartar)	KHC <sub>4</sub> H <sub>4</sub> O <sub>6</sub>	100	20					A									A	A	A	A	A	A	A	A		A		
Potassium borate	K <sub>3</sub> BO <sub>3</sub>	10	20													A	A	A	A	A	A	A						
Potassium borate	K <sub>3</sub> BO <sub>3</sub>	100	20													A	A	A	A	A	A	A						
Potassium borohydride, powder	KBH <sub>4</sub>	100	20	1.180																								
Potassium bromate	KBrO <sub>3</sub>	100	20													A	A	A	A	A	A	A						
Potassium bromate	KBrO <sub>3</sub>	100	80													B	B	A	A	A	A	A						
Potassium bromide	KBr	100	20	1.374				A		D	A	A		B	A	A	A	A	A	A	A	A	A					
Potassium bromide	KBr	100	25	2.750				A		D	A	A		B	A	A	A	A	A	A	A	A	A					
Potassium carbonate (Potash)	K <sub>2</sub> CO <sub>3</sub>	20	25	1.190		2.2	D	D	A	B	B	B		A	A	A	A	A	A	A	A	A	A					A
Potassium carbonate (Potash)	K <sub>2</sub> CO <sub>3</sub>	100	25	2.420			D	D	A	B	B	B		A	A	A	A	A	A	A	A	A	A					A
Potassium chlorate	K <sub>2</sub> CO <sub>3</sub>	50	20					A		B				A	A	A	A	A	A	A	A	A				A		
Potassium chlorate, aqueous	K <sub>2</sub> CO <sub>3</sub>	100	25	2.320				C		B				A	A	A	A	A	A	A	A	C	A					
Potassium chlorate, aqueous	K <sub>2</sub> CO <sub>3</sub>	100	80					C		B				A	A	B	B	A	A				A					
Potassium chloride	KCl	20	20	1.130			D	D	A	B	B	B		A	A	A	A	A	A	A	A	A	A					
Potassium chloride	KCl	100	20	1.980			D	D	A	B	B	B		A	A	A	A	A	A	A	A	A	A			A		
Potassium chromate	K <sub>2</sub> CrO <sub>4</sub>	40	20				A	A	A	B	A	A		B	C	A	A	A	A	A	A	A	A			A		
Potassium chromate	K <sub>2</sub> CrO <sub>4</sub>	100	20	2.730			A	B	A	B	A	A		B	C	A	A	A	A	A	A	A	A					
Potassium chromate	K <sub>2</sub> CrO <sub>4</sub>	100	60				A	B	A	B	A	A		B	C	B	A	A	A	A	A	A	A					
Potassium chromate	K <sub>2</sub> CrO <sub>4</sub>	100	80				A	B	A	B	A	A		B	C	B	B	A	A	A	A	B	A					
Potassium chromsulphate	KCr(SO <sub>4</sub> ) <sub>2</sub> +12H <sub>2</sub> O	100	20	1.830				A						A												A		
Potassium coppercyanide		100	20													A	A	A	A	A	A	A	A					
Potassium coppercyanide		100	80													B	A	A	A	A	A	A	A					
Potassium cyanate	KOCN	100	20	2.060																								
Potassium cyanide	KCN	38	20	1.180			C	D	A		B	D		A	A	A	A	A	A	A	A	A	A					
Potassium cyanide	KCN	50	20	1.310			C	D	A		B	D		A	A	A	A	A	A	A	A	A	A			A		A
Potassium cyanide	KCN	100	20	1.520			c	D	A		B	D		A	A	A	A	A	A	A	A	A	A					
Potassium cyanide	KCN	100	80				c	D	A		B	D		A	A	B	B	A	A				A					
Potassium dichromate, saturated	K <sub>2</sub> Cr <sub>2</sub> O <sub>7</sub>	100	20				A	A	A			B		A	C	A	A	A	A	A	A	A	A			A		A
Potassium dichromate, saturated	K <sub>2</sub> Cr <sub>2</sub> O <sub>7</sub>	100	80				A	A	A			B		A	C	B	B	A	A	A	A	B	A					
Potassium ferricyanide	K <sub>3</sub> Fe(CN) <sub>6</sub>	20	20	1.110								A				A	A	A	A	A	A	A				A		A
Potassium ferricyanide	K <sub>3</sub> Fe(CN) <sub>6</sub>	50	20	1.850												A	A	A	A	A	A	A						
Potassium ferricyanide	K <sub>3</sub> Fe(CN) <sub>6</sub>	100	20													A	A	A	A	A	A	A						
Potassium ferrocyanide	K <sub>4</sub> Fe(CN) <sub>6</sub>	16	20	1.110				A				A				A	A	A	A	A	A	A				A		A
Potassium ferrocyanide	K <sub>4</sub> Fe(CN) <sub>6</sub>	50	20	1.930												A	A	A	A	A	A	A						
Potassium ferrocyanide	K <sub>4</sub> Fe(CN) <sub>6</sub>	100	20	1.850												A	A	A	A	A	A	A						




Liquid	Chemical Formula	Concentration %	Temp, degree C	Specific gravity kg/dm3	Viscosity cSt	Vapour pressure kPa	Bronze	Aluminium	Cast iron	Ductile iron	Hastelloy B	Hastelloy C	Stainless Steel SIS 2333	Stainless Steel SIS 2343	EP - Epoxy	CPVC	PP	PVDF	PTFE	FPM - Viton	EPDM - EPT	NBR - Nitrile	CR - Neoprene	Kairez	Hytrek	Carbon	Silicon	Ceramic
Potassium fluoride	KF	45	20	1.460				A				A			A	A	A	A	A	A	A	A				A	A	
Potassium fluoride	KF	100	20													A	A	A	A	A	A	A						
Potassium fluoride	KF	100	80															A	A	A	A	B						
Potassium hydrogen fluoride	KHF2	40	20					D				A		A			A	A	A							A		
Potassium hydrogen fluoride	khf2	100	20	2.370																								
Potassium hydroxide (Caustic potash)	KOH	100	20	2.044																								
Potassium hydroxide (Caustic potash)	KOH+H2O	20	20	1.190			D	D	C	B	B		B		A	A	A	A	A	D	A	B	D			A	A	
Potassium hydroxide (Caustic potash)	KOH+H2O	25	20				D	D	C	B	B	B		B	A	A	A	A	A	D	A	B	D			A	A	
Potassium hydroxide (Caustic potash)	KOH+H2O	25	60				D	D	C	B	B	B		B	A	A	A	B	A	D	A	C	D			A	A	
Potassium hydroxide (Caustic potash)	KOH+H2O	25	80				D	D	C	B	B	B		B	A	B	A	C	A	D	A	D	D			A	A	
Potassium hydroxide (Caustic potash)	KOH+H2O	30	20	1.290		2.2	D	D	C	B	B	B		B	A	A	A	A	A	D	A	B	D			A	A	
Potassium hydroxide (Caustic potash)	KOH+H2O	45	20	1.470			D	D	C	B	B	B		B	A	A	A	A	A	D	A	D	D			A	A	
Potassium hydroxide (Caustic potash)	KOH+H2O	50	25	1.510		2.2	D	D	C	B	B	B		B	A	A	A	A	A	D	A	D	D			A	A	
Potassium hydroxide (Caustic potash)	KOH+H2O	60	20	1.630			D	D	C	D	B	B		B	A	A	A	A	A	D	A	D	D			A	A	
Potassium hypochlorite	KClO	100	20	1.200	1											A	A	A	A	A	A	B						
Potassium iodate	KIO <sub>3</sub>	6	20	1.050													A	A	A							A		
Potassium iodide	KI	50	20	1.550				A		C						A	A	A	A	A	A	A				A		
Potassium iodide	KI	100	20	3.130				D		C						A	A	A	A	A	A	A						
Potassium iodide	KI	100	80					D		C						A	A	A	A	A	A	B						
Potassium monophosphate	K <sub>3</sub> PO <sub>4</sub>	100	20				C		D					A	A							A	A					
Potassium nitrate	KNO <sub>3</sub>	10	20	1.080		2.2		A		B				A	A	A	A	A	A	A	A	A	A					
Potassium nitrate	KNO <sub>3</sub>	24	20	1.170				A		B				A	A	A	A	A	A	A	A	A	A			A	A	
Potassium nitrate	KNO <sub>3</sub>	50	20					A		B				A														
Potassium nitrate	KNO <sub>3</sub>	100	20	2.106			B	A				B		B	A	A	A	A	A	A	A	A	A					
Potassium nitrate	KNO <sub>3</sub>	100	80				B	A				B		B	A		A	A	A	A	A	B	A					
Potassium nitrite	KNO <sub>2</sub>	18	20					A									A	A	A							A	A	
Potassium oxalate	K <sub>2</sub> (CO <sub>2</sub> ) <sub>2</sub> , K <sub>2</sub> C <sub>2</sub> O <sub>4</sub> +H <sub>2</sub> O	15	20	1.170				A																				
Potassium oxalate	K <sub>2</sub> (CO <sub>2</sub> ) <sub>2</sub> , K <sub>2</sub> C <sub>2</sub> O <sub>4</sub> +H <sub>2</sub> O	100	20	2.130				A																			A	
Potassium perborate		100	20													A	A	A	A									
Potassium perchlorate	KClO <sub>4</sub>	1,7	20	1.010				A				A				A	A	A	A	A		A				A	A	
Potassium perchlorate	KClO <sub>4</sub>	100	10	2.520												A	A	A	A									
Potassium perchlorate	KClO <sub>4</sub>	100	20													A	A	A	A									
Potassium perchlorate	KClO <sub>4</sub>	100	80													B	B	A	A									
Potassium permanganate	KClO <sub>4</sub>	6	20	1.040			C	A	A	B		A		B	A	A	A	A	A	A	A	D	A			A		
Potassium permanganate	KClO <sub>4</sub>	10	20				C		A	B		A		B	A	A	A	A	A	A	A	C	A					
Potassium permanganate	KClO <sub>4</sub>	10	60				C		A	B		A		B	A	A	A	A	A	A	B		A					
Potassium permanganate	KClO <sub>4</sub>	20	20	1.040		2.2	C		A			A		B	A	A	A	A	A	A	A	D	A					
Potassium permanganate	KClO <sub>4</sub>	25	20				C		A			A		B	A	A	A	A	A	A	A	D	A					




Liquid	Chemical Formula	Concentration %	Temp, degree C	Specific gravity kg/dm3	Viscosity cSt	Vapour pressure kPa	Bronze	Aluminium	Cast iron	Ductile iron	Hastelloy B	Hastelloy C	Stainless Steel SIS 2333	Stainless Steel SIS 2343	EP - Epoxy	CPVC	PP	PVDF	PTFE	FPM - Viton	EPDM - EPT	NBR - Nitrile	CR - Neoprene	Kairez	Hytrek	Carbon	Silicon	Ceramic
Potassium permanganate	KMnO <sub>4</sub>	25	80				C		A			A		B	A	B	B	A	A			D	A					
Potassium permanganate	KMnO <sub>4</sub>	100	20	2.703			C		A			A		B	A	A	A		A	A			A					
Potassium peroxide	K <sub>2</sub> O <sub>2</sub>	100	20																									
Potassium persulphate	K <sub>2</sub> S <sub>2</sub> O <sub>8</sub>	100	20	2.480				D				A		A		A	A	A	A	A		D				A		
Potassium phosphate	KH <sub>2</sub> PO <sub>4</sub> , K <sub>2</sub> HPO <sub>4</sub>	10	20					D						A	A		A	A	A			A	A					
Potassium phosphate	KH <sub>2</sub> PO <sub>4</sub> , K <sub>2</sub> HPO <sub>4</sub>	100	20																									
Potassium silicate	K <sub>2</sub> SiO <sub>3</sub>	100	20					A									A	A	A							A		A
Potassium sulphate, pure	K <sub>2</sub> SO <sub>4</sub>	10	20	1.080			C	A	A	C		A		A	A	A	A	A	A	A	A	A	A			A		A
Potassium sulphate, pure	K <sub>2</sub> SO <sub>4</sub>	100	20	2.660			C	A	A	C		B		B	A	A	A	A	A	A	A	A	A					
Potassium sulphate, pure	K <sub>2</sub> SO <sub>4</sub>	100	80				c	A	A	c		B		B	A	A	A	A	A	A	B		A					
Potassium sulphide	K <sub>2</sub> S	45	20	1.430				D				D		A			A	A	A							A		A
Potassium sulphide	K <sub>2</sub> S	100	15	1.805																								
Potassium sulphite	K <sub>2</sub> SO <sub>3</sub>	20	20	1.180				A						A			A	A										A
Potassium tartrate	KHC <sub>4</sub> H <sub>4</sub> O <sub>6</sub>	100	20					A									A	A	A	A	A	A	A	A		A		A
Potassium thiocyanide	KCNS	25	20	1.130				A				A					A	A	A							A		A
Producer gas		100	20					B						B				A	A	A		A	B					
Propane, gas pure	C <sub>3</sub> H <sub>8</sub> , CH <sub>3</sub> CH <sub>2</sub> CH <sub>3</sub>	100	20	0.500	0.4	800	A	A						A	A	A	A	A	A	A	D	A	A					
Propane, liquid pure	C <sub>3</sub> H <sub>8</sub> , CH <sub>3</sub> CH <sub>2</sub> CH <sub>3</sub>	100	20																									
Propanol	C <sub>3</sub> H <sub>7</sub> OH	100	20	0.800																								
Propargyl alcohol	HC≡CCH <sub>2</sub> OH	7	20	0.970				A									A	A	A	A		A						
Propargyl bromide	HC≡CCH <sub>2</sub> Br	100	20	1.570																								
Propene	C <sub>3</sub> H <sub>6</sub> , CH <sub>3</sub> CH=CH <sub>2</sub>	100	20	0.510		800																						
Propionaldehyde	C <sub>2</sub> H <sub>5</sub> CHO	100	30	0.810		53.2																						
Propionic acid	C <sub>2</sub> H <sub>5</sub> COOH, CH <sub>3</sub> CH <sub>2</sub> COOH	25	20	1.030			B	A				A		A	A		A	A	A	A	A	D	D	A				
Propionic acid	C <sub>2</sub> H <sub>5</sub> COOH, CH <sub>3</sub> CH <sub>2</sub> COOH	50	20				B	A				A		A	A		A	A	A	A	A	D	D	A		A		
Propionic acid	C <sub>2</sub> H <sub>5</sub> COOH, CH <sub>3</sub> CH <sub>2</sub> COOH	100	20	0.993	1	1.3	B	A				A		A	A		A	A	A	A	A	D	D	A		A		
Propyl acetate (N-Propyl acetate), pure	CH <sub>3</sub> COO-C <sub>3</sub> H <sub>7</sub>	100	20	0.890			A		A					A	A			A	A	D	B	D	D					
Propyl acetate (N-Propyl acetate), pure	CH <sub>3</sub> COO-C <sub>3</sub> H <sub>7</sub>	100	40				A		A					A	A			B	A	D		D	D					
Propyl acetate (N-Propyl acetate), pure	CH <sub>3</sub> COO-C <sub>3</sub> H <sub>7</sub>	100	60				A		A					A	A			C	A	D		D	D					
Propyl acetate (N-Propyl acetate), pure	CH <sub>3</sub> COO-C <sub>3</sub> H <sub>7</sub>	100	80				A		A					A	A			D		D		D	D					
Propyl acetone, pure		100	20															D										
Propyl alcohol, pure	C <sub>2</sub> H <sub>5</sub> CH <sub>2</sub> OH	100	20	0.800			A	A	C			A	A	A	A	A	A	A	A	A	A	B	A			A		
Propyl alcohol, pure	C <sub>2</sub> H <sub>5</sub> CH <sub>2</sub> OH	100	60				A	A	C			A	A	A	A	A	A	A	A	A	A	C	A					
Propyl alcohol, pure	C <sub>2</sub> H <sub>5</sub> CH <sub>2</sub> OH	100	80				A	A	C			A	A	A	B	B	A	A	A	A	D	A						
Propyl amine	CH <sub>3</sub> (CH <sub>2</sub> ) <sub>2</sub> NH <sub>2</sub>	100	20	0.720		33																						
Propyl glycol	CH <sub>2</sub> OH-CH <sub>2</sub> OC <sub>3</sub> H <sub>7</sub>	100	20	0.910		0.2																						
Propyl nitrate	CH <sub>3</sub> (CH <sub>2</sub> ) <sub>2</sub> NO <sub>3</sub>	100	20	1.058				A						A				A	A	D								
Propylene	CH <sub>3</sub> CH=CH <sub>2</sub>	100	20	0.510		1020		A						A				A	A	A	D	D	D					




Liquid	Chemical Formula	Concentration %	Temp, degree C	Specific gravity kg/dm3	Viscosity cSt	Vapour pressure kPa	Bronze	Aluminium	Cast iron	Ductile iron	Hastelloy B	Hastelloy C	Stainless Steel SIS 2333	Stainless Steel SIS 2343	EP - Epoxy	CPVC	PP	PVDF	PTFE	FPM - Viton	EPDM - EPT	NBR - Nitrile	CR - Neoprene	Kairez	Hytrek	Carbon	Silicon	Ceramic	
Propylene chlorohydrin	C <sub>3</sub> H <sub>7</sub> ClO	100	20																A										
Propylene dichloride, pure	CH <sub>2</sub> ClCHClCH <sub>3</sub>	100	20	1.160		5.6														B	D	D							
Propylene glycol (1,2-Propanediol)	(CH <sub>2</sub> ) <sub>2</sub> OHCH <sub>2</sub> , C <sub>3</sub> H <sub>8</sub> O <sub>2</sub>	100	20	1.040	55	0	A	A	A			A	A			A	A	A	A	A	A	A	C	A		A			
Propylene oxide	CH <sub>2</sub> OCHCH <sub>3</sub>	100	20	0.830		60		B					A			A	D	A	D	D	D	D							
Protein solutions		100	20					A				A	A			A	A	A								A			
Silicon grease		100	20															A	A	A		A	A						
Silicon L-45		100	20				A		A					A	A					A		A	A						
Silicon tetrachloride	SiCl <sub>4</sub>	100	20	1.490	0.3	26														A		A	A						
Silicone oil		100	20				A	A	A					A	A	A	A	A	A	A	A	A	A		A	A			
Silikon X-527		100	20				A	A						A	A					A		A	A						
Silver bromide	AgBr	100	25	6.470				D			B	A		B	A														
Silver chloride	AgCl	100	25	5.560																									
Silver cyanide	AgCN	100	20													A	A	A	A	A	A	A							
Silver nitrate	AgNO <sub>3</sub>	8	20	1.070			D	D	D	D	B	A		A	A	A	A	A	A	A	A	A	A				A		
Silver nitrate	AgNO <sub>3</sub>	20	20	1.190			D	D	D	D	B	A		A	A	A	A	A	A	A	A	A	A				A		
Silver nitrate	AgNO <sub>3</sub>	100	20	4.350			D	D	D	D	B	A		A	A	A	A	A	A	A	A	A	A						
Silver nitrate	AgNO <sub>3</sub>	100	80				D	D	D	D	B	A		A	A		A	A	A	A	A	B	A						
Silver salts		100	20																										
Silver sulphate	Ag <sub>2</sub> SO <sub>4</sub>	100	20													A	A	A	A	A	A	A							
Silver sulphate	Ag <sub>2</sub> SO <sub>4</sub>	100	80													A		A	A	A	A	B							
Silver, plating solution		100	20									A		A	A	A	A	A	A	A	A	A	A						
Skydrol 500		100	20																	D	A	D	D						
Skydrol 7000		100	20																	B	A	D	D						
Soap		100	20					C		B				A		A	A	A	A	A	A	A							
Soap solution		100	20				C	A	A					A	A	A	A	A	A	A	A	A	C			A			
Soda (Sodium karbonate)	Na <sub>2</sub> CO <sub>3</sub>	100	20																										
Soda lime		100	20																										
Sodium	Na	100	20	0.970		0										A	A	A	A	A	A	A							
Sodium	Na	100	80													B	B	A	A	A	A	A							
Sodium acetate, saturated	NaCH <sub>3</sub> COO, NaC <sub>2</sub> H <sub>3</sub> O <sub>2</sub> +3H <sub>2</sub> O	100	20	1.450			A	A		C		A		B	A	A	A	A	A	B	A	A	A			A		A	
Sodium acetate, saturated	NaCH <sub>3</sub> COO, NaC <sub>2</sub> H <sub>3</sub> O <sub>2</sub> +3H <sub>2</sub> O	100	40				A	A		C				B	A	A	A	A	A	C	A	A	A						
Sodium acetate, saturated	NaCH <sub>3</sub> COO, NaC <sub>2</sub> H <sub>3</sub> O <sub>2</sub> +3H <sub>2</sub> O	100	80				A	A		C				B	A	A	A	A	A		A	B	A						
Sodium alum, saturated		100	20													A	A	A	A	A	A	A							
Sodium alum, saturated		100	80													A	A	A	A	A	A	B							
Sodium aluminate	NaAlO <sub>2</sub>	100	20					D		C	B			A	A				A	A	A	A	A				A		
Sodium aluminium sulphate	NaAl(SO <sub>4</sub> ) <sub>2</sub>	100	20					A				A				A	A	A	A								A		
Sodium arsenate	Na <sub>2</sub> HAsO <sub>4</sub> +7H <sub>2</sub> O	100	25	1.880				D				A				A	A	A									A		
Sodium arsenite	NaAs, NaAsO <sub>2</sub>	20	20				D	D	D			A		A	A	A	A		A			A							



Liquid	Chemical Formula	Concentration %	Temp, degree C	Specific gravity kg/dm3	Viscosity cSt	Vapour pressure kPa	Bronze	Aluminium	Cast iron	Ductile iron	Hastelloy B	Hastelloy C	Stainless Steel SIS 2333	Stainless Steel SIS 2343	EP - Epoxy	CPVC	PP	PVDF	PTFE	FPM - Viton	EPDM - EPT	NBR - Nitrile	CR - Neoprene	Kairez	Hytrek	Carbon	Silicon	Ceramic
Sodium arsenite	NaAs, NaAsO2	100	20				D	D	D			A		A	A	A	A	A	A	A			A			A		
Sodium benzoate	NaC6H5CO2	100	20									A		A		A	A	A	A			A				A		
Sodium bicarbonate	NaHCO3	5	20	1.040			A	A	C	C	B	B		A	A	A	A	A	A	A	A	A	A					
Sodium bicarbonate	NaHCO3	10	20	1.070			A	A	C	C	B	B		A	A	A	A	A	A	A	A	A	A			A		
Sodium bicarbonate	NaHCO <sub>3</sub>	100	20	2.160			A	c	c	C	B	B		A	A	A	A	A	A	A	A	A	A					
Sodium bichromate, saturated	Na <sub>2</sub> Cr <sub>2</sub> O <sub>7</sub> +2H <sub>2</sub> O	10	20					A				A				A	A	A	A	A	A	A	A			A		A
Sodium bichromate, saturated	Na <sub>2</sub> Cr <sub>2</sub> O <sub>7</sub> +2H <sub>2</sub> O	100	20	2.520												A	A	A	A	A	A	A	A					
Sodium bichromate, saturated	Na <sub>2</sub> Cr <sub>2</sub> O <sub>7</sub> +2H <sub>2</sub> O	100	80													B	B	A	A	A	A	A	B					
Sodium bisulphate	NaHSO <sub>4</sub> +H <sub>2</sub> O	10	20	1.080			C		D	D	B	B		A	A	A	A	A	A	A	A	A	C					
Sodium bisulphate	NaHSO <sub>4</sub> +H <sub>2</sub> O	50	20	1.160			C	A	D	D	B	B		A	A	A	A	A	A	A	A	A	A			A		A
Sodium bisulphate	NaHSO <sub>4</sub> +H <sub>2</sub> O	100	20	2.100			C		D	D	B	B		A	A	A	A	A	A	A	A	A	C					
Sodium bisulphate	NaHSO <sub>4</sub> +H <sub>2</sub> O	100	80				C		D	D	B	B		A	A	B	B	A	A	A	A	A	C					
Sodium bisulphite	NaHSO <sub>3</sub>	10	20	1.100		2.2	C	A	D	D		A		A	A	A	A	A	A	A	A	A	A					
Sodium bisulphite	NaHSO <sub>3</sub>	100	20	1.480			C	A	D	D		A		A	A	A	A	A	A	A	A	A	A			A		A
Sodium bisulphite	NaHSO <sub>3</sub>	100	80				C	A	D	D		A		A	A	B	B	A	A	A	A	A	A					
Sodium borate, saturated	Na <sub>2</sub> B <sub>4</sub> O <sub>7</sub> +10H <sub>2</sub> O	100	20	1.030				A						B			A	A	A	A	A	A	A			A		A
Sodium borhydride, powder	NaBH <sub>4</sub>	100	20	1.074																								
Sodium bromate	NaBrO <sub>3</sub>	25	20	1.230													A	A	A							A		
Sodium bromate	NaBrO <sub>3</sub>	100	20																									
Sodium bromide	NaBr	40	20	1.410				D		D				C		A	A	A	A			A						
Sodium bromide, saturated	NaBr+2H <sub>2</sub> O	100	20	2.180				D		D				C		A	A	A	A			A						
Sodium bromite	NaBrO <sub>2</sub>	100	20					D						A				A	A							A		
Sodium carbonate (Soda) (Soda Ash)	Na <sub>2</sub> CO <sub>3</sub>	10	20	1.150		2.2	B	D	A	B	B			A	A	A	A	A	A	A	A	A	A					
Sodium carbonate (Soda) (Soda Ash)	Na <sub>2</sub> CO <sub>3</sub>	25	20	1.127			B	D	A	B	B			A	A	A	A	A	A	A	A	A	A					
Sodium carbonate (Soda) (Soda Ash)	Na <sub>2</sub> CO <sub>3</sub>	100	80				B	D	A	B	B			A	A	A	A	A	A	A	A	A	B	A				
Sodium carbonate (Soda), povvder	Na <sub>2</sub> CO <sub>3</sub>	100	20	2.510			B	D	A	B	B			A	A	A	A	A	A	A	A	A	A					
Sodium chlorate, saturated	NaClO <sub>3</sub>	25	20	1.230				A		C		A			A	A	A	A	A	A	A	A	A			A		
Sodium chlorate, saturated	NaClO <sub>3</sub>	28	20	1.410				A		C		A			A	A	A	A	A	A	A	A	A			A		
Sodium chlorate, saturated	NaClO <sub>3</sub>	100	20	2.490				C		C		A		B	A	A	A	A	A	A	A	A	C	A				
Sodium chlorate, saturated	NaClO <sub>3</sub>	100	80					C		C		A		B	A	B	B	A	A				A					
Sodium chloride (Common salt)	NaClO <sub>3</sub>	25	20				C	D	A	D	A	A		B	A	A	A	A	A	A	A	A	A		C	A		
Sodium chloride (Common salt)	NaCl	100	20	2.170			C	D	A	D	A	A		B	A	A	A	A	A	A	A	A	A		c			
Sodium chloride (Common salt)	NaCl	100	80				C	D	A	D	A	A		B	A	A	A	A	A	A	A	B	A		c			
Sodium chlorite	NaClO <sub>2</sub>	25	20													D	D	B	B	D	D	D						
Sodium chlorite	NaClO <sub>2</sub>	25	40													D	D	C	B	D	D	D						
Sodium chlorite	NaClO <sub>2</sub>	25	60													D	D	D	B	D	D	D						
Sodium chlorite, diluted	NaClO <sub>2</sub>	100	20					D				A				A	A	A	A			D				D		
Sodium chromate	Na <sub>2</sub> CrO <sub>4</sub> +10H <sub>2</sub> O	100	20				A	A	A			A		A	C		A	A	A	A		A	A			A		A




Liquid	Chemical Formula	Concentration %	Temp, degree C	Specific gravity kg/dm3	Viscosity cSt	Vapour pressure kPa	Bronze	Aluminium	Cast iron	Ductile iron	Hastelloy B	Hastelloy C	Stainless Steel SIS 2333	Stainless Steel SIS 2343	EP - Epoxy	CPVC	PP	PVDF	PTFE	FPM - Viton	EPDM - EPT	NBR - Nitrile	CR - Neoprene	Kairez	Hytrel	Carbon	Silicon	Ceramic
Sodium cyanide	NaCN	100	20	1.600			D	D	A	B				A	A	A	A	A	A	A	A	A	A		A	A		A
Sodium cyanide, solution	NaCN	100	20				D	D	A	B				A	A	A	A	A	A	A	A	A	A		A			
Sodium cyanide, solution	NaCN	100	80				D	D	A	B				A	A	B	B	A	A	A	A	A	A		A			
Sodium dichloroisocyanurate	NaC3Cl2N3O3	100	20	0.950																								
Sodium dichromate	Na2Cr2O7+2H2O	100	20	2.520												A	A	A	A	A	A	A						
Sodium dihydrogen phosphate	NaH2P04	10	20	1.070													A	A								A		
Sodium diphosphate	Na2HP04	100	20				C		A					A	A								A	C				
Sodium disulphite	Na2S2O5	100	20														A	A								A		
Sodium dithionite	Na2S2O4	10	20																									
Sodium dithionite	Na2S2O4	100	20																									
Sodium ethylate (Sodium ethoxide)	NaC2H5O	100	20					D						A					A									
Sodium ferricyanide, saturated		100	20												A	A	A	A	A	A	A	A						
Sodium ferricyanide, saturated		100	80													B	B	A	A									
Sodium ferrocyanide, saturated		100	20													A	A	A	A	A	A	A						
Sodium ferrocyanide, saturated		100	80													B	B	A	A									
Sodium fluoride	NaF	5	20	1.050				A		D				A		A	A	A	A	A	A	A				A		A
Sodium fluoride	NaF	100	20	2.550				C		D				A		A	A	A	A	A	A	A						
Sodium fluorsilicate	Na2SiF6	100	20	2.680																								
Sodium formate	NaHCO2	46	20					A				A		A				A	A							A		
Sodium hexametaphosphate (Calgon)	(NaP03)6	100	20				C								A					A		A	A					
Sodium hydrogen difluoric	NaHF2	100	25	2.080																								
Sodium hydrogen phosphate	Na2HP04	6	20	1.070													A	A										
Sodium hydrosulphate	NaHSO4	100	20	2.440			C					B		A	A	A	A	A	A	A	A	A	C					
Sodium hydrosulphate	NaHSO4 *H2O	100	20	2.100			C					B		A	A	A	A	A	A	A	A	A	C					
Sodium hydrosulphide	NaHS	100	20	1.790																								
Sodium hydrosulphite	Na2S2O4*2H2O, Na2S2O4	100	20	1.400													A	A										
Sodium hydroxide (Caustic soda)	NaOH+H2O	10	20	1.22			D	D	A	B				A	A	A	A	A	A	C	A	A	A	A				
Sodium hydroxide (Caustic soda)	NaOH+H2O	15%	20	1.160			D	D	A	B				A	A	A	A	A	A	C	A	A	A	A				A
Sodium hydroxide (Caustic soda)	NaOH+H2O	15	60				D	A	A	B				A	A	A	A	B	A	D	A	A	A					
Sodium hydroxide (Caustic soda)	NaOH+H2O	15	80				D	A	A	B				A	A	B	B	C	A	D	B	C	A					
Sodium hydroxide (Caustic soda)	NaOH+H2O	20	20	1.22	0.8		D	D	A	B	A			A	A	A	A	A	A		A	A	A	A				
Sodium hydroxide (Caustic soda)	NaOH+H2O	30	20	1.330	0.8	2.2	D	D	C	B				A	A	A	A	A	A	C	A	A	C	A				A
Sodium hydroxide (Caustic soda)	NaOH+H2O	30	40				D	A	C	B				A	A	A	A	A	A	D	A	A	C	A				
Sodium hydroxide (Caustic soda)	NaOH+H2O	30	60				D	A	C	B				A	A	A	A	B	A	D	A	A	C					
Sodium hydroxide (Caustic soda)	NaOH+H2O	30	80				D	A	C	B				A	A	B	B	C	A	D	A	A	C					
Sodium hydroxide (Caustic soda)	NaOH+H2O	40	20	1.43	14					B							C	A	A	C	A	A	A	A				
Sodium hydroxide (Caustic soda)	NaOH+H2O	50	20	1.530	25		D	A		B	A	A		B	A	A	A	A	A	D	A	A	B	A		A		A
Sodium hydroxide (Caustic soda)	NaOH+H2O	50	40				D	A		B	A	A		B	A	A	A	B	A	D	A	A	B	A				




Liquid	Chemical Formula	Concentration %	Temp, degree C	Specific gravity kg/dm3	Viscosity cSt	Vapour pressure kPa	Bronze	Aluminium	Cast iron	Ductile iron	Hastelloy B	Hastelloy C	Stainless Steel SIS 2333	Stainless Steel SIS 2343	EP - Epoxy	CPVC	PP	PVDF	PTFE	FPM - Viton	EPDM - EPT	NBR - Nitrile	CR - Neoprene	Kairez	Hytrek	Carbon	Silicon	Ceramic
Sodium hydroxide (Caustic soda)	NaOH+H2O	50	60				D	A		B	A	A		B	A	A	A	C	A	D	A	A	B	A				
Sodium hydroxide (Caustic soda)	NaOH+HzO	50	80				D			B	A	A		B	A	B	B	D	A	D	A	A	B					
Sodium hydroxide (Caustic soda)	NaOH+H2O	70	20				D	D		B					A	A	B	A	A	D	A	D	B					
Sodium hydroxide (Caustic soda)	NaOH+H2O	70	40				D	D		B					A	A	B	B	A	D	A	D	B					
Sodium hydroxide (Caustic soda)	NaOH+H2O	70	60				D	D		B					A	A	B	C	A	D	A	D	B					
Sodium hydroxide (Caustic soda)	NaOH+H2O	70	80				D	D		B					A	B	B	D	A	D	B	D	B					
Sodium hydroxide (Caustic soda)	NaOH+H2O	80	20				D	D		B	B	B		C	A	A	A		A	D	A	D	B					
Sodium hydroxide (Caustic soda)	NaOH	100	20	2.130																								
Sodium hypochlorite	NaClO	5	20	1.020		2.3	D	D	D																	A		
Sodium hypochlorite	NaClO	13	20	1.200	1		D	D	D			A		C	A	A	B	A	A	D	D	D	B		A			
Sodium hypochlorite	NaClO	13	60				D	D	D			A		C	A	B	c	B	A	D	D	D	B		A			
Sodium hypochlorite	NaClO	20	20				D	D	D			A		C	A	A	A		A	A	B	B	B					
Sodium hypochlorite, solution	NaClO	100	20	1.220			D	D	D			A		C	C		A		A	A	D	D	B			A		
Sodium iodide	NaI	100	20					A						D			A	A	A			A				A		
Sodium metaphosphate	NaP03	100	20				C	A	D					A	A		A	A	A	A	A	A	B					
Sodium metasilicate	NaSi03	100	20				A		A					A	A	A	A	A	A	A	A	A	A					
Sodium methylate	NaCH30	100	20																									
Sodium monophosphate, di, tri	NaH2P04	100	20				A		D					C	A					A		A	A					
Sodium nitrate	NaN03	4	20	1.030			C	A	A	B				A	A	A	A	A	A	A	A	A	C					
Sodium nitrate	NaN03	45	20	1.370			C	A	A	B		A		A	A	A	A	A	A	A	A	A	C			A		A
Sodium nitrate, saturated	NaN03	100	20	2.260			C	A	A	B				B	A	A	A	A	A	A	A	A	C					
Sodium nitrate, saturated	NaN03	100	80				C	A	A	B				B	A	A	A	A	A	A	A	A	B	C				
Sodium nitrite	NaN02	50	20					A				A				A	A	A	A	A	A	A				A		A
Sodium nitrite, saturated	NaN02	100	20	2.170				A								A	A	A	A	A	A	A						
Sodium nitrite, saturated	NaN02	100	80					A								B	A	A	A	A	A	B						
Sodium oleate	NaC <sub>17</sub> H <sub>33</sub> CO <sub>2</sub>	100	20					A				A		A					A							A		
Sodium orthophenylphenate	NaC <sub>6</sub> H <sub>5</sub> C <sub>6</sub> H <sub>4</sub> O	100	20											A	A								D	A				
Sodium oxalate	Na2C204	3,3	20					A						A			A	A	A				A			A		
Sodium oxalate	Na2C204	100	20																									
Sodium palmitate		100	20																A	A								
Sodium palmitate solution		5	20																A	A								
Sodium perborate	NaB03+4H2O, NaB02H2O2	100	20				D	D	C	B				C	A	C	A	A	A	A	A	B	D			A		
Sodium perchlorate	NaCl04+H2O	10	20	1.070										A		A	A	A	A									
Sodium perchlorate	NaCl04+H2O	25	20	1.180				A				A		A		A	A	A	A									A
Sodium perchlorate	NaCl04+H2O	100	20	2.020										A		A	A	A	A									
Sodium perchlorate	NaCl04+H2O	100	80											A		B	B	A	A									
Sodium perdisulfate	Na2S208	100	20														A	A										
Sodium peroxide	Na202	5	20				D	D		C	B	B		A	A	A	A	A	A	A	A	A	D			D		A


Liquid	Chemical Formula	Concentration %	Temp, degree C	Specific gravity kg/dm3	Viscosity cSt	Vapour pressure kPa	Bronze	Aluminium	Cast iron	Ductile iron	Hastelloy B	Hastelloy C	Stainless Steel SIS 2333	Stainless Steel SIS 2343	EP - Epoxy	CPVC	PP	PVDF	PTFE	FPM - Viton	EPDM - EPT	NBR - Nitrile	CR - Neoprene	Kairez	Hytrek	Carbon	Silicon	Ceramic
Sodium peroxide	Na2O2	10	20	1.110			D	D		C	B	B		A	A	A	A	A	A	A	A	A	D					
Sodium peroxide	Na2O2	50	20				D	D	D		B	B		A	A	A	A	A	A	A		A	A					
Sodium peroxide	Na2O2	100	20	2.810			D	D	C		B	B		A	A	A	A	A	A	A	A	A	D					
Sodium peroxide	Na2O2	100	80				D	D	C		B	B		A	A	B	B	A	A	A	A		D					
Sodium persulphate	Na2S2O8	100	20					D						A			A	A	A				D			A		
Sodium phosphate acid		100	20													A	A	A	A	A	A	A						
Sodium phosphate acid		100	80													B		A	A	A	A	A						
Sodium phosphate, alkaline		100	20							C				A		A	A	A	A	A	A	A						
Sodium phosphate, neutral	Na3PO4	100	20				C	A		C				A	A	A	A	A	A	A	A	A	B	A		A		
Sodium phosphate, neutral	Na3PO4	100	80					B		c				A	A	B	A	A	A	A	A	A	B					
Sodium phosphate, primary	NaPO3+12H2O	10	20	1.070		2.2		D		c				A														
Sodium phosphate, primary	NaPO3+12H2O	100	25	1.910				D		c				A														
Sodium phosphate, secondary	NaPO3+12H2O	50	20	1.250		2.3		D		c				A														
Sodium phosphate, secondary	NaH2PO4+12H2O	100	25	1.520				D		c				A														
Sodium phosphate, tertiary	Na3PO4+12H2O	100	25	1.620				D		c				A														
Sodium polyphosphate		100	20				C		D					A	A					A	A	A	C					
Sodium propionate	CH3CH2CO2Na	4	20	1.040				A									A	A	A							A		
Sodium pyrophosphate	Na4P2O7	100	20														A	A										
Sodium silicate	Na2SiO3	20	20	1.240			C	A	A	B				A	A		A	A	A	A	A	A	A	A	A	A	A	A
Sodium silicate	Na2SiO3	100	20	2.400			C	D	A	B				B	A		A	A	A	A	A	A	A	A	A	A	A	A
Sodium silicofluoride	Na2SiF6	100	20					D									A	A										
Sodium sulphate (Glauber's salt)	Na2SO4, Na2SO4+10H2O	1	20	1.100		2.2	B	A	A	B	B	B		B	A	A	A	A	A	A	A	A	D		A			
Sodium sulphate (Glauber's salt)	Na2SO4, Na2SO4+10H2O	5	20	1.020		2.2	B	A	A	B	B	B		B	A	A	A	A	A	A	A	A	D		A			
Sodium sulphate (Glauber's salt)	Na2SO4, Na2SO4+10H2O	50	20	1.460			B	A	A	B	B				A	A	A	A	A	A	A	A	D		A	A		
Sodium sulphate (Glauber's salt)	Na2SO4, Na2SO4+10H2O	100	20				B	A	A	B	B	B		B	A	A	A	A	A	A	A	A	D		A			
Sodium sulphate, saturated	Na2SO4	100	20				B	A	A	B	B	B		B	A	A	A	A	A	A	A	A	D		A			
Sodium sulphate, saturated	Na2SO4	100	80				B	A	A		B	B		B	A	A	A	A	A	A	A	A	B	D		A		
Sodium sulphide	Na2S, Na2S+9H2O	16	20	1.160			D	D	A	B	B	A		B	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Sodium sulphide	Na2S, Na2S+9H2O	20	20	1.070		2.2	D	D	A	B	B	A		B	A	A	A	A	A	A	A	A	A	A	A	A		
Sodium sulphide	Na2S, Na2S+9H2O	100	20	1.856			D	D	A	B	B	A		B	A	A	A	A	A	A	A	A	A	A	A			
Sodium sulphide	Na2S, Na2S+9H2O	100	20	1.420			D	D	A	B	B	A		B	A	A	A	A	A	A	A	A	A	A	A			
Sodium sulphide	Na2S, Na2S+9H2O	100	80				D	D	A	B	B	A		B	A	A	A	A	A	A	A	A	B	A	A			
Sodium sulphite	Na2SO3, Na2SO3+7H2O	18	20	1.180			C	A	A	B				A	A	A	A	A	A	A	A	A	A			A	A	
Sodium sulphite	Na2SO3, Na2SO3+7H2O	40	20				C	A	A	B				A	A	A	A	A	A	A	A	A	A			A	A	
Sodium sulphite	Na2SO3, Na2SO3+7H2O	100	20	1.530			c		A						A	A	A	A	A	A	A	A	A					
Sodium sulphite	Na2SO3, Na2SO3+7H2O	100	80				c		A						A	A	A	A	A	A	B	B	A					
Sodium tartrate	C4H4O6Na2	50	20									A														A		




Liquid	Chemical Formula	Concentration %	Temp. degree C	Specific gravity kg/dm3	Viscosity cSt	Vapour pressure kPa	Bronze	Aluminium	Cast iron	Ductile iron	Hastelloy B	Hastelloy C	Stainless Steel SIS 2333	Stainless Steel SIS 2343	EP - Epoxy	CPVC	PP	PVDF	PTFE	FPM - Viton	EPDM - EPT	NBR - Nitrile	CR - Neoprene	Kairez	Hytrek	Carbon	Silicon	Ceramic
Sodium tetraborate (Borax), saturated	Na2B4O7+10H2O	100	20	1.030			A	C	A	C		A		A	A	A	A	A	A	A	A	A	C			A		
Sodium tetraborate (Borax), saturated	Na2B4O7+10H2O	100	40				A	C	A	C		A		A	A	A	A	A	A	A	A	B	C					
Sodium tetraborate (Borax), saturated	Na2B4O7+10H2O	100	60				A	C	A	C		A		A	A	A	A	A	A	A	A	C	C					
Sodium tetraborate (Borax), saturated	Na2B4O7+10H2O	100	80				A	C	A	C		A		A	A	A	A	A	A	A	A	D	C					
Sodium thiocyanate		100	20													A	A	A	A	A	A	A						
Sodium thiosulphate	Na2S2O3, Na2S2O3+5H2O	40	20				D	A	C					A	A	A	A	A	A	A	A	A	A			A		
Sodium thiosulphate	Na2S2O3, Na2S2O3+5H2O	100	20	1.730			D	A	C					A	A	A	A	A	A	A	A	A	A					
Sodium thiosulphate	Na2S2O3, Na2S2O3+5H2O	100	80				D	A	C					A	A	B	A	A	A	A	A	B	A					
Sodium triphosphate	Na3PO4,r	100	20				D		A					A	A							A	C					
Sodium tripolyphosphate	Na5P3O10	100	20				D		D					A	A							A						
Sodium, saturated	Na	100	20	0.970		0										A	A	A	A	A	A	A						
Sodium, saturated	Na	100	80													B	B	A	A	A	A	B						
Sour crude oil		100	20														A	A	A	A	D	B						
Soya sauce		100	20				A		D					A	A					A		A	A					
Soybean oil		100	20	0.940	60		A	A	A					A	A	A	A	A	A	A	A	A	D		C			
Soybean oil		100	80		12		A	A	A					A	A	B	B	A	A	A	C	D	D		C			
Sperm oil		100	20	0.88	27		A		A					A	A	A				A		A	D					
Spindle oil		100	20					A									A	A	A	A		A						
Spinning acid	H2SO4 - haltig	10	20											D			A	A										
Spinning bath acids	CS2 - haltig	100	20									A					A	A				D						
Stannic chloride (Tin (IV) chloride)	SnCl4	100	20	3.950			D	D	D	D				A	A	A	A	A	A	A	A	A	A					
Stannic chloride (Tin (IV) chloride)	SnCl4	100	80				D	D	D	D				A	A	B	B	A	A	A	A	A	A					
Stannic fluoborate	Sn(BF4)2	100	20				D		D					A	A					A		A	A					
Stannous chloride (Tin (II) chloride)	SnCl2, SnCl2+2H2O	20	20	1.170				D		D		A		D		A	A	A	A	A	B	A	A			A		A
Stannous chloride (Tin (II) chloride)	SnCl2, SnCl2+2H2O	100	20	2.710				D		D		A		D		A	A	A	A	A	B	A	A			A		A
Stannous chloride (Tin (II) chloride)	SnCl2, SnCl2+2H2O	100	80					D		D		A		D		B	B	A	A	A		A	A					
Stannous sulphate	SnSO4	100	20														A	A								A		
Stannous tetrachloride	SnCl4	100	20	2.330										D			A	A	A							A		A
Starch	(C6H10O5)x	100	20				A	A	C	C				A	A	A	A	A	A	A	A	A	A			A		
Starch syrup		100	20					A									A	A	A	A	A	A						
Steam above 150 C		100						A						A						D		D	D					
Steam under 150 C		100						A						A				A	A	D		D	C					
Stearic acid	C17H35COOH	100	20	0.940			C	A		C	A	A		A	A	A	B	A	A	A	D	B	C			A		
Stearic acid	C17H35COOH	100	60				C	A		C	A	A		A	A	A	B	A	A	B	D	B	C					
Stearic acid	C17H35COOH	100	80				C			C	A	A		A	A	B	C	A	A	C	D	C						
Stoddard solvent		100	20				A	A	A					A	A	A	A		A	A	D	A	D					
Strontium nitrate	Sr(NO3)2	40	20	1.420													A	A								A		




Liquid	Chemical Formula	Concentration %	Temp, degree C	Specific gravity kg/dm3	Viscosity cSt	Vapour pressure kPa	Bronze	Aluminium	Cast iron	Ductile iron	Hastelloy B	Hastelloy C	Stainless Steel SIS 2333	Stainless Steel SIS 2343	EP - Epoxy	CPVC	PP	PVDF	PTFE	FPM - Viton	EPDM - EPT	NBR - Nitrile	CR - Neoprene	Kairez	Hytrek	Carbon	Silicon	Ceramic	
Strontium nitrate	Sr(NO3)2	100	20	2.986																									
Strontium peroxide	SrO2	100	20	4.560																									
Styrene	C6H5CHCH2(COOH)2	100	20	0.910	11	0.6		A					A	A		c	A	A	C	D	C	D	A						
Succinic acid (Amber acid)	C4H6O4, C2H4(COOH)2	50	20	1.060				A				A	A		A	A	A	A	A	A	A	A				A		A	
Succinic acid (Amber acid)	C4H6O4, C2H4(COOH)2	100	20												A	A	A	A	A	A	A	A							
Succinic acid (Amber acid)	C4H6O4, C2H4(COOH)2	100	80												B	B	A	A											
Sucrose solution		100	20					B					A					A	A	A	A	A	A						
Sugar		100	20				A	A	A			A	A	A	A		A		A	A	A	A	A						
Sugar solution		100	20					A				A			A		A	A	A	A		A	A						
Sugar svrup		100	20																										
Sulfamic acid	NH2SO3H	20	20												D	D	D												
Sulfanilic acid	C6H4NH2SO3	100	20															A								A			
Sulfurous oxychloride	SOCl2	100	20	1.640		12.4																							
Sulphate liquor (Black liquor)	Ca(HSO3)2	100	20				D		D			A	C	A						A	A	A	A						
Sulphinol		100	20																A										
Sulphite liquor		6	20				D	D					A	A	A	A	A	A	A	A	A	D	B						
Sulphite liquor, paper processes		100	20				A		A				A	A										A					
Sulphite liquor, pulp processes		100	20				D		C				A	A									A	A					
Sulpholane	C4H8O2S	100	20																										
Sulphur	s	100	20	2.060			D	A	A				A		A	A	A	A	A	A	C	D	A						
Sulphur	s	100	80				D	A	A				A		B	A	A	A	A	A		D	A						
Sulphur chloride	S2Cl2	100	20	1.680			D	D	D				D	C		C	A	A	A	A	D	C	D						
Sulphur chloride	S2Cl2	100	40				D	D	D				D	C		D	A	A			D		D			A		A	
Sulphur chloride	S2Cl2	100	20	1.680			D	D	D	D			D	C		D	A	A			D	C	D			A		A	
Sulphur chloride	S2Cl2	100	40				D	D	D	D			D	C		D	A	A			D		D						
Sulphur dichloride	scl2	100	20															C	A	A	A	D	D						
Sulphur dichloride	scl2	100	40														D				D	D							
Sulphur dioxide, aqueous	so2	100	20																										
Sulphur dioxide, dry	so2	100	20	1.460		340	D	D	A			B	B	A	A	A	A	A	A	A	A	D	D			A		A	
Sulphur dioxide, humid (wet)	so2	100	20	1.400			D	D	A			B	B	A	B	B	A	A				D	D			A		A	
Sulphur dioxide, humid (wet)	so2	100	80				D	D	A			B	B	A	B	B	A	A				D	D			A		A	
Sulphur hexafluoride	SF6	100	20																A	A	A	B	A		A				
Sulphur trioxide	SO3	100	20	1.990			A	D					C	A	D	D	D	B	C	C	D	D	A		D				
Sulphur trioxide	so3	100	40				A	D					C	A	D	D	D		D	D	D	D	A		D				
Sulphuric acid	H2SO4	10	20	1.070			D	D	D	D	C	A	C	A	A	A	A	A	A	A	A	A	D	A	A				
Sulphuric acid	H2SO4	10	80				D	D	D	D	c	A	C	A	A	A	A	A	A	A	A	B	D	A	A				
Sulphuric acid	H2SO4	15	20	1.100			D	D	D	D	c	A	C	A	A	A	A	A	A	A	A	A	D	A	A				
Sulphuric acid	H2SO4	20	20	1.140			D	D	D	D	c	A	c	A	A	A	A	A	A	A	A	A	D	A	A				



Liquid	Chemical Formula	Concentration %	Temp, degree C	Specific gravity kg/dm3	Viscosity cSt	Vapour pressure kPa	Bronze	Aluminium	Cast iron	Ductile iron	Hastelloy B	Hastelloy C	Stainless Steel SIS 2333	Stainless Steel SIS 2343	EP - Epoxy	CPVC	PP	PVDF	PTFE	FPM - Viton	EPDM - EPT	NBR - Nitrile	CR - Neoprene	Kairez	Hytrek	Carbon	Silicon	Ceramic
Sulphuric acid	H <sub>2</sub> SO <sub>4</sub>	30	20	1.220			D	D	D	D	C	B		D	A	A	A	A	A	A	A	A	D	A	A			
Sulphuric acid	H <sub>2</sub> SO <sub>4</sub>	30	80				D	D	D	D	C	B		D	A	A	A	A	A	A	B	B	D		A			
Sulphuric acid	H <sub>2</sub> SO <sub>4</sub>	40	20	1.300			D	D	D	D	C	B		D	A	A	A	A	A	A	A	D	D	A	A	A		A
Sulphuric acid	H <sub>2</sub> SO <sub>4</sub>	50	20	1.400			D	D	D	D	C	B		D	A	A	A	A	A	A	A	A	D	A	A	A		A
Sulphuric acid	H <sub>2</sub> SO <sub>4</sub>	50	40				D	D	D	D	C	B		D	A	A	A	A	A	A	A	B	D	A	A			
Sulphuric acid	H <sub>2</sub> SO <sub>4</sub>	50	80				D	D	D	D	C	B		D	A	A	A	A	A	A	B	C	D		A			
Sulphuric acid	H <sub>2</sub> SO <sub>4</sub>	60	20	1.500			D	D	D	D	C	B		D	A	A	A	A	A	A	A	A	D	A				
Sulphuric acid	H <sub>2</sub> SO <sub>4</sub>	60	80				D	D	D	D	C	B		D	A	A	B	A	A	A	B	B	D	A				
Sulphuric acid	H <sub>2</sub> SO <sub>4</sub>	70	20	1.610			D	D	D	D	C	B		D	A	A	A	A	A	A	A	B	D	A		A		A
Sulphuric acid	H <sub>2</sub> SO <sub>4</sub>	70	60				D	D	D	D	C	B		D	A	A	A	A	A	A	B	B	D					
Sulphuric acid	H <sub>2</sub> SO <sub>4</sub>	70	80				D	D	D	D	C	B		D	A	A	B	A	A	A	B	C	D					
Sulphuric acid	H <sub>2</sub> SO <sub>4</sub>	75	20	1.650		0.09	D	D	D	D	C	B		D	C	A	A	A	A	A	A	D	D	A				
Sulphuric acid	H <sub>2</sub> SO <sub>4</sub>	80	20	1.730			D	D	D	D	C	A		D	A	A	A	A	A	A	A	B	D	A		A		A
Sulphuric acid	H <sub>2</sub> SO <sub>4</sub>	80	60				D	D	D	D	C	A		D	A	B	B	A	A	A	B	C	D					
Sulphuric acid	H <sub>2</sub> SO <sub>4</sub>	80	80				D	D	D	D	C	A		D	A	C	B	A	A	B	C	C	D					
Sulphuric acid	H <sub>2</sub> SO <sub>4</sub>	90	20	1.820			D	D	D	D	C	A		D	A	A	A	A	A	A	A	C	D			A		A
Sulphuric acid	H <sub>2</sub> SO <sub>4</sub>	90	40				D	D	D	D	C	A		D	A	A	A	A	A	A	B	C	D					
Sulphuric acid	H <sub>2</sub> SO <sub>4</sub>	90	60				D	D	D	D	C	A		D	A	B	B	A	A	A	C	C	D					
Sulphuric acid	H <sub>2</sub> SO <sub>4</sub>	90	80				D	D	D	D	C	A		D	A	C	B	A	A	B	D	C	D					
Sulphuric acid	H <sub>2</sub> SO <sub>4</sub>	93	20				D	D	D	D	C	A		D	A	A	A	A	A	A	B	C	D					
Sulphuric acid	H <sub>2</sub> SO <sub>4</sub>	93	40				D	D	D	D	C	A		D	A	A	A	A	A	A	B	D	D					
Sulphuric acid	H <sub>2</sub> SO <sub>4</sub>	93	60				D	D	D	D	C	A		D	A	B	B	A	A	B	C	D	D					
Sulphuric acid	H <sub>2</sub> SO <sub>4</sub>	93	80				D	D	D	D	C	A		D	A	C	B	A	A	B	D	D	D					
Sulphuric acid	H <sub>2</sub> SO <sub>4</sub>	94	20				D	D	D	D	C	A		D	A	A	B	A	A	A	C	D	D					
Sulphuric acid	H <sub>2</sub> SO <sub>4</sub>	94	40				D	D	D	D	C	A		D	A	B	B	A	A	B	D	D	D					
Sulphuric acid	H <sub>2</sub> SO <sub>4</sub>	94	60				D	D	D	D	C	A		D	A	C	B	A	B	C	D	D	D					
Sulphuric acid	H <sub>2</sub> SO <sub>4</sub>	94	80				D	D	D	D	C	A		D	A		C	B	B	C	D	D	D					
Sulphuric acid	H <sub>2</sub> SO <sub>4</sub>	95	20				D	D	D	D	C	A		D	A	A	C	A	A	A	D	D	D					
Sulphuric acid	H <sub>2</sub> SO <sub>4</sub>	95	40				D	D	D	D	C	A		D	A	B		A	A	C	D	D	D					
Sulphuric acid	H <sub>2</sub> SO <sub>4</sub>	95	60				D	D	D	D	C	A		D	A	C		A	B	C	D	D	D					
Sulphuric acid	H <sub>2</sub> SO <sub>4</sub>	95	80				D	D	D	D	C	A		D	A			B	B		D	D	D					
Sulphuric acid	H <sub>2</sub> SO <sub>4</sub>	96	20	1.840	50	0.09	D	D	D	D	A	A		A	A	B	D	A	A	B	D	D	D					
Sulphuric acid	H <sub>2</sub> SO <sub>4</sub>	96	40				D	D	D	D	A	A		A	A	B	D	A	A	C	D	D	D					
Sulphuric acid	H <sub>2</sub> SO <sub>4</sub>	96	60				D	D	D	D	A	A		A	A	C	D	A	B	D	D	D	D					
Sulphuric acid	H <sub>2</sub> SO <sub>4</sub>	96	80				D	D	D	D	A	A		A	A	D	D	B	B	D	D	D	D					
Sulphuric acid	H <sub>2</sub> SO <sub>4</sub>	98	20	1.85	16		D	D	D	D	A	A		A	A	B	D	A	B	D	D	D	D					A
Sulphuric acid	H <sub>2</sub> SO <sub>4</sub>	98	40				D	D	D	D	A	A		A	A	C	D	A	B	D	D	D	D					
Sulphuric acid	H <sub>2</sub> SO <sub>4</sub>	98	60				D	D	D	D	A	A		A	A	D	D	B	B	D	D	D	D					




Liquid	Chemical Formula	Concentration %	Temp, degree C	Specific gravity kg/dm3	Viscosity cSt	Vapour pressure kPa	Bronze	Aluminium	Cast iron	Ductile iron	Hastelloy B	Hastelloy C	Stainless Steel SIS 2333	Stainless Steel SIS 2343	EP - Epoxy	CPVC	PP	PVDF	PTFE	FPM - Viton	EPDM - EPT	NBR - Nitrile	CR - Neoprene	Kairez	Hytrek	Carbon	Silicon	Ceramic
Sulphuric acid	H <sub>2</sub> SO <sub>4</sub>	98	80				D	D	D	D	A	A		A	A	D	D	C	B	D	D	D	D					
Sulphuric acid	H <sub>2</sub> SO <sub>4</sub>	100	20	1.840			D	D	D	D	A	A		A	A	D	D	D	D	B	D	D	D					
Sulphurous acid	H <sub>2</sub> SO <sub>3</sub>	100	20	1.030			D	D	D	D		B		B	A	A	A	A	A	A	A	C	D			A		A
Sulphurous acid	H <sub>2</sub> SO <sub>3</sub>	100	80				D	D	D	D		B		B	A	B	A	A	A	B	A		D			A		A
Sulphuryl chloride, dry	SO <sub>2</sub> Cl <sub>2</sub>	100	20	1.667	1	13.3		A									D		A	A		D				A		
Sulphuryl chloride, humid	SO <sub>2</sub> Cl <sub>2</sub>	100	20	1.667	1	13.3		D									D		A	A		D				A		
Sweet sorghum		100	20				D		A					A	A					A		A	A					
Svrup		100	20				D	B		C				A	A	A	A			A	A	B	A	A				
Svrup, brown		100	20	1,4	9300		D	B		C				A	A	A	A			A	A	B	A	A				
Svrup, brown		100	30	1,4	2800		D	B		c				A	A	A	A			A	A	B	A	A				
Svrup, brown		100	40	1,4	1000		D	B		c				A	A	A	A			A	A	B	A	A				
Svrup, dark		100	20	1,4	7800		D	B		c				A	A	A	A			A	A	B	A	A				
Svrup, dark		100	30	1,4	2300		D	B		c				A	A	A	A			A	A	B	A	A				
Svrup, dark		100	40	1,4	900		D	B		c				A	A	A	A			A	A	B	A	A				
Svrup, white		100	20	1,4	8200		D	B		c				A	A	A	A			A	A	B	A	A				
Svrup, white		100	30	1,4	2300		D	B		c				A	A	A	A			A	A	B	A	A				
Svrup, white		100	40	1,4	900		D	B		c				A	A	A	A			A	A	B	A	A				
Tali oil (Pine oil), crude		100	20	0.970			D	A	C	B				A	A	A	A	A	A	A	A	D	A	D				
Tallow, pure		100	20											A	A		A	A	A	A	A	A	A	A	A			
Tannic acid	C <sub>20</sub> H <sub>6</sub> , C <sub>76</sub> H <sub>52</sub> O <sub>46</sub>	10	20	1.035			A	C	C	C				C	A	A	A	A	A	A		A	A		A			
Tannic acid	C <sub>20</sub> H <sub>6</sub> , C <sub>76</sub> H <sub>52</sub> O <sub>46</sub>	50	20				A	C	C	c				C	A	A	A	A	A	A		A	A			A		
Tannic acid	C <sub>20</sub> H <sub>6</sub> , C <sub>76</sub> H <sub>52</sub> O <sub>46</sub>	100	20				A	C	C	c				C	A	A	A	A	A	A	B	B	A					
Tanning extracts		100	20					A				A					A	A	A	A		A						
Tanning liguor		100	20				A					A		A	A	A	A	A	A		B	A	A					
Tanning oil		100	20											A	A					A		A	D					
Tar		100	20					A		B		A		A		D	B	A	A	A	D	A	C			A		
Tar oil		100	20					A									D		A	A	D	A	C			A		
Tartaric acid	C <sub>2</sub> H <sub>2</sub> (OH) <sub>2</sub> (COOH) <sub>2</sub> , C <sub>4</sub> H <sub>6</sub> O <sub>6</sub>	10	20				A	A	C	D	B				A	A	A	A	A	A	A	A	A		C	A		
Tartaric acid, saturated	C <sub>2</sub> H <sub>2</sub> (OH) <sub>2</sub> (COOH) <sub>2</sub> , C <sub>4</sub> H <sub>6</sub> O <sub>6</sub>	100	20	1.760			A	A	C	D	B	B		B	A	A	A	A	A	A	A	A	A		C	A		
Tartaric acid, saturated	C <sub>2</sub> H <sub>2</sub> (OH) <sub>2</sub> (COOH) <sub>2</sub> , C <sub>4</sub> H <sub>6</sub> O <sub>6</sub>	100	60				A	A	C	D	B	B		B	A	B	B	A	A		A	A	A		C			
Tartaric acid, saturated	C <sub>2</sub> H <sub>2</sub> (OH) <sub>2</sub> (COOH) <sub>2</sub> , C <sub>4</sub> H <sub>6</sub> O <sub>6</sub>	100	80				A		C	D	B	B		B	A	B	C	A	A		A	A	A		C			
Terpineol	C <sub>10</sub> H <sub>18</sub> O	100	20					A						A					A	A	C	B	D					
Tertiary butyl alcohol		100	20												A	A	A	A	A	A	B	D	B					
Tertiary butyl catechol		100	20					C						B						A	B	D	B					
Tertiary butyl mercaptan		100	20																	A		D	D					
Tetrabromomethane		100	20																	A		D						
Tetrachlorethylene, dry, pure	C <sub>2</sub> Cl <sub>4</sub> , CCl <sub>2</sub> CCl <sub>2</sub>	100	20	1.623	1	1.9		A						A			D	A	A	A	D	D	D	A		A		
Tetrachlorethylene, humid, pure	C <sub>2</sub> Cl <sub>4</sub> , CCl <sub>2</sub> CCl <sub>2</sub>	100	20	1.623	1	1.9		D						A			D	A	A	A	D	D	D	A		A		



Liquid	Chemical Formula	Concentration %	Temp, degree C	Specific gravity kg/dm3	Viscosity cSt	Vapour pressure kPa	Bronze	Aluminium	Cast iron	Ductile iron	Hastelloy B	Hastelloy C	Stainless Steel SIS 2333	Stainless Steel SIS 2343	EP - Epoxy	CPVC	PP	PVDF	PTFE	FPM - Viton	EPDM - EPT	NBR - Nitrile	CR - Neoprene	Kairez	Hytrel	Carbon	Silicon	Ceramic	
Tetrachloroethane, pure	Cl2CH-CHCl2, (Cl2CH)2	100	20	1.590		0.8	C		C				A	A		D	A	A	A	D	D	D	A			A			
Tetrachloromethane	CCl4	100	20	1.590			B					A	A	A		D	A	A	A	D	D	D	C						
Tetraethyl lead (Motor fuel)	Pb(C2H5)4, Pb(CH3-CH2)4	100	20	1.660					A				A	A		A	A	A	B	D	D	C							
Tetraethyl lead, pure	Pb(H3-CH2)4, Pb(C2H5)4	100	20	1.660				B	A				A	A		A	A	A	B	D	D								
Tetrahydrofuran, pure	C4H8O, (CH2)4O	100	20	0.888	12	20	D	C				A	A	A	D	B	B	A	D	D	D	D	A	C	A				
Tetrahydrofuran, pure	C4H8O, (CH2)4O	100	40				D	C				A	A	A	D	C	C	A	D	D	D	D	A	C					
Tetrahydrofuran, pure	C4H8O, (CH2)4O	100	60				D	C				A	A	A	D	D		A	D	D	D	D		C					
Tetrahydrofuran, pure	C4H8O, (CH2)4O	100	80				D	C					A	A	D	D		B	D	D	D	D		C					
Tetraline (Tetrahydronaphthalene), pure	C10H12	100	20	0.970		0.1		A					A	A		D	A	A	A	D	C	D				A			
Tetramethyl lead	Pb(CH3)4	100	20	1.990																									
Tetramethylene dichloride	CH2ClCH2CH2CH2Cl	100	20	1.140		0.5																							
Tetramethyl ammonium hydroxide		50	20															A	A										
Tetramethyl ammonium hydroxide		50	60															B	A										
Tetrapropylene	C12H24	100	20	0.760																									
Thioglycolic acid	HSCH2COOH	80	20	1.320			D	D	D				A	A									C						
Thioglycolic acid	HSCH2COOH	100	25	1.330			D	D	D				A	A									C						
Thionylchloride, pure	SOCI2	100	20	1.640		13.3	D	A	D				D		C	D	D	A	A			D	D			A			
Thorium nitrate	Tn(NO3)4	100	20																										
Tin	Sn	100	25	5.750																									
Tin dichloride (Stannous chloride)	SnCl2, SnCl2+2H2O	100	20							D		A	D																
Tin, plating solution		100	20									A	A	A	A	A	A	A	A	A	A	A	A						
Tin, plating solution		100	60									A	A	A	A	B	B	A	A	A	B	A	A						
Tin, plating solution		100	80									A	A	A	A			A	A	B		A	A						
Titanium sulfate	Ti(SO4)2	100	20													A	A	A	A										
Titanium tetrachloride	TiCl4	100	20	1.730		1.3		D					B					A	A	A	D	C	D						
Toluene	C6H5CH3, C7H8	100	20	0.870	1	2.9	D	A	A	A			A	A	D	B	A	A	B	D	D	D	A	C	A				
Toluene	C6H5CH3, C7H8	100	40				D	A	A	A			A	A	D	C	A	A		D	D	D	A	C					
Toluene	C6H5CH3, C7H8	100	60				D	A	A	A			A	A	D	D	B	A		D	D	D		C					
Toluene	C6H5CH3, C7H8	100	80				D	A	A	A			A	A	D	D	C	A		D	D	D		C					
Tomato juice		100	20					A					A	A					A	A	A	A							
Tooth paste		100	20				A		D				A	A						A		A	C						
Transformer oil (Switch oil)		100	20				A	A	A				A	A		A	A	A	D	D	A	D							
Transmission fluid		100	20	0.95	11		A		A				A	A						A									
Triacetin, pure		100	20																	B	A	B	B						
Triamylamine	(C5H11)3N	100	25	0.790		0.9																							
Tributyl phosphate	(C4H9)3PO4	100	20	0.980				A					A	A	c	B	A	A	D	B	D	D		C					
Tributyl phosphate	(C4H9)3PO4	100	60					A					A	A	c	c	C	A	D		D	D		C					

Liquid	Chemical Formula	Concentration %	Temp, degree C	Specific gravity kg/dm3	Viscosity cSt	Vapour pressure kPa	Bronze	Aluminium	Cast iron	Ductile iron	Hastelloy B	Hastelloy C	Stainless Steel SIS 2333	Stainless Steel SIS 2343	EP - Epoxy	CPVC	PP	PVDF	PTFE	FPM - Viton	EPDM - EPT	NBR - Nitrile	CR - Neoprene	Kairez	Hytrek	Carbon	Silicon	Ceramic		
Tributyl phosphate	(C4H9)3P04	100	80					A						A	A	C		D		D		D	D		c					
Tributylamine	(C4H9)3N	100	20	0.780																										
Trichloroacetic acid	CCl <sub>3</sub> cooH,CCl <sub>3</sub> CO <sub>2</sub> H	50	20				A	D	D			A		D			A	A	A	D	C	D	D	A		A				
Trichloroacetic acid	CCl <sub>3</sub> cooH,CCl <sub>3</sub> CO <sub>2</sub> H	100	20	1.620			A	D	D			A		D	B		A	A	A	D	D	D	B	A		A				
Trichloroacetic acid	CCl <sub>3</sub> cooH,CCl <sub>3</sub> CO <sub>2</sub> H	100	40				A	D	D			A		D	B		A	B	A	D	D	D	B	A						
Trichloroacetic acid	CCl <sub>3</sub> cooH,CCl <sub>3</sub> CO <sub>2</sub> H	100	60				A	D	D			A		D	B		A	C	A	D	D	D	B	A						
Trichloroacetic acid	CCl <sub>3</sub> cooH,CCl <sub>3</sub> CO <sub>2</sub> H	100	80				A	D	D			A		D	B			D	A	D	D	D	B	A						
Trichloroethane (1.1.2 Trichloroethane)	C <sub>2</sub> H <sub>3</sub> Cl <sub>3</sub>	100	20	1.340			D	D	D					A	A		A	A	A	A	D	D	D	D						
Trichloroethylene	C <sub>2</sub> HCl <sub>3</sub> , CCl <sub>2</sub> CHCl	50	20				A	D	C			A		A			A	A	A	A		D	D			A		A		
Trichloroethylene	C <sub>2</sub> HCl <sub>3</sub> , CCl <sub>2</sub> CHCl	100	20	1.464	1	7.7	A	A	C	C		A		A	A	D	B	A	A	A	D	D	D	A		A		A	A	
Trichloroethylene	C <sub>2</sub> HCl <sub>3</sub> , CCl <sub>2</sub> CHCl	100	40				A	A	c	C				A	A	D	C	A	A		D	D	D	A						
Trichloroethylene	C <sub>2</sub> HCl <sub>3</sub> , CCl <sub>2</sub> CHCl	100	60				A	A	c	c				A	A	D	D	A	A		D	D	D	A						
Trichloroethylene	C <sub>2</sub> HCl <sub>3</sub> , CCl <sub>2</sub> CHCl	100	80				A	A	c	c				A	A	D	D	B	A		D	D	D	A						
Trichloromethane (Chloroform), pure	CHCl <sub>3</sub>	100	20	1.480			D							A	D	B	A	A	B	D	D	D								
Trichloropane	CH <sub>3</sub> CHClCHCl <sub>2</sub>	100	20				A		A					A	A					A		D	D							
Trichloropropane	CH <sub>2</sub> ClCHClCH <sub>2</sub> Cl	100	20				A		A					A	A					A		A	A							
Tricresyl phosphate (Lindol), pure	(C <sub>6</sub> H <sub>4</sub> CH <sub>3</sub> O) <sub>3</sub> P0	100	20	1.130			A	A				A		A	A		A		A	D	A	D	D			A				
Triethanolamine	(C <sub>2</sub> H <sub>4</sub> OH) <sub>3</sub> N	100	20	1.120			A	B						A	A		D	D	A	D	A	C	A	A		A				
Triethyl phosphate		100	20					A						A					A											
Triethylamine	(C <sub>2</sub> H <sub>6</sub> ) <sub>3</sub> N	100	20	0.725		7.1	A					A		A	A	A	B		A		A	B				A				
Triethylamine	(C <sub>2</sub> H <sub>5</sub> ) <sub>3</sub> N	100	40				A					A		A	A	A	C		A		A									
Triethylamine	(C <sub>2</sub> H <sub>5</sub> ) <sub>3</sub> N	100	60				A					A		A	A	A	D		A		A									
Trimethyl carbinol	(CH <sub>3</sub> ) <sub>3</sub> COH	100	20	0.790		4																								
Trimethyl propane		100	20															A	A											
Trimethylamine	(CH <sub>3</sub> ) <sub>3</sub> N	100	20	0.630		250																								
Trimethylene	C <sub>3</sub> H <sub>6</sub>	100	20	0.610																										
Trinitrobenzene	C <sub>6</sub> H <sub>3</sub> (N0 <sub>2</sub> ) <sub>3</sub>	100	20	1.690																										
Trinitrotoluene	C <sub>6</sub> H <sub>2</sub> (N0 <sub>2</sub> ) <sub>3</sub> CH <sub>3</sub>	100	20	1.654								A		A	A					B	D	D	B							
Trioctyl phosphate	(C <sub>8</sub> H <sub>17</sub> ) <sub>3</sub> P04	100	20														A		A	D	A	D	D							
Triphenyl phosphite		100	20																											
Trisodium phosphate		100	20						C					A					A											
Triton oil		100	20				A		A					A	A					A		A	A							
Tung oil (China-wood oil)		100	20						A					B					A	A	D	A	B							
Türbine oil (#140)		100	20				A	A	A					A	A	A	B	A	A	A	D	A	A							
Turpentine	(C <sub>10</sub> )H <sub>16</sub>	100	20	0.860	2	0.67	D	A	A	B				A	A	A	B	A	A	A	B	B	D							
Turpentine	(C <sub>10</sub> )H <sub>16</sub>	100	40				D	A	A	B				A	A	A	c	A	A				D							
Turpentine	(C <sub>10</sub> )H <sub>16</sub>	100	60				D	A	A	B				A	A	A	D	A	A			D								
Turpentine oil	(C <sub>10</sub> )H <sub>16</sub>	100	20	0.860		0.67	A										D	D	A	A		A				A				



Liquid	Chemical Formula	Concentration %	Temp, degree C	Specific gravity kg/dm3	Viscosity cSt	Vapour pressure kPa	Bronze	Aluminium	Cast iron	Ductile iron	Hastelloy B	Hastelloy C	Stainless Steel SIS 2333	Stainless Steel SIS 2343	EP - Epoxy	CPVC	PP	PVDF	PTFE	FPM - Viton	EPDM - EPT	NBR - Nitrile	CR - Neoprene	Kairez	Hytrek	Carbon	Silicon	Ceramic		
Uranium hexafluoride	UFe	100	25	5.100																										
Uranium nitrate	UO2(NO3)2+6H2O	100	15	2.807																										
Urea (Carbamide)	CO(NH2)2, NH2CONH2	30	20																											
Urea (Carbamide)	CO(NH2)2, NH2CONH2	100	20	1.320			C	A	A	C		A		A	A	A	A	A	A	A	A	A	D			A				
Urea formalin		100	20												A					A		A	C							
Uric acid	C5H4N4O3	33	20						D			A					A	A	A							A				
Urine		100	20				C	D						A	A	A	A	A	A	A	A	A	D							
Valclene 200 (Dupont)		100	20				A								A						D		A	D						
Vanilla extract		100	20											A	A						C		A	A						
Varnish		100	20				A	A	C	C				A	A				A	A	A	D	A	D						
Vaseline (Petrolatum), pure		100	20											A	A	A	A	A	A	A	D	A	A			A				
Vaseline oil		100	20															A		A		A	B							
Vegetable juice		100	20				C		D					A	A					A		A	D							
Vegetable oil		100	20				A	A	C					A	A	A	A	A	A	A	A	A	A	B						
Vinegar		100	20				C	A	C					A	A	A	A	A	A	A	A	C	C							
Vinyl acetate	C4H6O2,CH3COOCH=CH2	100	20	0.932	11	12								A		D	A	A	A	D	B	D	A	A						
Vinyl acetate	C4H6O2,CH3COOCH=CH2	100	40												D	A	A	A	A	D	D	D		A						
Vinyl acetylene	CHCCHCH2	100	20												A					A		A	P							
Vinyl bromide	CH2=CHBr	100	20	1.516																										
Vinyl chloride	CH2=CHCl	100	20	0.983	1	340											A	A	A	A	C	D	D	A						
Vinyl ethyl ether	CH2=CHOCH2CH3	100	20	0.770		53.2																								
Vinyl fluoride	CH2=CHF	100	20																											
Vinyl methyl ether	CH2=CHOCH3	100	20	0.750		148																								
Vinyl styrene	C6H4(CH:CH2)2	100	20	0.930																										
Vinylidene fluoride	CH2CF2	100	20																											
Viscose spinning solution		100	20														A	A					D							
Water	H2O	100	20	0.997		2.3		B		c				A		A	A	A	A	A	A	A	A							
Water	H2O	100	60					B		c				A		A	A	A	A	A	A	A	B	A						
Water	H2O	100	80					B		c				A		A	A	A	A	A	A	A	C	A						
Water (Sewage water)	H2O	100	20					B	D	D				A		A	A	A	A	A	A	A	A							
Water, acid, mine	H2O	100	20				C	D	C					A	A	A	A		A	A		A	C							
Water, chlorinated	H2O	100	20				A	C	A					A	A		A	A	A	A		A	A			A				
Water, distilled	H2O	100	20	1.000			D	A	D	D				A	A	A	A	A	A	A	A	A	A			A				
Water, distilled, de-ionized	H2O	100	20				D	D		D				A			A	A	A							A				
Water, fresh	H2O	100	20				A		A					A	A	A	A	A	A	A	A	A	A							
Water, salt	H2O	100	20				A	B	D					A	A	A	A	A	A	A	A	A	A		A					
VWater, salt	H2O	100	40				A	B	D					A	A	A	A	A	A	A	A	B	A		A					
Water, sea water	H2O	100	20	1.020		2.3	A	D	D	D		D		A	A	A	A	A	A	A	A	A	A			A				





You are in exact point where quality,  
experience and technology meet.

Our Quality Certificates





DES Sanayi Sitesi 107. Sokak B14 Blok No:2 Umraniye, İstanbul / Turkey

**Phone:** + 90 (216) 212 02 46 | **Fax:** +90 216 660 13 08

**Web:** [www.ekinendustriyel.com](http://www.ekinendustriyel.com) | **E-mail:** [info@ekinendustriyel.com](mailto:info@ekinendustriyel.com)

